

# NW Array Drilling and Trenching

## Confirm Extensions to Gold

### Mineralisation

**Felix Gold (ASX:FXG)** is reporting drilling and trenching gold assay results from the Northwest Array at Treasure Creek. These results are from the drill program in a tightly focused, small-footprint target area designed to test the high-grade antimony mineralisation within the broader gold halo. The program supported the antimony strategy but also has confirmed strong gold mineralisation. Drilling within this zone has targeted the orientation and continuity of massive stibnite veins across multiple directions, as well as the north-northeast trending breccia unit. The program also supports waste rock characterisation and other relevant data required for near-term production studies. The dataset reflects the high density of drilling within a confined area. The initial step-out trenching approximately 130 metres west of the main target area has been completed, with those results also included here.

## Key Highlights

### High-Grade Gold Results

- Surface trench 25NWTR001 exposes **67m of gold mineralisation across 90m (26m @ 1.86 g/t Au, including 12m @ 2.86 g/t Au)**— located 130m west of the main 2025 drilling area, extending the NW Array mineralised corridor into an area acquired by Felix in May 2024, confirming historical shallow air-track drilling results.
- Drill results from the main antimony target area continue to confirm the presence of broad zones of gold mineralisation forming halos around antimony vein zones.
- Gold assay results are pending for 44 diamond holes and 18 RC holes. Antimony/ multielement assay results are pending for a further 45 diamond holes and 6 RC holes.
- Best drill results include:
  - **47.36m @ 1.34 g/t Au** from 19.5m, including **7.8 m @ 1.79 g/t Au** from 29.24 m and including **7.09m @ 2.27 g/t Au** from 59.77m (Hole 25TCDC020)
  - **15.71m @ 2.91 g/t Au** from 37.61m, including 11.01m @ 3.87 g/t Au (Hole 25TCDC004)
  - **13.72m @ 2.83 g/t Au**, including **7.62m @ 4.45 g/t Au** from 27.43m (Hole 25TCRC003)
- Mineralisation remains open along strike and at depth.

## Video Update

Watch Joe Webb's 2-minute explainer, ask questions, and join the conversation on our [Investor Hub](#).

Watch Now

## Executive Director's Comment

Felix Gold's Executive Director, Joseph Webb, commented:

*"Following our recent announcement of 47 metres at 2.45 g/t and 29 metres at 3.90 g/t gold from drilling, today's trenching results show the mineralised system extends at least 130 metres further west along strike — with 67 metres of gold mineralisation exposed across a 90-metre trench. **The system remains open in all directions.***

*Gold built this company, however our immediate focus remains building America's first fully integrated antimony supply chain, from ore to metal, on U.S. soil. Our 831,000-ounce JORC gold resource represents significant strategic optionality that we continue to advance in parallel. Today's results reinforce the value embedded in our gold portfolio.*

*NW Array hosts both commodities within the same structural corridor. Gold forms broader mineralisation halos around the antimony-bearing structures being targeted for near-term production. The infrastructure, permitting, and baseline studies serve both antimony and gold. The drilling generates data for the two commodities - one platform, complementary value creation.*

*We are located 30 kilometres by road from Kinross Gold's Fort Knox mill which is a Tier 1 facility actively seeking additional ore under its Kinross Alaska strategy. With gold prices hitting all time high, the potential for a simple extraction strategy is high. We see great potential in the district which is why we are currently the largest landholder in the Fairbanks Gold Mining District ."*

**Cautionary Statement:** The Company cautions that it is assessing the economic viability of near-term antimony production. No Mineral Resources or Ore Reserves have been declared and no JORC-compliant economic studies have been completed. Any progression toward production remains subject to further technical, regulatory and commercial evaluation, permitting approvals and formal Board approval. The Company may elect to progress parts or all of the project prior to completion of such compliant studies. Statements regarding peer projects are based on the Company's review of publicly available information and the Company has not conducted an exhaustive review of all antimony projects globally.

## A Premier Gold Mining District

Felix is the largest landholder in the Fairbanks Gold Mining District, with **831,000 oz of JORC gold resources** and significant exploration upside across >1500 km<sup>2</sup> (388,000+ acres) in Alaska's most productive gold region. The district has produced over 16 million ounces of gold historically and hosts Kinross Gold's Fort Knox mine — a Tier 1 operation located just 30km from NW Array by paved road. Established infrastructure, including grid power, year-round road access, skilled workforce, and proximity to processing facilities, provides a straightforward development pathway

(Fig 1). Kinross's Alaska strategy involves consolidating regional ore sources to feed the Fort Knox mill. Kinross is currently trucking ore 400km (250 miles) from Manh Choh, demonstrating willingness to source material from significant distances. NW Array's proximity - 30km versus 400km - represents a potential toll treatment pathway that could complement Felix Gold's immediate antimony focus.




Fig 1. Location of reported gold results from NW Array, shown within the Fairbanks Gold Mining District

## NW Array Prospect

The NW Array Prospect hosts both high-grade antimony and gold mineralisation within the same structural corridor. Gold generally forms a broad mineralisation halo, within which occur the antimony-bearing structures. The same geological system delivers value from the two commodities.

The prospect includes the historic Scrafford Mine, Alaska's second-largest historical antimony producer. Felix Gold's systematic exploration has defined multiple mineralised structures within an expanding footprint, with both gold and antimony mineralisation remaining open in multiple directions.

## Gold Drilling Results — NW Array

### Geological Setting and Interpretation

The NW Array prospect hosts both high-grade antimony and gold mineralisation within the same structural corridor. Gold generally forms a broader mineralisation halo, within which occur the antimony-bearing structures, particularly in brecciated zones.

Drilling and trenching have revealed two main styles of mineralisation:


- **East-west trending vein zones** — individual veins or close-spaced zones of veining, fracturing, and brecciation with quartz fill, dipping approximately 60-70° towards the south to south-southwest
- **“Black breccia” zones** — broader mineralised fault structures with angular clasts of silicified wallrock and fine-grained disseminations, dipping approximately 50° towards the southeast to east

High gold grades are commonly associated with these brecciated zones and correspond with antimony-bearing structures. The Sb-enriched mineralised system extends over an area approximately 200 metres by 125 metres to depths exceeding 150 metres vertically, and remains open along strike and at depth.

### Surface Trenching Results

Trench 25NWTR001 is located approximately 130 metres west of the southern end of the main drilling area which targeted antimony veining, and was designed to confirm high-grade gold results from historical shallow air-track drill holes with a best intersection of 12m @ 1.7 g/t Au. The area was acquired by Felix in mid-2024 and was not trenched during earlier programs in 2022-2023. The current 90-metre trench exposed a total of 67 metres of >0.3 g/t gold, extending the structural corridor hosting mineralisation significantly beyond the current drill-tested area.

The highest grade intersections in trench 001 from 46m to 72m of 1.86 g/t Au and from 75m to 82m of 1.3 g/t Au are related to a fault breccia developed at the contact between felsic porphyry to the west and schist to the east. The breccia zone is mapped dipping approximately 30° to the east, striking north with a true thickness of approximately 10m. The maximum grade over 1m of 8.27 g/t Au occurs near the western end of this zone close to the contact with porphyry. Three lower-grade zones between 0m and 36m (<1 g/t Au on average) are within silicified and fractured felsic porphyry with minor disseminated sulphides. Antimony grades within the trench are mostly less than 0.1% Sb, despite having some poddy stibnite observed within the fault breccia zone. A few samples returned Sb grades between 0.3% and 0.5%, from fractured felsic porphyry and fault breccia.



**Fig 2.** NW Array Prospect — Selected best intersections from new gold assay results coloured by average intersection grade. Previously reported intersections in lighter colours. Note location of trench 25NWTR001 130m west of southern edge of main drilling area targeting antimony veining.

## Drilling Results

The latest gold assay results from a total of 39 drill holes provide further insights into the geometry and extents of bulk low-grade and high-grade gold mineralisation within the area covered by close spaced drilling targeting narrow antimony veins. The “black breccia” zones that contain antimony mineralisation are confirmed as high-grade gold structures dipping moderately east to south-east, parallel to the western contact of schist and felsic porphyry. Higher gold grades also occur within east to east-southeast trending zones contained within a north-northeast trending corridor.

Black breccia intersections with high-grade gold assays include diamond holes 25TCDC003 (19.41m @ 1.96 g/t Au from 30.82m), 25TCDC004 (15.71m @ 2.91 g/t Au from 37.61m) and 25TCDC020 (7.09m @ 2.27 g/t Au from 59.77m).

Many of the other significant intersections are related to zones of fractured and silicified felsic porphyry with local clay-altered breccia zones and common iron oxides on fractures. The best results in 25TCDC018 of 39.37m @ 0.98 g/t Au from 29.2m and 25TCDC019 of 34.89m @ 0.99 g/t Au from 27.5m are related to this style of mineralisation. Some of these zones of altered felsic are also associated with antimony veining (for example 25TCDC004 8.11m @ 2.8 g/t Au from 18m), although the latter can also occur without significant gold mineralisation.

Outside the felsic porphyry and black breccia zones there are also some intersections related to fault zones wholly within schist, some of which can locally contain high grades. Hole 25TCDC013 contains two such zones: 13.84m @ 2.66 g/t Au from 23.07m and 1.18m @ 11.59 g/t Au from 44.85m.

Interpretation of results is ongoing, but there is an emerging picture of a mineralised corridor trending north-northeast along the western contact of felsic porphyry and schist. Within this north-northeast trending envelope there are zones trending east to east-northeast that are associated with gold and antimony mineralisation.

## Further Results Pending

To date, out of 67 diamond holes (5,858m) and 56 RC holes (3,077m) drilled at NW Array, antimony/multielement assay results are pending for 45 diamond holes and 6 RC holes. Gold assay results are pending for 44 diamond holes and 18 RC holes.

**Table 1: Significant Gold Intersections**

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
25NWTR001		0	12	12	0.87
25NWTR001	Including	5	11	6	1.2
25NWTR001	And	13	29	16	0.51

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
25NWTR001	And	30	36	6	0.58
<b>25NWTR001</b>	<b>And</b>	<b>46</b>	<b>72</b>	<b>26</b>	<b>1.86</b>
<b>25NWTR001</b>	<b>Including</b>	<b>48</b>	<b>60</b>	<b>12</b>	<b>2.86</b>
25NWTR001	And Including	64	71	7	1.31
25NWTR001	And	75	82	7	1.3
25NWTR001	Including	77	81	4	1.86
25NWTR002		0	2	2	0.58
25TCDC002		3.78	9.11	5.33	0.51
<b>25TCDC002</b>	<b>And</b>	<b>19.3</b>	<b>30.42</b>	<b>11.12</b>	<b>1.99</b>
25TCDC002	Including	20.77	22.89	2.12	3.09
<b>25TCDC002</b>	<b>And Including</b>	<b>26.17</b>	<b>30.42</b>	<b>4.25</b>	<b>3.15</b>
25TCDC002	And	35.37	40.34	4.97	0.58
25TCDC002	And	45.24	50.38	5.14	0.64
<b>25TCDC003</b>		<b>2</b>	<b>28.9</b>	<b>26.9</b>	<b>1.46</b>
<b>25TCDC003</b>	<b>Including</b>	<b>15.03</b>	<b>28.9</b>	<b>13.87</b>	<b>2.41</b>
<b>25TCDC003</b>	<b>And</b>	<b>30.82</b>	<b>50.23</b>	<b>19.41</b>	<b>1.96</b>
25TCDC003	Including	30.82	33.62	2.8	1.92
<b>25TCDC003</b>	<b>And Including</b>	<b>39.94</b>	<b>50.23</b>	<b>10.29</b>	<b>2.88</b>
<b>25TCDC004</b>		<b>1.26</b>	<b>16.76</b>	<b>15.5</b>	<b>0.88</b>
25TCDC004	Including	6.15	8.67	2.52	1.21
25TCDC004	And Including	12.8	15.43	2.63	1.8
<b>25TCDC004</b>	<b>And</b>	<b>18</b>	<b>26.11</b>	<b>8.11</b>	<b>2.8</b>
<b>25TCDC004</b>	<b>Including</b>	<b>19.98</b>	<b>24.91</b>	<b>4.93</b>	<b>4.13</b>
25TCDC004	And	30.48	32.63	2.15	0.72
<b>25TCDC004</b>	<b>And</b>	<b>37.61</b>	<b>53.32</b>	<b>15.71</b>	<b>2.91</b>
<b>25TCDC004</b>	<b>Including</b>	<b>37.61</b>	<b>48.62</b>	<b>11.01</b>	<b>3.87</b>
<b>25TCDC005</b>		<b>1.55</b>	<b>14.14</b>	<b>12.59</b>	<b>1.28</b>

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
<b>25TCDC005</b>	<b>Including</b>	<b>2.72</b>	<b>13.11</b>	<b>10.39</b>	<b>1.46</b>
25TCDC005	And	23.86	40.9	17.04	0.52
25TCDC005	And	46.94	53.13	6.19	1.22
25TCDC005	And Including	47.8	50.7	2.9	2.14
25TCDC006		9.08	15.9	6.82	0.79
25TCDC006	Including	9.08	12.68	3.6	1.17
25TCDC006	And	19.15	20.45	1.3	1.05
<b>25TCDC006</b>	<b>And</b>	<b>25.67</b>	<b>39.92</b>	<b>14.25</b>	<b>1.97</b>
<b>25TCDC006</b>	<b>Including</b>	<b>32.05</b>	<b>39.92</b>	<b>7.87</b>	<b>3.2</b>
25TCDC011		0	10.6	10.6	0.95
25TCDC011	Including	3.41	8.32	4.91	1.33
<b>25TCDC011</b>	<b>And</b>	<b>14.82</b>	<b>38.02</b>	<b>23.2</b>	<b>0.87</b>
25TCDC011	Including	23.35	25.97	2.62	1.2
25TCDC011	And Including	31.42	36.77	5.35	1.52
25TCDC011	And	38.61	44.4	5.79	1.78
25TCDC011	Including	39.2	44.4	5.2	1.91
<b>25TCDC011</b>	<b>And</b>	<b>53.84</b>	<b>66.03</b>	<b>12.19</b>	<b>0.97</b>
25TCDC011	Including	54.3	61.4	7.1	1.32
25TCDC012		0	5.83	5.83	0.63
25TCDC012	And	12.9	17.98	5.08	0.64
25TCDC012	And	23.59	31.6	8.01	0.33
<b>25TCDC012</b>	<b>And</b>	<b>32.5</b>	<b>42.3</b>	<b>9.8</b>	<b>1.27</b>
<b>25TCDC012</b>	<b>Including</b>	<b>36.4</b>	<b>41.51</b>	<b>5.11</b>	<b>2.09</b>
25TCDC012	And	44.35	51.69	7.34	0.67
25TCDC013		0	12.37	12.37	0.85
25TCDC013	Including	3.28	7	3.72	1.39
25TCDC013	And	16.32	18.5	2.18	1.57

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
<b>25TCDC013</b>	<b>And</b>	<b>23.07</b>	<b>36.91</b>	<b>13.84</b>	<b>2.66</b>
<b>25TCDC013</b>	<b>Including</b>	<b>24.1</b>	<b>30.1</b>	<b>6</b>	<b>3.62</b>
<b>25TCDC013</b>	<b>Including</b>	<b>32.01</b>	<b>35.42</b>	<b>3.41</b>	<b>3.59</b>
<b>25TCDC013</b>	<b>And</b>	<b>44.85</b>	<b>46.66</b>	<b>1.81</b>	<b>11.59</b>
25TCDC016		21.75	25.6	3.85	0.38
25TCDC016	And	38.51	46.3	7.79	0.76
25TCDC016	Including	44.7	46.3	1.6	2.1
25TCDC017		20.84	22.08	1.24	1.02
25TCDC017	And	28.59	33.4	4.81	0.5
25TCDC017	And	46.25	50.98	4.73	0.56
<b>25TCDC017</b>	<b>And</b>	<b>58.69</b>	<b>74.22</b>	<b>15.53</b>	<b>1.74</b>
25TCDC017	Including	62.4	66.8	4.4	1.63
<b>25TCDC017</b>	<b>And Including</b>	<b>68.28</b>	<b>74.22</b>	<b>5.94</b>	<b>2.94</b>
25TCDC018		0	10.72	10.72	0.44
25TCDC018	And	11.94	26.88	14.94	0.62
<b>25TCDC018</b>	<b>And</b>	<b>29.2</b>	<b>68.57</b>	<b>39.37</b>	<b>0.98</b>
<b>25TCDC018</b>	<b>Including</b>	<b>30.72</b>	<b>45.24</b>	<b>14.52</b>	<b>1.45</b>
<b>25TCDC018</b>	<b>And</b>	<b>69.8</b>	<b>82.63</b>	<b>12.83</b>	<b>1.54</b>
<b>25TCDC018</b>	<b>Including</b>	<b>72.42</b>	<b>82.63</b>	<b>10.21</b>	<b>1.8</b>
25TCDC018	And	85.77	87.48	1.71	2.11
25TCDC019		0	7.86	7.86	0.58
25TCDC019	And	11.31	26.43	15.12	0.58
<b>25TCDC019</b>	<b>And</b>	<b>27.5</b>	<b>62.39</b>	<b>34.89</b>	<b>0.99</b>
25TCDC019	Including	27.5	35.03	7.53	1.19
25TCDC019	And Including	38.23	43.8	5.57	1.17
25TCDC019	And Including	44.93	49.75	4.82	1.04
25TCDC019	And Including	54.8	59.95	5.15	1.51

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
25TCDC019	And	63.67	73.9	10.23	0.97
25TCDC019	Including	64.87	71.62	6.75	1.24
25TCDC020		0	12.37	12.37	0.45
<b>25TCDC020</b>	<b>And</b>	<b>19.5</b>	<b>66.86</b>	<b>47.36</b>	<b>1.34</b>
<b>25TCDC020</b>	<b>Including</b>	<b>29.24</b>	<b>37.04</b>	<b>7.8</b>	<b>1.79</b>
25TCDC020	And Including	38.42	43.69	5.27	1.45
25TCDC020	And Including	53	57.17	4.17	2.07
<b>25TCDC020</b>	<b>And Including</b>	<b>59.77</b>	<b>66.86</b>	<b>7.09</b>	<b>2.27</b>
25TCDC024		27.03	35.23	8.2	0.96
25TCDC024	Including	28.15	31.9	3.75	1.19
25TCDC024	And	36.82	44.05	7.23	1.07
25TCDC024	Including	40.32	44.05	3.73	1.72
25TCDC024	And	75.34	79.68	4.34	0.97
25TCDC024	Including	76.4	79.1	2.7	1.13
25TCDC045		2.74	3.51	0.77	1.88
25TCDC045		22.25	26.52	4.27	1.26
25TCDC045	Including	22.25	23.43	1.18	2.77
25TCDC051		57.39	58.14	0.75	1.5
25TCDC051	And	65.32	68.58	3.26	0.34
25TCDC051	And	78.94	83.65	4.71	0.35
25TCMW002		68.58	71.63	3.05	0.34
<b>25TCRC002</b>		<b>1.52</b>	<b>16.76</b>	<b>15.24</b>	<b>0.91</b>
25TCRC002	Including	13.72	15.24	1.52	2.61
25TCRC002	And	25.91	32	6.09	0.54
25TCRC002	And	47.24	50.29	3.05	0.44
25TCRC003		1.52	6.1	4.58	0.51
25TCRC003	And	12.19	15.24	3.05	0.47

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
<b>25TCRC003</b>	<b>And</b>	<b>27.43</b>	<b>41.15</b>	<b>13.72</b>	<b>2.83</b>
<b>25TCRC003</b>	<b>Including</b>	<b>27.43</b>	<b>35.05</b>	<b>7.62</b>	<b>4.45</b>
25TCRC003	And Including	39.62	41.15	1.53	2.07
<b>25TCRC004</b>		<b>1.52</b>	<b>27.43</b>	<b>25.91</b>	<b>1.1</b>
<b>25TCRC004</b>	<b>Including</b>	<b>1.52</b>	<b>13.72</b>	<b>12.2</b>	<b>1.42</b>
25TCRC004	And Including	21.34	22.86	1.52	2.65
25TCRC004	And	39.62	41.15	1.53	1.06
25TCRC004	And	48.77	60.96	12.19	0.45
25TCRC008		27.43	30.48	3.05	0.5
25TCRC008	And	53.34	57.91	4.57	0.7
25TCRC009		41.15	47.24	6.09	1.3
25TCRC009	Including	41.15	45.72	4.57	1.61
25TCRC010		6.1	7.62	1.52	0.73
<b>25TCRC010</b>	<b>And</b>	<b>13.72</b>	<b>33.53</b>	<b>19.81</b>	<b>0.87</b>
25TCRC010	Including	15.24	19.81	4.57	1.39
25TCRC010	And	50.29	62.48	12.19	0.53
25TCRC010	And	64.01	71.63	7.62	0.76
25TCRC014		0	7.62	7.62	0.64
<b>25TCRC014</b>	<b>And</b>	<b>12.19</b>	<b>36.58</b>	<b>24.39</b>	<b>0.53</b>
<b>25TCRC014</b>		<b>38.1</b>	<b>53.34</b>	<b>15.24</b>	<b>1.09</b>
25TCRC014	Including	38.1	44.2	6.1	1.35
25TCRC014	And Including	45.72	50.29	4.57	1.27
25TCRC015		4.57	13.72	9.15	0.59
<b>25TCRC015</b>	<b>And</b>	<b>15.24</b>	<b>50.29</b>	<b>35.05</b>	<b>0.7</b>
25TCRC015	Including	42.67	47.24	4.57	1.64
25TCRC019		10.67	16.76	6.09	0.66
25TCRC021		1.52	12.19	10.67	0.46

Hole ID		From (m)	To (m)	Interval (m)	Au g/t
25TCRC021	And	18.29	25.91	7.62	0.53
25TCRC021	And	27.43	32	4.57	0.43
25TCRC021	And	33.53	38.1	4.57	0.47
25TCRC021	And	39.62	45.72	6.1	0.71
25TCRC021	And	50.29	59.44	9.15	0.84
25TCRC021	Including	54.86	59.44	4.58	1.05
25TCRC026		42.67	51.82	9.15	0.84
25TCRC026	Including	48.77	51.82	3.05	1.13
25TCRC028		39.62	42.67	3.05	0.44
25TCRC029		36.58	39.62	3.04	0.56
25TCRC030		54.86	62.48	7.62	0.67
<b>25TCRC031</b>		<b>33.53</b>	<b>62.48</b>	<b>28.95</b>	<b>0.63</b>
25TCRC033		1.52	12.19	10.67	0.53
25TCRC033	And	21.34	28.96	7.62	0.38
<b>25TCRC033</b>	<b>And</b>	<b>32</b>	<b>64.01</b>	<b>32.01</b>	<b>1.07</b>
25TCRC033	Including	35.05	42.67	7.62	1.05
25TCRC033	And Including	44.2	48.77	4.57	1.42
<b>25TCRC033</b>	<b>And Including</b>	<b>57.91</b>	<b>64.01</b>	<b>6.1</b>	<b>1.9</b>
25TCRC048		12.19	25.91	13.72	0.75
25TCRC048	And	35.05	38.1	3.05	0.89
25TCMW003	No significant intersections meeting reporting criteria				
25TCMW005	No significant intersections meeting reporting criteria				
25TCRC022	No significant intersections meeting reporting criteria				
25TCRC023	No significant intersections meeting reporting criteria				
25TCRC024	No significant intersections meeting reporting criteria				
25TCRC025	No significant intersections meeting reporting criteria				

*Note: Reported intervals are downhole lengths. True widths are estimated at 50-75% of downhole length depending on angle of drilling relative to structures. Significant intersections calculated using 0.3 g/t Au cut-off with maximum 3m internal dilution.*

## Table 2: Collar Details

Coordinates: NAD 83 Zone 6 North


HoleID	Hole Type	UTM_NAD83_Zone 06N			EOH (m)	Azimuth (m)	Dip (m)
		East	North	RL (m)			
25NWTR001	TR	461544.4	7208874	500.6	90	105	-11.5
25NWTR002	TR	461728.5	7208950	466.2	37	120	-13
25TCDC002	DD	461831.3	7209061	440.789	61.26	199.5	-51.5
25TCDC003	DD	461830.1	7209061	440.829	61.14	224.6	-54.3
25TCDC004	DD	461805.6	7209016	443.865	62.83	359.6	-44.4
25TCDC005	DD	461806.7	7209018	444.201	68.49	47.6	-44.7
25TCDC006	DD	461803.8	7209018	444.035	61.39	334.6	-46
25TCDC011	DD	461775.1	7209024	452.978	67.7	60	-45
25TCDC012	DD	461773.5	7209025	453.014	60.56	30	-45
25TCDC013	DD	461771.5	7209025	453.05	65.53	359.1	-45
25TCDC016	DD	461747.9	7208929	457.183	68.98	4.6	-46.4
25TCDC017	DD	461750.1	7208928	457.212	74.22	34.3	-48
25TCDC018	DD	461732.6	7208891	457.922	87.48	26.5	-47.8
25TCDC019	DD	461731.7	7208892	457.985	77.42	14.5	-44.9
25TCDC020	DD	461730.6	7208892	457.956	76.17	358.2	-45.2
25TCDC024	DD	461783.1	7208954	448.901	80.47	311.3	-45
25TCDC045	DD	461751.4	7208797	449.661	78.49	35	-45
25TCDC051	DD	461618.4	7208803	482.398	88.39	200	-45
25TCMW002	RC	461244.7	7208442	548.044	79.25	268.4	-89.7
25TCMW003	RC	462259.4	7208758	348.299	13.72	87	-89.3
25TCMW005	RC	464434	7210337	243.578	12.19	347.7	-88.7

HoleID	Hole Type	UTM_NAD83_Zone 06N			EOH (m)	Azimuth (m)	Dip (m)
		East	North	RL (m)			
25TCRC002	RC	461828.5	7209063	440.856	50.29	294.2	-59.6
25TCRC003	RC	461822.1	7209040	441.86	50.29	24.7	-59.8
25TCRC004	RC	461805.7	7209021	446.505	60.96	26	-59.6
25TCRC008	RC	461769	7208919	451.435	57.91	2.1	-45.2
25TCRC009	RC	461769.5	7208919	451.346	57.91	29.6	-46.2
25TCRC010	RC	461760.5	7208900	451.837	76.2	0.2	-45.3
25TCRC014	RC	461752.4	7208881	452.178	53.34	24.5	-45.2
25TCRC015	RC	461753.1	7208882	452.181	50.29	359.4	-44.6
25TCRC019	RC	461785.6	7208960	448.651	50.29	170.2	-44.9
25TCRC021	RC	461752.8	7208875	452.267	60.96	72.9	-49.3
25TCRC022	RC	461787.3	7208901	445.862	60.96	2.5	-45.5
25TCRC023	RC	461787.8	7208902	445.895	50.29	34.4	-44.2
25TCRC024	RC	461785	7208903	445.84	50.29	55.1	-55.1
25TCRC025	RC	461750.4	7208932	457.162	54.86	49.6	-44.5
25TCRC026	RC	461748.2	7208933	457.249	51.82	26.5	-45
25TCRC028	RC	461744.5	7208932	457.163	50.29	336.3	-44.7
25TCRC029	RC	461745.7	7208913	457.434	60.96	25.3	-44.8
25TCRC030	RC	461744.2	7208913	457.932	64.01	8.8	-43.1
25TCRC031	RC	461742.5	7208911	458.239	65.53	352.5	-45.2
25TCRC033	RC	461730.8	7208890	459.315	70.1	14.6	-44.2
25TCRC048	RC	461724	7208940	463.997	50.29	39.3	-46


TR = Trench, DD = Diamond Core, RC = Reverse Circulation

Holes 25TCMW002, 25TCMW003, and 25TCMW005 are regional water monitoring bores with no significant intersections.






**Fig 4.** NW Array Prospect — Enlargement of northern part of main drilling area with selected best intersections from new gold assay results (bold text) coloured by average intersection grade. Previously reported intersections in lighter colours.



**Fig 5.** NW Array Prospect — Enlargement of southern part of main drilling area with selected best intersections (bold text) from new gold assay results coloured by average intersection grade. Previously reported intersections in lighter colours.



**Figure 6:** NW Array Prospect — Section A–B 25m width with Significant Gold Intersections From Drill Holes Reported in This Announcement  
Previously reported gold assays (transparent) and antimony intersections >0.2% Sb (green bars) shown for geological context

This ASX release was approved for release by the Board.  
**ENDS**

## Video Update

Watch Joe Webb's 2-minute explainer, ask questions, and join the conversation on our [Investor Hub](#).

**Watch Now**

## Enquiries

### Joseph Webb

*Executive Director*

Felix Gold Limited

Ph: +61 422 955 411

E: [joe.webb@felixgold.com.au](mailto:joe.webb@felixgold.com.au)

**View website:** [www.felixgold.com.au](http://www.felixgold.com.au)

**Get updates directly to your inbox:** [www.felixgold.com.au/auth/signup](http://www.felixgold.com.au/auth/signup)

**View this Announcement:** <https://www.felixgold.com.au/link/rA00Yy>

## About Felix Gold

**Felix Gold Limited (ASX: FXG)** is advancing two complementary opportunities in Alaska's Fairbanks Mining District: near-term antimony production and district-scale gold.

**Antimony:** Felix Gold is building America's Antimony Solution — a fully integrated domestic supply chain from proven U.S. ore. The Treasure Creek Antimony Project hosts one of the only proven sources of high-grade antimony ore in the United States. With ~90% antimony-bearing minerals and virtually no deleterious elements, Felix Gold has demonstrated military-grade antimony concentrate and 98% extraction — results that, to the Company's knowledge, no other Western project has publicly achieved.

**Gold:** Felix Gold is the largest landholder in the Fairbanks Mining District, with 831,000 oz of JORC gold resources located 30km from Kinross's Fort Knox mill — a Tier 1 operation actively seeking third-party ore.

The same infrastructure, permitting pathway, and team serve both commodities. Mineralisation outcrops at surface adjacent to year-round paved road with grid power, just 30km from Fairbanks. No federal land significantly reduces permitting timeframes compared to other U.S. critical minerals projects.

Visit [www.felixgold.com.au](http://www.felixgold.com.au) for more information.

## Competent Person Statements

The information in this report that relates to Exploration Results is based on, and fairly represents, information compiled by Dr James Lally, a Competent Person who is a Member of The Australian Institute of Geoscientists. Dr Lally is an independent consultant to Felix Gold Limited and is a shareholder in the Company. Dr Lally has sufficient experience, which is relevant to the style of mineralisation and type of deposit under consideration and to the activity which is being undertaken to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves.' Dr Lally consents to the inclusion in this report of the matters based on his information in the form and context in which it appears.

## Forward-Looking Statements

Various statements in this release constitute statements relating to intentions, future acts and events. Such statements are generally classified as "forward-looking statements" and involve known and unknown risks, uncertainties and other important factors that could cause those future acts, events and circumstances to differ materially from what is presented or implicitly portrayed herein. Words such as "anticipates", "expects", "intends", "plans", "believes", "seeks", "estimates", "may", "potential", "pathway", "aims", "targeting" and similar expressions are intended to identify forward-looking statements. Forward-looking statements in this announcement include references to potential third-party processing or toll treatment arrangements for gold, future exploration programs and their anticipated outcomes, and infrastructure advantages and development potential. With respect to gold development specifically: no feasibility study has been completed, no commercial agreements exist with third parties for ore processing, and there is no certainty that any toll treatment arrangement will be achieved. Felix cautions shareholders and prospective shareholders not to place undue reliance on these forward-looking statements and references to what events have transpired for other entities, which reflect the view of Felix only as of the date of this release. The forward-looking statements made in this release relate only to events as of the date on which the statements are made. Various statements in this release may also be based on the circumstances of other entities. Felix gives no assurance that the anticipated results, performance or achievements expressed or implied in those statements will be achieved.

## Previous Disclosure – 2012 JORC Code

The information in this release that relates to Exploration Results, Mineral Resources and Exploration Targets for Felix's Fairbanks Gold Projects was extracted from the following ASX Announcements:

**29 Jan 2026 FXG: Drilling Confirms Broad Zones of Gold Mineralisation at Treasure Creek**  
**27 Jan 2025 FXG: Antimony Metal Production Program Commences**  
**25 Nov 2025 FXG: Shallow High-grade Gold Results at Treasure Creek**  
**23 Jan 2025 FXG: High-grade Antimony and Gold Results from Trenching**  
**20 June 2024 FXG: Maiden NW Array Inferred Mineral Resource**  
**16 May 2024 FXG: Felix Gold Secures Strategic Claims, Expanding Scale Potential of NW Array Gold Trend**  
**10 Apr 2024 FXG: North West Array Bottle Roll Gold Recoveries Average 90%**  
**19 Oct 2023 FXG: High Grade Antimony Assays up to 28% Sb**  
**11 Aug 2023 FXG: Assay Results Unveiling Substantial Gold Zones with Continued High-Grade Antimony Enrichment**  
**24 July 2023 FXG: Continuation of Broad Zones of Gold and High-Grade Stibnite from NW Array**  
**17 July 2023 FXG: High-Grade Critical Mineral Discovery at NW Array**  
**04 July 2023 FXG: NW Array Drilling Announcement**  
**03 July 2023 FXG: NW Array Drilling Returns Broad Gold Intercepts**  
**30 May 2023 FXG: Drilling Commenced at NW Array**  
**14 Mar 2023 FXG: Exploration Target for NW Array**  
**03 Feb 2023 FXG: Deeper Gold Mineralization and Prospective Feeder Zones Discovered**  
**19 Jan 2023 FXG: New Gold Zones Identified in Reconnaissance Drilling**  
**09 Dec 2022 FXG: Scrafford Shear Potential Grows and High-Grade Antimony Initiatives Commenced**  
**01 Dec 2022 FXG: Near-Surface Gold Zones Extended into Northern Treasure Creek**  
**18 Oct 2022 FXG: Significant Expansion of NW Array Gold Zone**  
**05 Oct 2022 FXG: 400M Traverse of Thick Gold Mineralisation Open**  
**01 Aug 2022 FXG: Multiple Thick, Near-Surface Intercepts at Treasure Creek**  
**22 Jun 2022 FXG: Step-out Drilling Success at Treasure Creek**  
**28 Jan 2022 FXG: Felix Gold Prospectus**

A copy of such announcements is available to view on the Felix Gold Limited website [felixgold.com.au/announcements](http://felixgold.com.au/announcements). **These previous reports were issued in accordance with the 2012 Edition of the JORC Code.** The Company confirms that it is not aware of any new information or data that materially affects the information included in the original market announcements. The Company confirms that the form and context in which the Competent Person's findings are presented have not been materially modified from the original market announcement.

## APPENDIX: JORC Code Table 1 Report

### Section 1: Sampling Techniques and Data

Criteria	Explanation	Commentary
<b>Sampling techniques</b>	<ul style="list-style-type: none"> <li><i>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as downhole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</i></li> <li><i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i></li> <li><i>Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems.</i></li> <li><i>Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</i></li> </ul>	<ul style="list-style-type: none"> <li>Trenches were excavated using a mechanical excavator to a depth of 1.5 metres. Samples were collected along 1 metre horizontal lengths by chipping the exposed area along the trench wall about 0.75m above the floor with a geological hammer. Polyweave bags were placed under the sampling interval to collect sample debris and to avoid contamination with other material. Sample weights varied between 2.5kg and 5kg.</li> <li>Reverse Circulation drilling was sampled on 1.52 m (5 feet) intervals from which 5-6kg was split and pulverised / crushed to produce samples for ICP multi-element analysis, high grade Sb analysis and gold analysis by PhotonAssay™</li> <li>Diamond drill core was sampled over downhole lengths between 0.3m and 2.5m (average 1m) to produce samples for ICP multi-element analysis, high grade Sb analysis and gold analysis by PhotonAssay™ . Diamond drill-core sample intervals were adjusted based on changes in geology.</li> </ul>

Criteria	Explanation	Commentary
<p><b>Drilling techniques</b></p>	<ul style="list-style-type: none"> <li>• <i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face- sampling bit or other type, whether core is oriented and if so, by what method, etc).</i></li> </ul>	<ul style="list-style-type: none"> <li>• Reverse Circulation (RC) holes were drilled with a 76mm (3 inch) face-sampling hammer with 73mm (2.875 inch) drill rods and 102mm (4 inch) casing.</li> <li>• Diamond holes were wireline HQ (63.5mm diameter) holes.</li> <li>• The diamond drill program reported here was undertaken by C-n-C Drilling LLC utilizing CS 14 skid mounted drill.</li> <li>• Core was oriented wherever possible for collection of structural data using a Reflex ACTIII</li> <li>• The core was reconstructed into continuous runs on a cradle for orientation marking before it was laid in the box at the drill.</li> </ul>

Criteria	Explanation	Commentary
<p><b>Drill sample recovery</b></p>	<ul style="list-style-type: none"> <li>• <i>Method of recording and assessing core and chip sample recoveries and results assessed.</i></li> <li>• <i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i></li> <li>• <i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i></li> </ul>	<ul style="list-style-type: none"> <li>• RC samples were visually assessed for recovery and were considered representative of bedrock intersected.</li> <li>• For several RC holes the first (and sometimes second) samples had insufficient recoveries from the splitter to provide enough material for a photonassay analysis.</li> <li>• Visual inspection of samples estimated no significant loss of sample from each 1.52m interval.</li> <li>• No relationship between sample recovery and reported analyses has been established.</li> <li>• Diamond core recovery was determined by measuring the total length of core in the barrel over the run length.</li> <li>• Hole depths were checked against the drillers core blocks at the time of processing. Inconsistencies between the logging and the driller's depth measurement blocks were investigated.</li> <li>• Diamond core samples are considered dry. The recovery and condition are recorded between every core block. Generally, recovery is 98-100% but on very rare occasions in weathered material or very broken material, recovery was down to 50%.</li> <li>• For Diamond drilling, contractors adjust the rate of drilling and method of recovery issues arise</li> <li>• No significant sample loss or bias has been noticed</li> </ul>

Criteria	Explanation	Commentary
<p><b>Logging</b></p>	<ul style="list-style-type: none"> <li>• <i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i></li> <li>• <i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i></li> <li>• <i>The total length and percentage of the relevant intersections logged.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Qualitative logging of RC chips and diamond core for lithology and alteration with semi-quantitative logs for oxide and sulphide mineralisation.</li> <li>• RC and diamond holes were logged in for their entire lengths.</li> <li>• Logging detail is sufficient to support geological modelling and mineral resource estimation.</li> <li>• Representative RC chip samples from each 1.52m interval were placed in chip trays and photographed.</li> <li>• All drill core was photographed wet using a digital camera and stored on the site server.</li> <li>• Core logging included RQD and geotechnical measurements. Structural measurements of veins, fractures and foliation were taken from core using a strip protractor.</li> </ul>

Criteria	Explanation	Commentary
<p><b>Sub-sampling techniques and sample preparation</b></p>	<ul style="list-style-type: none"> <li>• <i>If core, whether cut or sawn and whether quarter, half or all core taken.</i></li> <li>• <i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i></li> <li>• <i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i></li> <li>• <i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i></li> <li>• <i>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</i></li> <li>• <i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Trench samples were submitted in their entirety to the laboratory with no further sub-sampling.</li> <li>• RC intervals were sub-sampled using a 3-tier dry sample splitter attached to the drill rig cyclone. Two samples were taken from each 1.52 m interval, collecting ~12.5% each of the total sample, ranging in weight from 2-3 kg. One sample was retained for archival purposes while the other was sent to the analytical laboratory.</li> <li>• Diamond core sampling intervals were determined by the logging geologist, with sampling breaks at major changes in lithology/alteration or mineralisation. Sub-samples were taken by sawing the HQ core in half along its axis using a Dewalt tile saw on-site. One half of the core was bagged for analysis and the other half retained in the core tray.</li> <li>• Sample sizes for RC and core samples are considered appropriate for both gold and antimony mineralisation.</li> <li>• Quality control procedures for ensuring sample representivity in RC sampling comprised the use of field duplicates and pulp duplicates at a rate of 1 in 20, alternating between the two duplicate types.</li> <li>• Quality control procedures for ensuring sample representivity in core sampling comprised the use of coarse crush duplicate splits from half core samples and pulp duplicates at a rate of 1 in 20, alternating between the two duplicate types.</li> <li>• Duplicate results show that for RC and diamond drilling sampling is representative for antimony, with variability in results linked to assay methods rather than sampling (see below).</li> </ul>

<p><b>Quality of assay data and laboratory tests</b></p>	<ul style="list-style-type: none"> <li>• <i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i></li> <li>• <i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></li> <li>• <i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.</i></li> </ul>	<ul style="list-style-type: none"> <li>• All samples were submitted to MSA Laboratories in Vancouver, Canada for analysis.</li> <li>• Gold was analysed using the PhotonAssay technique (MSA labs CPAu-1D method code). Two splits of approximately 500g of crushed material (70% passing 2mm) are taken from the sub-sample submitted to the laboratory using a riffle splitter. Both splits are subjected to high-intensity X-rays and the resulting gamma radiation emissions are detected and used to determine gold concentration in the sample.</li> <li>• For some very low-volume RC sub-samples at the hole collar there was insufficient material to provide the 500g required for photonassay. These are marked in appendix 2 as “insufficient sample”.</li> <li>• Analysis of split pair samples shows very good correlation with only three outlier values that have yet to be explained.</li> <li>• PhotonAssay results include quality flags for some samples that were reviewed by the CP:             <ul style="list-style-type: none"> <li>○ HB (High Background): Indicates elevated background radiation detected during measurement, primarily affecting samples &lt;0.1 ppm Au. Multi-element data shows Ba, U, and Th levels are generally low.</li> <li>○ HET (Heterogeneous): Indicates high within-sample variability based on multiple readings at different angles. Less than 0.1% of analyses (8 samples) were flagged with HET and of these only 3 samples showed a significant difference between duplicate pairs</li> </ul> </li> <li>• 5% of samples submitted for PhotonAssay are being cross-checked by screen fire assay at the same laboratory. No results for screen fore assays are available as yet.</li> <li>• 4 acid digest with ICP-MS finish was used to analyse for a full suite of trace elements: Ag, Al, As, Ba, Be, Bi, Ca, Cd, Ce, Co, Cr, Cs, Cu, Fe, Ga, Ge, Hf, In, K, La, Li, Mg, Mn, Mo, Na, Nb, Ni, P, Pb, Rb, Re, S, Sb, Sc, Se, Sn, Sr, Ta, Te, Th, Ti, Tl, U, V, W, Y, Zn, Zr.</li> </ul>
--	---	---

Criteria	Explanation	Commentary
		<ul style="list-style-type: none"> <li>4-Acid ICP-MS has an upper detection limit (UDL) of 1% for antimony. Suspected very high-grade (&gt;10% Sb) samples were flagged in sample submission sheets and analysed using a wet titration method. Samples not flagged as high grade, but which returned above UDL assays for ICP were re-analysed using a peroxide fusion with ICP finish. The cut-off ICP Sb assay for re-analysis by peroxide fusion was changed to 3000ppm after results indicated that volatile loss and insoluble precipitate formation was causing some ICP results to severely under-call the Sb grade.</li> <li>Quality control procedures include the insertion of certified reference materials, coarse blanks (locally sourced sand) and field and pulp duplicates. Acceptable levels of accuracy and precision have been established, notwithstanding the issues with some Sb analyses described above</li> </ul>
<p><b>Verification of sampling and assaying</b></p>	<ul style="list-style-type: none"> <li><i>The verification of significant intersections by either independent or alternative company personnel.</i></li> <li><i>The use of twinned holes.</i></li> <li><i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i></li> <li><i>Discuss any adjustment to assay data.</i></li> </ul>	<ul style="list-style-type: none"> <li>A senior manager verifies all significant and anomalous intersections during the drill hole validation process.</li> <li>All primary data was collected in the field by Felix Gold contract staff and supplied in digital format to Felix Gold.</li> <li>No twinned holes were drilled for this data set.</li> <li>All data is stored and validated within a Plexer relational database managed by Gad Solutions in Brisbane, Australia. Data undergoes QA/QC validation prior to being accepted and loaded in the database. Assay results are merged when received electronically from the laboratory. A senior geologist reviews the dataset checking for the correct merging of results and that all data has been received and entered. Any adjustments to this data are recorded permanently in the database. Digital records of assays are stored electronically.</li> <li>No adjustments have been made to the final assay data reported by the laboratory</li> </ul>

Criteria	Explanation	Commentary
<b>Location of data points</b>	<ul style="list-style-type: none"> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> <li>Specification of the grid system used.</li> <li>Quality and adequacy of topographic control.</li> </ul>	<ul style="list-style-type: none"> <li>RC and diamond hole collar locations are initially located by handheld GPS to an accuracy of 3m.</li> <li>After completion of drilling, all drill collars are located with a differential GPS system to an accuracy of 10 cm.</li> <li>Locations are given in NAD83/UTM Zone 6N projection.</li> <li>Diagrams and location table are provided in the report.</li> <li>Topographic control is by detailed airphoto, DTM file, and differential GPD</li> <li>Downhole surveys were conducted using an Axis Champ north-seeking gyro tool which collected data points approximately every 3 m downhole.</li> <li>True north azimuths supplied from the gyro were corrected to UTM grid north.</li> </ul>
<b>Data spacing and distribution</b>	<ul style="list-style-type: none"> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</li> <li>Whether sample compositing has been applied.</li> </ul>	<ul style="list-style-type: none"> <li>Variable drill hole spacings were used to adequately test targets and are determined from geochemical, geophysical and geological data with historical drilling information.</li> <li>Data spacing is sufficient to establish geological and grade continuity to a level appropriate for a future update of the current gold-only mineral resource estimate at NW Array with addition of antimony</li> <li>Reported intersections have been composited using a cut-off grade of 0.3 g/t Au.</li> </ul>
<b>Orientation of data in relation to geological structure</b>	<ul style="list-style-type: none"> <li>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</li> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	<ul style="list-style-type: none"> <li>Drill holes are oriented at various angles to mineralised structures, in part due to access restrictions for drill pad locations and also due to the interpreted difference in strike and dip of the main mineralised structures.</li> <li>Although individual holes may not be oriented optimally for sampling some structures, there is no overall sampling bias introduced.</li> </ul>

Criteria	Explanation	Commentary
<b>Sample security</b>	<ul style="list-style-type: none"> <li>The measures taken to ensure sample security.</li> </ul>	<ul style="list-style-type: none"> <li>Samples were collected by company personnel on site, to the company logging and cutting office and delivered direct to the preparation laboratory via company personnel. A transport contractor takes the prepared samples to Vancouver.</li> </ul>
<b>Audits or reviews</b>	<ul style="list-style-type: none"> <li>The results of any audits or reviews of sampling techniques and data.</li> </ul>	<ul style="list-style-type: none"> <li>No audits or reviews have been completed at this early stage of the drilling program.</li> </ul>

## Section 2: Reporting of Exploration Results

Criteria	Explanation	Commentary
<b>Mineral tenement and land tenure status</b>	<ul style="list-style-type: none"> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a license to operate in the area.</li> </ul>	<ul style="list-style-type: none"> <li>The Treasure Creek Project is located in the Fairbanks Gold Mining District in central Alaska.</li> <li>The Treasure Creek Project area consists of 238 active Alaska State Mining Claims (MCs) and 2 Upland Mining Leases (UMLs) for a total of 11687.31 hectares. There are also 4 pending MCs for a total of 64.75 hectares.</li> <li>The Treasure Creek Project is a consolidation of mining claims and upland mining leases held by Oro Grande Mining Claims LLC (10 MCs and 1 UML), Goldstone Resources LLC (19 MCs and 1 UML), Wally Trudeau (5 MCs), and Felix Gold Ltd (204 MCs).</li> <li>Felix has acquired the mining claims or the exclusive rights to explore and an option to purchase the mining claims.</li> <li>Felix has acquired all requisite operating permits to conduct the current exploration program.</li> </ul>

Criteria	Explanation	Commentary
<b>Exploration done by other parties</b>	<ul style="list-style-type: none"> <li><i>Acknowledgment and appraisal of exploration by other parties.</i></li> </ul>	<ul style="list-style-type: none"> <li>Gold was first discovered at Fairbanks in 1902, since then the wider area has been the subject of an enormous amount of exploration and placer mining by companies and individual prospectors.</li> <li>Since 1969, the Treasure Creek area has been explored by companies including Cantu Minerals, Mohawk Oil, Aalenian Resources/Silverado Mines, American Copper and Nickel Company (ACNC), Amax, Goldstone/Our Creek (OCMC), Canex Resources, Tri-Con Mining and BHP-Utah.</li> <li>Most of the work was focused on Au-Sb mines at and around Scrafford, and in the eastern third of Felix's current tenure. Several diamond holes were completed in the NW Array prospect area.</li> </ul>
<b>Geology</b>	<ul style="list-style-type: none"> <li><i>Deposit type, geological setting and style of mineralisation.</i></li> </ul>	<ul style="list-style-type: none"> <li>Hard-rock gold mineralisation styles in Felix's Treasure Creek prospect are currently dominated by shear- and fault-vein hosted gold ± antimony deposits, including historic mines at Scrafford (Sb). Broad zones of disseminated and stockwork gold mineralisation are also found within Cretaceous age intrusive rocks, such as at Fort Knox (operated by Kinross) and Golden Summit (Freegold Ventures).</li> <li>Gold mineralisation is linked to a causative intrusion of Cretaceous-Tertiary felsic to intermediated composition. Proximity to the intrusion, structural setting and host rock all control the specific style of deposit produced. Antimony mineralisation is also associated with these felsic sill-like bodies.</li> <li>Post-mineralisation cover in the Fairbanks area comprises valley-fill gravels plus locally thick accumulations of wind-blown silt (loess).</li> </ul>

Criteria	Explanation	Commentary
<p><b>Drill hole information</b></p>	<ul style="list-style-type: none"> <li>• <i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i></li> <li>• <i>easting and northing of the drill hole collar</i></li> <li>• <i>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i></li> <li>• <i>dip and azimuth of the hole</i></li> <li>• <i>down hole length and interception depth hole length.</i></li> <li>• <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Refer to the body of the text of the announcement for all drill hole information relating to this announcement.</li> <li>• Details of any other drill holes referred to can be found in previous announcements listed under “Previous Disclosure - JORC 2012 Code”.</li> <li>• No material information has been excluded.</li> </ul>
<p><b>Data aggregation methods</b></p>	<ul style="list-style-type: none"> <li>• <i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.</i></li> <li>• <i>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i></li> <li>• <i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Significant Gold intercepts are regarded as those having minimum continuous mineralisation of at least 3.0m @ &gt;0.3 g/t Au. Assays were aggregated by length-weighted averaging with no top-cutting applied.</li> <li>• Higher-grade inclusions within intersections used a cut-off of 1 g/t Au</li> <li>• A maximum of 3m total of internal waste with 3m consecutive waste intervals was allowed during economic compositing. No metal equivalents have been reported.</li> </ul>

Criteria	Explanation	Commentary
<p><b>Relationship between mineralisation widths and intercept lengths</b></p>	<ul style="list-style-type: none"> <li>• <i>These relationships are particularly important in the reporting of Exploration Results.</i></li> <li>• <i>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</i></li> <li>• <i>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known').</i></li> </ul>	<ul style="list-style-type: none"> <li>• All intercepts quoted are downhole widths.</li> <li>• The geometry of mineralisation with respect to the hole angle varies due to the wide range of drilling azimuths and variable strike and dip of mineralised zones. Modelling is ongoing to determine the true thickness of different gold mineralised zones.</li> <li>• Where core drilling has intersected structures with discernable orientations the estimated true widths are indicated in Table</li> <li>• Further drill results should verify the orientations of mineralisation as presented in this announcement.</li> </ul>
<p><b>Diagrams</b></p>	<ul style="list-style-type: none"> <li>• <i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Refer to figures in the body of the text.</li> </ul>
<p><b>Balanced reporting</b></p>	<ul style="list-style-type: none"> <li>• <i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Gold plus previously reported antimony and arsenic assays for all samples in the reported drill holes are included as an appendix to this announcement.</li> </ul>

Criteria	Explanation	Commentary
<b>Other substantive exploration data</b>	<ul style="list-style-type: none"> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</li> </ul>	<ul style="list-style-type: none"> <li>Trenching completed earlier this year and in 2024 confirmed the presence of east-striking and south-dipping zones of complex stibnite veining that vary in width and tenor over short strike lengths.</li> <li>A maiden Mineral Resource estimate was reported on 20th June 2024 for gold mineralisation at NW Array (FXG announcement 20 June 2024). Antimony was not included in the estimate due to lack of assay data</li> <li>Metallurgical testwork on bulk samples was completed earlier in 2025 on bulk samples from trenching (FXG Announcement 29 May 2025). Testwork achieved 85% Sb recovery, producing 69% Sb grade concentrates via gravity and flotation processes.</li> <li>Bulk density has been determined by the water immersion method on drill core samples, giving a density for porphyry of 2.59 g/cm<sup>3</sup> and schist of 2.7 g/cm<sup>3</sup>.</li> <li>Additional density measurements on drill core samples are being undertaken.</li> <li>Four water monitoring bore holes were drilled as part of the 2025 drilling program and data on groundwater levels has been collected over 2 quarters.</li> </ul>
<b>Further work</b>	<ul style="list-style-type: none"> <li>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	<ul style="list-style-type: none"> <li>The 2025 drill program at NW array is ongoing, mainly targeted at better definition of the known mineralised zones, in particular the high-grade “black breccia”</li> <li>The mineralised system remains open at depth and along strike to the north and south.</li> </ul>

## Appendix: Complete Assay Data

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25NWTR001	0	1	1	1.193	1264.7	0.015
25NWTR001	1	2	1	0.156	601.2	0.134
25NWTR001	2	3	1	0.791	1062.1	0.032
25NWTR001	3	4	1	0.25	536.1	0.025
25NWTR001	4	5	1	0.371	905.8	0.028
25NWTR001	5	6	1	2.19	2580.7	0.013
25NWTR001	6	7	1	0.384	1088.8	0.01
25NWTR001	7	8	1	0.656	1977.6	0.015
25NWTR001	8	9	1	2.661	2660.1	0.025
25NWTR001	9	10	1	0.184	738.5	0.044
25NWTR001	10	11	1	1.125	1459.4	0.019
25NWTR001	11	12	1	0.485	1461.5	0.021
25NWTR001	12	13	1	0.237	1047.7	0.016
25NWTR001	13	14	1	0.975	1892.2	0.152
25NWTR001	14	15	1	0.445	1474.9	0.36
25NWTR001	15	16	1	0.276	1005.6	0.02
25NWTR001	16	17	1	0.646	1916	0.015
25NWTR001	17	18	1	0.197	962.6	0.019
25NWTR001	18	19	1	0.275	826.6	0.013
25NWTR001	19	20	1	0.388	1287.6	0.021
25NWTR001	20	21	1	0.599	1683.5	0.022
25NWTR001	21	22	1	0.504	1204.5	0.035
25NWTR001	22	23	1	0.816	1777.8	0.131
25NWTR001	23	24	1	0.514	1616.7	0.165
25NWTR001	24	25	1	0.636	1456.5	0.04
25NWTR001	25	26	1	0.526	1657.8	0.44
25NWTR001	26	27	1	0.569	1654.8	0.5
25NWTR001	27	28	1	0.483	2265.2	0.146
25NWTR001	28	29	1	0.38	831.3	0.044
25NWTR001	29	30	1	0.239	1240.5	0.036
25NWTR001	30	31	1	1.232	2544.9	0.015
25NWTR001	31	32	1	0.968	1581	0.041
25NWTR001	32	33	1	0.207	875.8	0.046
25NWTR001	33	34	1	0.136	725.6	0.34
25NWTR001	34	35	1	0.334	694.9	0.042
25NWTR001	35	36	1	0.582	580.7	0.022

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25NWTR001	36	37	1	0.296	542.2	0.009
25NWTR001	37	38	1	0.102	421.4	0.022
25NWTR001	38	39	1	0.155	338.7	0.019
25NWTR001	39	40	1	0.193	546	0.03
25NWTR001	40	41	1	0.288	374.8	0.004
25NWTR001	41	42	1	0.189	222.7	0.007
25NWTR001	42	43	1	0.089	274.4	0.009
25NWTR001	43	44	1	0.051	445.5	0.017
25NWTR001	44	45	1	0.08	181.9	0.008
25NWTR001	45	46	1	0.094	314.4	0.008
25NWTR001	46	47	1	0.736	483.5	0.007
25NWTR001	47	48	1	0.284	874.4	0.008
25NWTR001	48	49	1	3.613	6361.7	0.043
25NWTR001	49	50	1	8.271	4474.8	0.042
25NWTR001	50	51	1	3.165	2557.7	0.021
25NWTR001	51	52	1	1.296	2029.7	0.035
25NWTR001	52	53	1	3.511	4670.8	0.48
25NWTR001	53	54	1	1.722	2874.4	0.211
25NWTR001	54	55	1	1.413	2628.1	0.163
25NWTR001	55	56	1	1.287	1366.3	0.031
25NWTR001	56	57	1	2.979	2585.4	0.13
25NWTR001	57	58	1	4.577	5029.8	0.071
25NWTR001	58	59	1	1.222	4546.2	0.046
25NWTR001	59	60	1	1.228	3057.3	0.094
25NWTR001	60	61	1	0.95	1491	0.025
25NWTR001	61	62	1	0.837	1339.3	0.016
25NWTR001	62	63	1	0.709	1478.6	0.021
25NWTR001	63	64	1	0.618	1396.5	0.024
25NWTR001	64	65	1	1.006	1585.1	0.016
25NWTR001	65	66	1	1.422	2123	0.024
25NWTR001	66	67	1	2.645	2326.5	0.01
25NWTR001	67	68	1	0.717	1040.4	0.008
25NWTR001	68	69	1	1.182	2446.6	0.014
25NWTR001	69	70	1	1.184	4221.2	0.023
25NWTR001	70	71	1	1.007	2915.3	0.013
25NWTR001	71	72	1	0.848	5771.2	0.025

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25NWTR001	72	73	1	0.179	2188.1	0.015
25NWTR001	73	74	1	0.143	1121.9	0.019
25NWTR001	74	75	1	0.156	1342.6	0.026
25NWTR001	75	76	1	0.452	1719.8	0.024
25NWTR001	76	77	1	0.75	2462.2	0.028
25NWTR001	77	78	1	1.848	3896.9	0.159
25NWTR001	78	79	1	1.252	6154.1	0.023
25NWTR001	79	80	1	1.047	10000	0.026
25NWTR001	80	81	1	3.305	1882.9	0.027
25NWTR001	81	82	1	0.462	2446	0.016
25NWTR001	82	83	1	0.274	1704.9	0.154
25NWTR001	83	84	1	0.053	332.1	0.029
25NWTR001	84	85	1	0.048	1080.3	0.044
25NWTR001	85	86	1	0.072	917.5	0.072
25NWTR001	86	87	1	0.05	703.3	0.034
25NWTR001	87	88	1	0.071	575.4	0.023
25NWTR001	88	89	1	0.081	861	0.036
25NWTR001	89	90	1	0.044	594.1	0.018
25NWTR002	0	1	1	0.66	972.6	4.9
25NWTR002	1	2	1	0.5	1793.2	0.159
25NWTR002	2	3	1	0.269	3262.1	0.257
25NWTR002	3	4	1	0.149	1705.9	0.107
25NWTR002	4	5	1	0.216	997.6	0.052
25NWTR002	5	6	1	0.169	1202.3	0.072
25NWTR002	6	7	1	0.04	888.5	0.099
25NWTR002	7	8	1	0.05	248.6	0.017
25NWTR002	8	9	1	0.061	450.1	0.043
25NWTR002	9	10	1	0.089	585.9	0.035
25NWTR002	10	11	1	0.142	682.9	0.034
25NWTR002	11	12	1	0.109	746.4	0.025
25NWTR002	12	13	1	0.188	485.1	0.013
25NWTR002	13	14	1	0.059	760	0.027
25NWTR002	14	15	1	0.107	1234.6	0.039
25NWTR002	15	16	1	0.115	769	0.039
25NWTR002	16	17	1	0.213	554.3	0.026
25NWTR002	17	18	1	0.205	646.3	0.029

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25NWTR002	18	19	1	0.06	549.1	0.016
25NWTR002	19	20	1	0.151	760.7	0.044
25NWTR002	20	21	1	0.656	685.8	0.029
25NWTR002	21	22	1	0.281	802.1	0.041
25NWTR002	22	23	1	0.132	270.3	0.009
25NWTR002	23	24	1	0.135	595.1	0.015
25NWTR002	24	25	1	0.206	574.3	0.013
25NWTR002	25	26	1	0.144	662.3	0.011
25NWTR002	26	27	1	0.15	429.5	0.012
25NWTR002	27	28	1	0.148	455.3	0.015
25NWTR002	28	29	1	0.035	175	0.007
25NWTR002	29	30	1	0.064	291.9	0.02
25NWTR002	30	31	1	0.13	616.4	0.021
25NWTR002	31	32	1	0.055	147.8	0.011
25NWTR002	32	33	1	0.058	248.8	0.012
25NWTR002	33	34	1	0.062	325.3	0.018
25NWTR002	34	35	1	0.036	130.2	0.006
25NWTR002	35	36	1	0.02	242.9	0.017
25NWTR002	36	37	1	0.092	580.8	0.035
25TCDC002	1.95	3.78	1.83	0.197	821.1	0.01
25TCDC002	3.78	4.94	1.16	0.43	1124	0.016
25TCDC002	4.94	6.22	1.28	0.377	996.6	0.011
25TCDC002	6.22	7.62	1.4	0.25	1666.3	0.014
25TCDC002	7.62	9.11	1.49	0.932	2603.3	0.011
25TCDC002	9.11	10.39	1.28	0.094	1327.3	0.021
25TCDC002	10.39	11.34	0.95	0.034	1600.9	0.025
25TCDC002	11.34	12.17	0.83	0.12	1502.2	0.02
25TCDC002	12.17	13.36	1.19	0.114	610.8	0.015
25TCDC002	13.36	14.85	1.49	0.37	850.3	0.008
25TCDC002	14.85	16.07	1.22	0.116	927	0.026
25TCDC002	16.07	17.38	1.31	0.115	486.2	0.028
25TCDC002	17.38	18.17	0.79	0.113	331.6	0.016
25TCDC002	18.17	19.3	1.13	0.108	347.4	0.036
25TCDC002	19.3	20.77	1.47	0.439	618.1	0.04
25TCDC002	20.77	21.77	1	1.641	211.7	0.006
25TCDC002	21.77	22.89	1.12	4.378	2195.3	0.248

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC002	22.89	23.84	0.95	0.286	840.4	0.022
25TCDC002	23.84	25.24	1.4	0.699	1532.5	0.031
25TCDC002	25.24	26.17	0.93	0.304	1113.9	0.1
25TCDC002	26.17	26.62	0.45	1.516	281.1	9.33
25TCDC002	26.62	27.13	0.51	1.517	411.9	6.61
25TCDC002	27.13	27.92	0.79	1.909	359.7	17.54
25TCDC002	27.92	28.65	0.73	1.835	306.9	0.54
25TCDC002	28.65	29.22	0.57	5.482	679.3	14.54
25TCDC002	29.22	30.42	1.2	4.978	2132.2	1.07
25TCDC002	30.42	31.79	1.37	0.287	765.9	0.055
25TCDC002	31.79	33.07	1.28	0.24	1118.8	0.031
25TCDC002	33.07	34.28	1.21	0.115	1958.1	0.03
25TCDC002	34.28	35.37	1.09	0.148	2762.1	0.031
25TCDC002	35.37	36.58	1.21	1.073	5180.8	0.018
25TCDC002	36.58	38.04	1.46	0.684	5266.6	0.015
25TCDC002	38.04	39.03	0.99	0.144	1534	0.013
25TCDC002	39.03	40.34	1.31	0.332	1322.4	0.035
25TCDC002	40.34	41.48	1.14	0.162	1011.9	0.014
25TCDC002	41.48	42.9	1.42	0.124	846.6	0.014
25TCDC002	42.9	44.05	1.15	0.073	616.4	0.011
25TCDC002	44.05	45.24	1.19	0.054	518	0.009
25TCDC002	45.24	46.48	1.24	0.301	913	0.016
25TCDC002	46.48	48.01	1.53	0.07	553.7	0.015
25TCDC002	48.01	49.04	1.03	2.269	2860.4	0.026
25TCDC002	49.04	50.38	1.34	0.357	1434.4	0.017
25TCDC002	50.38	51.47	1.09	0.206	1620	0.03
25TCDC002	51.47	52.47	1	0.0075	1456.2	0.026
25TCDC002	52.47	53.7	1.23	0.061	1355.8	0.041
25TCDC002	53.7	55.02	1.32	0.03	692.1	0.025
25TCDC002	55.02	56.48	1.46	0.145	1009.9	0.032
25TCDC002	56.48	57.45	0.97	0.016	696.9	0.032
25TCDC002	57.45	58.76	1.31	0.151	1833.7	0.128
25TCDC002	58.76	59.95	1.19	0.213	1301.8	0.056
25TCDC002	59.95	61.26	1.31	0.183	1430.3	0.044
25TCDC003	2	2.95	0.95	0.318	657.2	0.007
25TCDC003	2.95	5.12	2.17	0.394	556.6	0.006

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC003	5.12	6.68	1.56	0.471	1775.9	0.022
25TCDC003	6.68	7.47	0.79	0.193	416.5	0.015
25TCDC003	7.47	9.23	1.76	0.818	616	0.013
25TCDC003	9.23	11	1.77	0.487	1023.1	0.064
25TCDC003	11	12	1	0.519	180	0.012
25TCDC003	12	12.98	0.98	0.409	170.2	0.012
25TCDC003	12.98	13.9	0.92	0.137	342.8	0.029
25TCDC003	13.9	15.03	1.13	0.37	604.2	0.016
25TCDC003	15.03	16.42	1.39	3.594	2662.7	0.039
25TCDC003	16.42	17.86	1.44	1.538	1279.5	0.112
25TCDC003	17.86	18.9	1.04	2.379	469.1	3.01
25TCDC003	18.9	20.42	1.52	2.382	1433.7	2.97
25TCDC003	20.42	22.54	2.12	3.067	2404.5	1.28
25TCDC003	22.54	23.8	1.26	0.57	418.2	0.023
25TCDC003	23.8	24.99	1.19	0.7	1077.6	0.028
25TCDC003	24.99	26.23	1.24	1.037	712.4	0.073
25TCDC003	26.23	27.34	1.11	5.852	10000	0.093
25TCDC003	27.34	28.9	1.56	2.778	10000	0.057
25TCDC003	28.9	29.92	1.02	0.182	1865.4	0.064
25TCDC003	29.92	30.82	0.9	0.127	1438	0.094
25TCDC003	30.82	31.94	1.12	1.01	1358.7	0.126
25TCDC003	31.94	33.62	1.68	2.524	8095.1	0.144
25TCDC003	33.62	35.22	1.6	0.024	1326.5	0.065
25TCDC003	35.22	36.3	1.08	0.293	1563.8	0.04
25TCDC003	36.3	37.86	1.56	0.54	2853.9	0.021
25TCDC003	37.86	39.94	2.08	0.858	5239.6	0.071
25TCDC003	39.94	40.95	1.01	1.142	3611.2	0.159
25TCDC003	40.95	42.69	1.74	2.216	5989.6	0.078
25TCDC003	42.69	43.73	1.04	2.435	9164.1	0.29
25TCDC003	43.73	45.32	1.59	1.961	10000	0.26
25TCDC003	45.32	45.84	0.52	2.551	4785.8	0.82
25TCDC003	45.84	46.45	0.61	0.438	529.4	22.02
25TCDC003	46.53	47.47	0.94	3.126	1007.7	0.49
25TCDC003	47.47	48.46	0.99	5.403	1660.5	1.56
25TCDC003	48.46	49.12	0.66	11.47	10000	1.66
25TCDC003	49.12	50.23	1.11	1.376	657.5	0.69

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC003	50.23	51.51	1.28	0.199	978.8	0.122
25TCDC003	51.51	52.87	1.36	0.173	1185.6	0.074
25TCDC003	52.87	54.41	1.54	0.207	828.2	0.048
25TCDC003	54.41	55.5	1.09	0.202	691.2	0.036
25TCDC003	55.5	56.87	1.37	0.02	466.7	0.019
25TCDC003	56.87	58.06	1.19	0.044	227	0.006
25TCDC003	58.06	59.1	1.04	0.029	231.6	0.005
25TCDC003	59.1	60.02	0.92	0.169	277.6	0.004
25TCDC003	60.02	61.14	1.12	0.0075	79	0.002
25TCDC004	1.26	2.21	0.95	1.824	2155.8	0.1
25TCDC004	2.21	2.7	0.49	0.736	5869.8	0.76
25TCDC004	2.7	3.58	0.88	0.227	2670.5	0.272
25TCDC004	3.58	4.29	0.71	0.626	1228.1	7.68
25TCDC004	4.29	5.2	0.91	0.658	3469	0.67
25TCDC004	5.2	6.15	0.95	0.412	1817.9	0.162
25TCDC004	6.15	7.47	1.32	1.181	1515.1	0.058
25TCDC004	7.47	8.67	1.2	1.234	771.1	0.031
25TCDC004	8.67	9.94	1.27	0.731	778.4	0.029
25TCDC004	9.94	11.07	1.13	0.511	749.2	0.024
25TCDC004	11.07	12.8	1.73		2178.6	0.026
25TCDC004	12.8	14.14	1.34	1.571	4369.9	0.017
25TCDC004	14.14	15.43	1.29	2.042	5234.5	0.023
25TCDC004	15.43	16.76	1.33	0.446	2782.3	0.018
25TCDC004	16.76	18	1.24		1579.4	0.028
25TCDC004	18	19.18	1.18	0.898	2800.4	0.043
25TCDC004	19.18	19.98	0.8	0.867	802.8	0.067
25TCDC004	19.98	21.1	1.12	3.221	1672.1	0.229
25TCDC004	21.1	22.3	1.2	4.629	3228.1	1.16
25TCDC004	22.3	23.52	1.22	5.393	4333.7	1.11
25TCDC004	23.52	24.91	1.39	3.316	2267.5	0.206
25TCDC004	24.91	26.11	1.2	0.533	2100.9	0.03
25TCDC004	26.11	27.43	1.32	0.153	2468.4	0.02
25TCDC004	27.43	28.74	1.31	0.254	2641.8	0.018
25TCDC004	28.74	29.63	0.89	0.229	1613.4	0.014
25TCDC004	29.63	30.48	0.85	0.269	2466.2	0.017
25TCDC004	30.48	31.6	1.12	0.903	5210	0.01

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC004	31.6	32.63	1.03	0.523	2217.3	0.011
25TCDC004	32.63	33.95	1.32		5318.6	0.018
25TCDC004	33.95	35.4	1.45	0.18	2415.5	0.014
25TCDC004	35.4	36.5	1.1	0.08	3121	0.056
25TCDC004	36.5	37.61	1.11		1574.1	0.123
25TCDC004	37.61	38.56	0.95	2.972	5313.3	1.56
25TCDC004	38.56	39.43	0.87	2.476	6608.1	0.29
25TCDC004	39.43	40.4	0.97	1.719	884.7	3
25TCDC004	40.4	41.27	0.87	1.743	620.5	5.01
25TCDC004	41.27	42.09	0.82	5.047	2245.8	12.1
25TCDC004	42.09	43.14	1.05	5.366	1186.5	6.2
25TCDC004	43.14	43.87	0.73	5.334	1219.9	24.93
25TCDC004	43.87	44.62	0.75	4.653	2187.9	1.88
25TCDC004	44.62	45.46	0.84	2.508	958.5	6.27
25TCDC004	45.46	46.3	0.84	3.801	2573.7	22.39
25TCDC004	46.3	46.97	0.67	7.126	1517	9.49
25TCDC004	46.97	47.41	0.44	13.182	5068.9	1.38
25TCDC004	47.41	48.62	1.21	1.146	3141.9	0.082
25TCDC004	48.62	49.65	1.03	0.715	2092.4	0.58
25TCDC004	49.65	50.26	0.61	0.164	1935	0.58
25TCDC004	50.26	51.63	1.37	0.219	1259.5	0.088
25TCDC004	51.63	53.32	1.69	1.227	1052.6	1.28
25TCDC004	53.32	54.47	1.15	0.06	301.7	0.106
25TCDC004	54.47	55.48	1.01	0.409	619.3	0.078
25TCDC004	55.48	56.89	1.41	0.047	251.4	0.016
25TCDC004	56.89	57.9	1.01	0.085	187.5	0.016
25TCDC004	57.9	59.18	1.28	0.081	228.4	0.025
25TCDC004	59.18	60.8	1.62	0.098	166.3	0.036
25TCDC004	60.8	61.75	0.95	0.083	72.8	0.007
25TCDC004	61.75	62.83	1.08	0.07	231.3	0.012
25TCDC005	1.55	2.72	1.17	0.41	1307.9	0.067
25TCDC005	2.72	3.69	0.97	1.006	1941.1	0.07
25TCDC005	3.69	4.52	0.83	0.435	2363.8	1.09
25TCDC005	4.52	5.49	0.97	1.362	627.7	0.274
25TCDC005	5.49	6.15	0.66	3.036	292.2	5.66
25TCDC005	6.15	6.74	0.59	2.902	516.4	7.56

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC005	6.74	7.5	0.76	2.521	168.7	0.245
25TCDC005	7.5	8.02	0.52	1.551	118.6	1.16
25TCDC005	8.02	8.63	0.61	1.047	183.2	0.221
25TCDC005	8.63	9.2	0.57	1.497	204.9	0.147
25TCDC005	9.2	10.16	0.96	0.934	1087.1	0.088
25TCDC005	10.16	10.94	0.78	1.734	419.1	0.148
25TCDC005	10.94	11.97	1.03	0.755	82	0.058
25TCDC005	11.97	13.11	1.14	1.388	185.5	0.128
25TCDC005	13.11	14.14	1.03	0.422	113.8	0.015
25TCDC005	14.14	14.96	0.82	0.149	232.2	0.015
25TCDC005	14.96	16.2	1.24	0.122	188.9	0.013
25TCDC005	16.2	17.6	1.4	0.11	330.3	0.013
25TCDC005	17.6	18.76	1.16	0.033	565.8	0.011
25TCDC005	18.76	19.73	0.97	0.065	384.4	0.01
25TCDC005	19.73	20.73	1	0.104	836.2	0.017
25TCDC005	20.73	21.55	0.82	0.042	1189.2	0.05
25TCDC005	21.55	22.25	0.7	0.024	750.1	0.024
25TCDC005	22.25	23.1	0.85	0.08	807.5	0.03
25TCDC005	23.1	23.86	0.76	0.069	1319.9	0.022
25TCDC005	23.86	24.95	1.09	0.458	4242.2	0.085
25TCDC005	24.95	25.71	0.76	1.244	3043.2	0.065
25TCDC005	25.71	26.53	0.82	0.379	2541.7	0.034
25TCDC005	26.53	27.11	0.58	0.261	1782.2	0.019
25TCDC005	27.11	27.84	0.73	0.634	2034.9	0.02
25TCDC005	27.84	28.22	0.38	1.297	864.9	7.73
25TCDC005	28.22	28.77	0.55	1.106	2181	3.93
25TCDC005	28.77	30.02	1.25	0.736	2125.6	0.28
25TCDC005	30.02	30.72	0.7	0.418	1585.3	0.052
25TCDC005	30.72	31.53	0.81	0.446	1053.4	0.016
25TCDC005	31.53	32.06	0.53	0.644	718.4	2.32
25TCDC005	32.06	32.62	0.56	0.434	1330.3	0.015
25TCDC005	32.62	33.74	1.12	0.541	1528.7	0.021
25TCDC005	33.74	34.9	1.16	0.153	1033.2	0.017
25TCDC005	34.9	35.9	1	0.339	1363.3	0.016
25TCDC005	35.9	37	1.1	0.277	1898.4	0.021
25TCDC005	37	38.2	1.2	0.429	2210.8	0.025

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC005	38.2	38.96	0.76	0.317	1364.8	0.039
25TCDC005	38.96	39.84	0.88	0.78	1840.1	0.031
25TCDC005	39.84	40.9	1.06	0.319	2230.4	0.012
25TCDC005	40.9	41.5	0.6	0.217	1036.2	0.008
25TCDC005	41.5	41.98	0.48	0.378	1260.2	0.98
25TCDC005	41.98	42.95	0.97	0.137	715.7	0.018
25TCDC005	42.95	43.79	0.84	0.148	393.1	0.018
25TCDC005	43.79	44.87	1.08	0.155	786.8	0.018
25TCDC005	44.87	45.7	0.83	0.204	1338.6	0.013
25TCDC005	45.7	46.94	1.24	0.167	2595.7	0.016
25TCDC005	46.94	47.8	0.86	0.776	1209.5	0.021
25TCDC005	47.8	48.4	0.6	4.529	4586.8	0.026
25TCDC005	48.4	49.41	1.01	2.072	10000	0.071
25TCDC005	49.41	50.7	1.29	1.083	4991.6	0.037
25TCDC005	50.7	51.4	0.7	0.125	3771.6	0.05
25TCDC005	51.4	51.95	0.55	0.36	3433.7	0.051
25TCDC005	51.95	53.13	1.18	0.345	2731	0.017
25TCDC005	53.13	54.24	1.11	0.072	1097.6	0.011
25TCDC005	54.24	55.4	1.16	0.026	680.5	0.009
25TCDC005	55.4	56.24	0.84	0.028	885.9	0.008
25TCDC005	56.24	57.15	0.91	0.034	856.6	0.009
25TCDC005	57.15	57.73	0.58	0.419	1453.7	0.035
25TCDC005	57.73	58.6	0.87	0.0075	476.8	0.026
25TCDC005	58.6	59.6	1	0.071	1658.9	0.014
25TCDC005	59.6	60.75	1.15	0.022	1244.5	0.013
25TCDC005	60.75	62.14	1.39	0.039	1440.4	0.035
25TCDC005	62.14	63.62	1.48	0.033	1423.1	0.039
25TCDC005	63.62	64.5	0.88	0.017	913.4	0.03
25TCDC005	64.5	65.2	0.7	0.0075	1032.1	0.024
25TCDC005	65.2	65.95	0.75	0.461	1017.4	0.026
25TCDC005	65.95	67.24	1.29	0.017	667.8	0.017
25TCDC005	67.24	68.49	1.25	0.026	550.9	0.042
25TCDC006	0	1.35	1.35	0.18	729.7	0.084
25TCDC006	1.35	2.54	1.19	0.09	728.9	0.044
25TCDC006	2.54	3.5	0.96		742	0.07
25TCDC006	3.5	4.76	1.26		901.1	0.053

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC006	4.76	5.95	1.19	0.06	495	0.027
25TCDC006	5.95	7.08	1.13	0.095	895.4	0.072
25TCDC006	7.08	8.03	0.95	0.097	904.6	0.116
25TCDC006	8.03	9.08	1.05	0.046	1171.8	0.077
25TCDC006	9.08	11.09	2.01	1.101	2502.2	0.094
25TCDC006	11.09	11.59	0.5	0.566	1567.5	0.265
25TCDC006	11.59	12.11	0.52	1.459	209.3	5.14
25TCDC006	12.11	12.68	0.57	1.699	743.2	0.18
25TCDC006	12.68	13.42	0.74		816.6	0.045
25TCDC006	13.42	13.79	0.37	0.372	210.7	1.48
25TCDC006	13.79	14.51	0.72	0.468	148.7	1.44
25TCDC006	14.51	15.9	1.39	0.507	1092.9	0.037
25TCDC006	15.9	16.6	0.7		1384.9	0.047
25TCDC006	16.6	17.35	0.75	0.288	2273	0.052
25TCDC006	17.35	18.44	1.09	0.29	2802.4	0.018
25TCDC006	18.44	19.15	0.71	0.207	833.9	0.033
25TCDC006	19.15	19.85	0.7	0.301	942	0.026
25TCDC006	19.85	20.45	0.6	1.926	582.2	0.016
25TCDC006	20.45	21.61	1.16		2080.4	0.045
25TCDC006	21.61	22.62	1.01	0.186	1335	0.031
25TCDC006	22.62	23.6	0.98	0.097	695.5	0.034
25TCDC006	23.6	24.6	1	0.101	455.5	0.037
25TCDC006	24.6	25.67	1.07	0.062	430.5	0.039
25TCDC006	25.67	26.1	0.43	0.884	289.3	2.69
25TCDC006	26.1	26.58	0.48	0.132	381.7	0.021
25TCDC006	26.58	27.3	0.72	0.19	905.3	0.012
25TCDC006	27.3	27.8	0.5	0.176	982.4	0.013
25TCDC006	27.8	28.17	0.37	0.209	3364.7	0.019
25TCDC006	28.17	28.68	0.51	0.249	1536.8	0.017
25TCDC006	28.68	29.9	1.22	0.542	4397.6	0.01
25TCDC006	29.9	31.05	1.15	0.745	4437.7	0.009
25TCDC006	31.05	31.55	0.5	0.65	2122.1	0.02
25TCDC006	31.55	32.05	0.5	0.374	4793.1	0.051
25TCDC006	32.05	32.77	0.72	1.625	3366.7	0.13
25TCDC006	32.77	33.57	0.8	1.51	5865.5	0.09
25TCDC006	33.57	34.33	0.76	2.146	8318.9	0.13

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC006	34.33	35.3	0.97	2.568	10000	0.18
25TCDC006	35.3	35.74	0.44	1.863	5059.4	0.18
25TCDC006	35.74	36.27	0.53	1.813	5316.9	1.25
25TCDC006	36.27	36.83	0.56	2.102	1908.6	5.65
25TCDC006	36.83	37.39	0.56	4.399	7071.8	0.49
25TCDC006	37.39	37.8	0.41	4.293	6193.9	3.5
25TCDC006	37.8	38.37	0.57	9.288	8006.9	5.66
25TCDC006	38.37	38.95	0.58	7.53	10000	0.45
25TCDC006	38.95	39.41	0.46	2.773	10000	0.22
25TCDC006	39.41	39.92	0.51	1.125	3073.9	0.05
25TCDC006	39.92	41.05	1.13	0.279	1438.5	0.045
25TCDC006	41.05	42.12	1.07	0.164	498.6	0.034
25TCDC006	42.12	42.6	0.48	0.076	535.7	0.033
25TCDC006	42.6	43.83	1.23	0.241	875	0.045
25TCDC006	43.83	44.43	0.6	0.211	1478.7	0.058
25TCDC006	44.43	45.41	0.98	0.174	783.6	0.021
25TCDC006	45.41	46.45	1.04	0.576	556	0.018
25TCDC006	46.45	47.18	0.73	0.078	282.1	0.011
25TCDC006	47.18	48.39	1.21	0.076	262.2	0.005
25TCDC006	48.39	49.32	0.93	0.17	565.3	0.011
25TCDC006	49.32	50.47	1.15	0.155	323.8	0.006
25TCDC006	50.47	51.51	1.04	0.201	395.2	0.004
25TCDC006	51.51	52.4	0.89	0.218	480.7	0.007
25TCDC006	52.4	53.03	0.63	0.383	467.6	0.009
25TCDC006	53.03	54.03	1	0.155	489.7	0.011
25TCDC006	54.03	54.99	0.96	0.222	269.2	0.003
25TCDC006	54.99	56.34	1.35	0.229	393.6	0.008
25TCDC006	56.34	56.69	0.35	0.146	723.4	0.008
25TCDC006	56.69	57.39	0.7	0.551	451.7	0.006
25TCDC006	57.39	57.9	0.51	0.077	194.4	0.007
25TCDC006	57.9	58.77	0.87	0.158	221.5	0.004
25TCDC006	58.77	59.69	0.92	0.17	375.1	0.003
25TCDC006	59.69	60.57	0.88	0.074	106.1	0.01
25TCDC006	60.57	61.39	0.82	0.249	885.5	0.007
25TCDC011	0	1.32	1.32	0.742	1179.4	0.04
25TCDC011	1.32	1.93	0.61	0.539	1227.8	0.061

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC011	1.93	2.43	0.5	0.537	1322.5	0.06
25TCDC011	2.43	3.41	0.98	0.723	1489.5	0.049
25TCDC011	3.41	3.9	0.49	1.611	2822.3	0.42
25TCDC011	3.9	4.38	0.48	0.654	858	3.15
25TCDC011	4.38	4.8	0.42	1.206	2041.9	0.4
25TCDC011	4.8	5.52	0.72	1.041	2992.9	0.24
25TCDC011	5.52	6.4	0.88	2.267	2027.1	1.79
25TCDC011	6.4	7.3	0.9	0.984	1832.2	0.148
25TCDC011	7.3	8.32	1.02	1.269	865.8	0.095
25TCDC011	8.32	9.43	1.11	0.212	2044.8	0.041
25TCDC011	9.43	10.6	1.17	0.907	1712.1	0.042
25TCDC011	10.6	11.88	1.28	0.057	780.6	0.016
25TCDC011	11.88	13.19	1.31	0.0075	351.9	0.009
25TCDC011	13.19	14.82	1.63	0.264	2403.7	0.053
25TCDC011	14.82	15.7	0.88	0.514	1208.2	0.042
25TCDC011	15.7	16.7	1	1.457	2197.9	0.054
25TCDC011	16.7	17.67	0.97	0.119	9969.1	0.034
25TCDC011	17.67	18.47	0.8	1.026	4504.7	0.034
25TCDC011	18.47	19.72	1.25	0.398	1411.5	0.035
25TCDC011	19.72	20.18	0.46			
25TCDC011	20.18	20.94	0.76	0.581	1204.2	0.022
25TCDC011	20.94	22.1	1.16	0.588	3181.3	0.054
25TCDC011	22.1	23.35	1.25	0.465	3949	0.044
25TCDC011	23.35	24.92	1.57	1.236	4606.6	0.045
25TCDC011	24.92	25.97	1.05	1.135	721.8	0.194
25TCDC011	25.97	26.73	0.76	0.655	899.5	0.64
25TCDC011	26.73	28.1	1.37	0.669	1434.2	0.057
25TCDC011	28.1	29.14	1.04	0.263	703.3	0.022
25TCDC011	29.14	30.43	1.29	0.309	1050.7	0.017
25TCDC011	30.43	31.42	0.99	0.835	1267	0.019
25TCDC011	31.42	32.7	1.28	1.144	2017.9	0.014
25TCDC011	32.7	33.95	1.25	0.654	1108.5	0.023
25TCDC011	33.95	35.4	1.45	1.307	1121.5	0.042
25TCDC011	35.4	36.04	0.64	0.789	983	0.77
25TCDC011	36.04	36.77	0.73	4.709	3694	0.115
25TCDC011	36.77	38.02	1.25	0.846	4337.5	0.113

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC011	38.02	38.61	0.59	0.294	6392.2	0.034
25TCDC011	38.61	39.2	0.59	0.682	5899.9	0.016
25TCDC011	39.2	39.96	0.76	2.671	10000	0.022
25TCDC011	39.96	41.03	1.07	0.812	2178.5	0.01
25TCDC011	41.03	42.36	1.33	1.078	2847.3	0.009
25TCDC011	42.36	43.11	0.75	0.99	2858.9	0.004
25TCDC011	43.11	43.43	0.32	3.278	10000	0.006
25TCDC011	43.43	44.4	0.97	3.916	10000	0.013
25TCDC011	44.4	45.5	1.1	0.28	2089.3	0.007
25TCDC011	45.5	46.85	1.35	0.106	1685.8	0.013
25TCDC011	46.85	48.03	1.18	0.106	1575.6	0.059
25TCDC011	48.03	49.22	1.19	0.079	1872.3	0.029
25TCDC011	49.22	50.5	1.28	0.031	1476.9	0.017
25TCDC011	50.5	51.2	0.7	0.053	1127	0.022
25TCDC011	51.2	52.8	1.6	0.086	617.1	0.017
25TCDC011	52.8	53.84	1.04	0.038	1877.1	0.073
25TCDC011	53.84	54.3	0.46	0.542	1801.4	0.24
25TCDC011	54.3	55.67	1.37	1.571	3056.2	0.127
25TCDC011	55.67	56.2	0.53	3.596	6105	0.112
25TCDC011	56.2	56.93	0.73	0.675	1924.3	0.147
25TCDC011	56.93	58.4	1.47	1.735	5657.9	0.31
25TCDC011	58.4	59.53	1.13	0.311	1483.9	0.104
25TCDC011	59.53	60.4	0.87	0.808	1642.6	0.039
25TCDC011	60.4	61.4	1	1.205	5359.1	0.046
25TCDC011	61.4	62.1	0.7	0.679	832.7	0.138
25TCDC011	62.1	63.2	1.1	0.241	198.6	0.077
25TCDC011	63.2	63.6	0.4	0.873	321.9	0.106
25TCDC011	63.6	64.3	0.7	0.623	1437.8	0.069
25TCDC011	64.3	64.76	0.46	0.466	1087.5	0.046
25TCDC011	64.76	66.03	1.27	0.343	1520	0.043
25TCDC011	66.03	66.8	0.77	0.077	499.6	0.064
25TCDC011	66.8	67.7	0.9	0.153	881.8	0.053
25TCDC012	0	1.89	1.89	0.662	1363.2	0.131
25TCDC012	1.89	2.74	0.85	0.306	1037.9	0.043
25TCDC012	2.74	3.5	0.76	0.032	881	0.037
25TCDC012	3.5	4.5	1	0.668	828.7	0.025

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC012	4.5	5.3	0.8	1.086	900.6	0.036
25TCDC012	5.3	5.83	0.53	1.128	805.2	0.044
25TCDC012	5.83	6.83	1	0.233	1102.4	0.034
25TCDC012	6.83	8.6	1.77	0.276	2534.6	0.036
25TCDC012	8.6	9.69	1.09	0.814	2377.6	0.027
25TCDC012	9.69	10.49	0.8	0.022	1684.9	0.019
25TCDC012	10.49	11.19	0.7	0.174	3290.2	0.016
25TCDC012	11.19	11.89	0.7	0.297	681.8	0.022
25TCDC012	11.89	12.9	1.01	0.135	145.4	0.025
25TCDC012	12.9	13.73	0.83	0.373	472.2	0.048
25TCDC012	13.73	14.8	1.07	1.449	732.6	0.046
25TCDC012	14.8	15.65	0.85	0.505	1001.4	0.06
25TCDC012	15.65	16.46	0.81	0.463	1017.5	0.042
25TCDC012	16.46	17.08	0.62	0.509	960	0.044
25TCDC012	17.08	17.98	0.9	0.313	1574.3	0.037
25TCDC012	17.98	18.63	0.65	0.085	311.8	0.012
25TCDC012	18.63	19.8	1.17	0.06	131.3	0.009
25TCDC012	19.8	20.83	1.03	0.062	279.8	0.02
25TCDC012	20.83	22.13	1.3	0.163	434.6	0.008
25TCDC012	22.13	23.59	1.46	0.209	329.6	0.052
25TCDC012	23.59	25.82	2.23	0.318	1315.2	0.008
25TCDC012	25.82	26.65	0.83	0.164	553.7	0.009
25TCDC012	26.65	27.79	1.14	0.697	905.9	0.007
25TCDC012	27.79	28.93	1.14	0.049	174.8	0.009
25TCDC012	28.93	29.75	0.82	0.069	238.5	0.02
25TCDC012	29.75	30.72	0.97	0.632	623.2	0.016
25TCDC012	30.72	31.6	0.88	0.338	731.3	0.01
25TCDC012	31.6	32.5	0.9	0.192	308.4	0.008
25TCDC012	32.5	33.77	1.27	0.671	497.8	0.009
25TCDC012	33.77	34.17	0.4	0.198	316.7	0.007
25TCDC012	34.17	35.54	1.37	0.238	757.1	0.031
25TCDC012	35.54	36.4	0.86	0.043	751.7	0.007
25TCDC012	36.4	37.02	0.62	2.941	3356.9	0.028
25TCDC012	37.02	37.4	0.38	1.209	538.5	2.92
25TCDC012	37.4	37.8	0.4	1.291	1565.5	0.189
25TCDC012	37.8	38.22	0.42	1.51	2903.7	0.027

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC012	38.22	39.26	1.04	1.454	2735	0.034
25TCDC012	39.26	40.07	0.81	1.836	3933	0.085
25TCDC012	40.07	40.44	0.37	5.822	6918.1	1.16
25TCDC012	40.44	40.84	0.4	2.573	10000	13.85
25TCDC012	40.84	41.51	0.67	1.601	4856.9	0.084
25TCDC012	41.51	42.3	0.79	0.544	1990.4	0.09
25TCDC012	42.3	43.65	1.35	0.247	1685	0.097
25TCDC012	43.65	44.35	0.7	0.26	898.5	0.08
25TCDC012	44.35	45.5	1.15	0.391	555.5	0.036
25TCDC012	45.5	46.63	1.13	0.266	233.9	0.026
25TCDC012	46.63	47.67	1.04	0.172	952.5	0.053
25TCDC012	47.67	48.66	0.99	1.133	1034.8	0.043
25TCDC012	48.66	49.8	1.14	1.573	1913.4	0.034
25TCDC012	49.8	50.69	0.89	0.708	1642.7	0.044
25TCDC012	50.69	51.69	1	0.413	873.4	0.023
25TCDC012	51.69	52.85	1.16	0.123	225	0.009
25TCDC012	52.85	53.63	0.78	0.199	645.4	0.011
25TCDC012	53.63	54.84	1.21	0.101	409.4	0.019
25TCDC012	54.84	56.12	1.28	0.066	301.6	0.009
25TCDC012	56.12	58.08	1.96	0.128	226.8	0.018
25TCDC012	58.08	58.93	0.85	0.114	175.2	0.011
25TCDC012	58.93	59.7	0.77	0.076	95.6	0.009
25TCDC012	59.7	60.56	0.86	0.09	217.6	0.011
25TCDC013	0	1.37	1.37	0.669	1119.5	0.83
25TCDC013	1.37	2.27	0.9	0.813	838.4	0.096
25TCDC013	2.27	3.28	1.01	0.95	750.9	0.107
25TCDC013	3.28	4.51	1.23	1.82	524.4	0.049
25TCDC013	4.51	5.15	0.64	1.825	1470.5	0.125
25TCDC013	5.15	6.29	1.14	0.645	967.7	0.115
25TCDC013	6.29	7	0.71	1.44	1150.6	0.025
25TCDC013	7	8.79	1.79	0.969	3616	0.028
25TCDC013	8.79	10	1.21	0.404	3792.1	0.017
25TCDC013	10	10.58	0.58	0.044	1798.6	0.012
25TCDC013	10.58	11.65	1.07	0.18	1887.6	0.015
25TCDC013	11.65	12.37	0.72	0.45	554.8	0.017
25TCDC013	12.37	13.16	0.79	0.139	469.7	0.091

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC013	13.16	13.75	0.59	0.04	355	0.059
25TCDC013	13.75	14.88	1.13	0.256	951.6	0.085
25TCDC013	14.88	15.57	0.69	0.268	920.2	0.011
25TCDC013	15.57	16.32	0.75	0.259	723.1	0.007
25TCDC013	16.32	17.65	1.33	1.584	6381.2	0.062
25TCDC013	17.65	18.5	0.85	1.56	1641.9	0.034
25TCDC013	18.5	19.83	1.33	0.151	437.6	0.006
25TCDC013	19.83	21.63	1.8	0.063	102.4	0.003
25TCDC013	21.63	22.41	0.78	0.0075	31.7	0.004
25TCDC013	22.41	23.07	0.66	0.02	51.4	0.004
25TCDC013	23.07	24.1	1.03	0.781	752.4	0.007
25TCDC013	24.1	24.59	0.49	1.72	1889.7	0.045
25TCDC013	24.59	25.42	0.83	4.324	10000	0.028
25TCDC013	25.42	26.32	0.9	1.65	10000	0.022
25TCDC013	26.32	26.85	0.53	0.745	1630.5	0.047
25TCDC013	26.85	27.42	0.57	5.485	2489.7	2.5
25TCDC013	27.42	27.9	0.48	1.069	305.9	2.93
25TCDC013	27.9	28.37	0.47	2.839	842.2	0.78
25TCDC013	28.37	29.3	0.93	0.055	168	0.065
25TCDC013	29.3	30.1	0.8	12.942	996.4	0.037
25TCDC013	30.1	30.63	0.53	0.996	963.1	0.029
25TCDC013	30.63	31.39	0.76	0.201	1048.6	0.015
25TCDC013	31.39	32.01	0.62	0.221	1013.9	0.015
25TCDC013	32.01	32.85	0.84	7.935	7338.4	0.21
25TCDC013	32.85	33.46	0.61	0.57	897.4	0.071
25TCDC013	33.46	34.53	1.07	1.577	3548	0.087
25TCDC013	34.53	35.42	0.89	3.985	4642.3	0.185
25TCDC013	35.42	36.91	1.49	0.84	1221.9	0.028
25TCDC013	36.91	37.95	1.04	0.028	224.8	0.122
25TCDC013	37.95	39.05	1.1	0.247	402.9	0.157
25TCDC013	39.05	40.02	0.97	0.0075	159.5	0.005
25TCDC013	40.02	41.09	1.07	0.0075	104.3	0.005
25TCDC013	41.09	41.6	0.51	0.035	297.7	0.011
25TCDC013	41.6	42.6	1	0.279	740.1	0.019
25TCDC013	42.6	43.47	0.87	0.114	579.6	0.005
25TCDC013	43.47	44.85	1.38	0.188	162.4	0.005

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC013	44.85	45.65	0.8	1.76	936.8	0.008
25TCDC013	45.65	46.66	1.01	19.377	10000	0.023
25TCDC013	46.66	47.05	0.39	0.248	1168.4	0.015
25TCDC013	47.05	48.22	1.17	0.037	230.4	0.003
25TCDC013	48.22	49.32	1.1	0.033	319	0.009
25TCDC013	49.32	49.9	0.58	0.021	322.3	0.005
25TCDC013	49.9	50.53	0.63	0.031	186.9	0.004
25TCDC013	50.53	51.28	0.75	0.0075	107.8	0.002
25TCDC013	51.28	52.1	0.82	0.078	220.8	0.003
25TCDC013	52.1	53.31	1.21	0.207	402.6	0.005
25TCDC013	53.31	54.75	1.44	0.128	294.9	0.004
25TCDC013	54.75	55.89	1.14	0.0075	62.4	0.006
25TCDC013	55.89	56.7	0.81	0.042	74.9	0.006
25TCDC013	56.7	57.49	0.79	0.0075	17.4	0.008
25TCDC013	57.49	58.64	1.15	0.039	33	0.003
25TCDC013	58.64	59.11	0.47	0.02	119	0.003
25TCDC013	59.11	60.23	1.12	0.453	505.5	0.003
25TCDC013	60.23	61.12	0.89	0.297	504	0.005
25TCDC013	61.12	61.82	0.7	0.054	203.7	0.006
25TCDC013	61.82	62.85	1.03	0.257	764.5	0.004
25TCDC013	62.85	63.9	1.05	0.111	276.5	0.002
25TCDC013	63.9	65.03	1.13	0.063	118.2	0.003
25TCDC013	65.03	65.53	0.5	0.0075	28.8	0.004
25TCDC016	0	1.28	1.28	0.135	675.4	0.036
25TCDC016	1.28	3.19	1.91	0.069	493.3	0.021
25TCDC016	3.19	4.24	1.05	0.032	306.1	0.023
25TCDC016	4.24	5.45	1.21	0.023	211.4	0.016
25TCDC016	5.45	6.3	0.85	0.102	307.5	0.032
25TCDC016	6.3	7.23	0.93	0.088	358.3	0.033
25TCDC016	7.23	7.99	0.76	0.161	965.4	0.051
25TCDC016	7.99	8.5	0.51	0.137	452	0.024
25TCDC016	8.5	8.92	0.42	0.146	570.4	0.022
25TCDC016	8.92	10.12	1.2	0.11	695.8	0.068
25TCDC016	10.12	11.1	0.98	0.153	534	0.018
25TCDC016	11.1	11.78	0.68	0.031	123.3	0.012
25TCDC016	11.78	12.3	0.52	0.0075	149.6	0.005

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC016	12.3	13.37	1.07	0.07	345.7	0.026
25TCDC016	13.37	14.6	1.23	0.102	511.3	0.01
25TCDC016	14.6	15.45	0.85	0.053	804	0.028
25TCDC016	15.45	16.15	0.7	0.068	629.6	0.029
25TCDC016	16.15	16.6	0.45	0.127	2126	0.18
25TCDC016	16.6	17.74	1.14	0.169	745.4	0.045
25TCDC016	17.74	18.82	1.08	0.48	514.5	1.39
25TCDC016	18.82	19.75	0.93	0.126	1717.7	0.97
25TCDC016	19.75	20.85	1.1	0.089	457.4	0.043
25TCDC016	20.85	21.75	0.9	0.199	1452.4	0.194
25TCDC016	21.75	22.72	0.97	0.377	1573.4	0.78
25TCDC016	22.72	23.62	0.9	0.113	550.9	0.022
25TCDC016	23.62	23.98	0.36	1.152	1912.4	1.13
25TCDC016	23.98	24.42	0.44	0.462	582.3	0.98
25TCDC016	24.42	25.6	1.18	0.31	1090.1	0.51
25TCDC016	25.6	26.65	1.05	0.093	340.3	0.021
25TCDC016	26.65	27.58	0.93	0.257	841.5	0.022
25TCDC016	27.58	28.65	1.07	0.164	468.8	0.019
25TCDC016	28.65	29.35	0.7	0.17	879.5	0.031
25TCDC016	29.35	30.23	0.88	0.216	980.7	0.031
25TCDC016	30.23	31.45	1.22	0.314	1079.1	0.013
25TCDC016	31.45	32.37	0.92	0.366	1262.8	0.016
25TCDC016	32.37	33.41	1.04	0.237	1079.1	0.021
25TCDC016	33.41	34.35	0.94	0.172	1172.4	0.017
25TCDC016	34.35	34.96	0.61	0.168	2053.6	0.062
25TCDC016	34.96	36.07	1.11	0.25	2363.3	0.056
25TCDC016	36.07	37.22	1.15	0.112	1126.8	0.026
25TCDC016	37.22	38.51	1.29	0.212	1147.2	0.034
25TCDC016	38.51	39.75	1.24	0.52	534.5	0.012
25TCDC016	39.75	41.09	1.34	0.411	486.4	0.019
25TCDC016	41.09	42	0.91	0.294	311.4	0.017
25TCDC016	42	43.2	1.2	0.352	383.2	0.021
25TCDC016	43.2	44.01	0.81	0.152	96.2	0.017
25TCDC016	44.01	44.41	0.4	0.632	217.7	0.029
25TCDC016	44.41	44.7	0.29	0.967	169.1	0.113
25TCDC016	44.7	45.42	0.72	2.172	402.4	0.103

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC016	45.42	45.85	0.43	2.545	1157.3	0.105
25TCDC016	45.85	46.3	0.45	1.543	246.2	0.097
25TCDC016	46.3	47.38	1.08	0.083	332.3	0.056
25TCDC016	47.38	48.4	1.02	0.062	421.9	0.05
25TCDC016	48.4	49.48	1.08	0.027	515.1	0.061
25TCDC016	49.48	50.57	1.09	0.045	660.2	0.075
25TCDC016	50.57	51.59	1.02	0.332	1145.9	0.051
25TCDC016	51.59	52.78	1.19	0.125	608.3	0.071
25TCDC016	52.78	53.98	1.2	0.123	616.8	0.067
25TCDC016	53.98	54.43	0.45	0.236	1196	0.023
25TCDC016	54.43	55.53	1.1	0.021	209.9	0.01
25TCDC016	55.53	56.94	1.41	0.03	390.7	0.01
25TCDC016	56.94	58.1	1.16	0.0075	515.4	0.008
25TCDC016	58.1	59.35	1.25	0.0075	337.1	0.004
25TCDC016	59.35	60.8	1.45	0.05	301.3	0.004
25TCDC016	60.8	61.92	1.12	0.032	744.5	0.008
25TCDC016	61.92	62.6	0.68	0.044	461	0.003
25TCDC016	62.6	63.76	1.16	0.046	663.8	0.004
25TCDC016	63.76	65.03	1.27	0.016	440.4	0.005
25TCDC016	65.03	66.17	1.14	0.015	642.8	0.005
25TCDC016	66.17	67	0.83	0.062	565.9	0.006
25TCDC016	67	67.93	0.93	0.026	1304.1	0.011
25TCDC016	67.93	68.98	1.05	0.0075	607.2	0.005
25TCDC017	0	1.21	1.21	0.689	508.1	1.49
25TCDC017	1.21	2.56	1.35	0.118	465.8	0.03
25TCDC017	2.56	3.66	1.1	0.057	295.2	0.023
25TCDC017	3.66	4.27	0.61	0.13	309.8	0.02
25TCDC017	4.27	5.36	1.09	0.079	200.1	0.02
25TCDC017	5.36	6.3	0.94	0.066	306.2	0.019
25TCDC017	6.3	7.16	0.86	0.147	643.2	0.05
25TCDC017	7.16	7.75	0.59	0.017	76.1	0.009
25TCDC017	7.75	9.1	1.35	0.074	105.7	0.01
25TCDC017	9.1	10.1	1	0.0075	224.8	0.016
25TCDC017	10.1	11.09	0.99	0.075	389.5	0.016
25TCDC017	11.09	11.86	0.77	0.112	570.1	0.024
25TCDC017	11.86	13.06	1.2	0.092	179.4	0.009

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC017	13.06	13.54	0.48	0.0075	273.9	0.008
25TCDC017	13.54	14.78	1.24	0.028	264.5	0.016
25TCDC017	14.78	15.95	1.17	0.039	508.5	0.034
25TCDC017	15.95	16.97	1.02	0.034	282.3	0.023
25TCDC017	16.97	17.92	0.95	0.053	233.3	0.025
25TCDC017	17.92	19.65	1.73	0.051	253.1	0.018
25TCDC017	19.65	20.84	1.19	0.048	329.5	0.019
25TCDC017	20.84	22.08	1.24	1.023	905.4	1.76
25TCDC017	22.08	23.58	1.5	0.106	483.1	0.052
25TCDC017	23.58	24.82	1.24	0.121	681.1	0.037
25TCDC017	24.82	26.24	1.42	0.179	665.2	0.04
25TCDC017	26.24	27.53	1.29	0.105	674.4	0.021
25TCDC017	27.53	28.14	0.61	0.294	1283.2	0.062
25TCDC017	28.14	28.59	0.45	0.199	859.2	0.037
25TCDC017	28.59	29.81	1.22	0.686	1125.5	0.035
25TCDC017	29.81	30.92	1.11	0.21	583.8	0.014
25TCDC017	30.92	32.21	1.29	0.074	144.7	0.008
25TCDC017	32.21	33.4	1.19	1.041	496.6	0.021
25TCDC017	33.4	34.75	1.35	0.0075	173.4	0.012
25TCDC017	34.75	35.87	1.12	0.042	174	0.023
25TCDC017	35.87	37.2	1.33	0.057	48.7	0.015
25TCDC017	37.2	38.24	1.04	0.113	442	0.016
25TCDC017	38.24	38.75	0.51	0.07	187.8	0.023
25TCDC017	38.75	39.93	1.18	0.05	41.6	0.01
25TCDC017	39.93	40.84	0.91	0.024	44.6	0.007
25TCDC017	40.84	42.05	1.21	0.0075	42.9	0.014
25TCDC017	42.05	42.97	0.92	0.0075	22.6	0.011
25TCDC017	42.97	44.13	1.16	0.057	276	0.022
25TCDC017	44.13	45.01	0.88	0.099	991.3	0.055
25TCDC017	45.01	45.62	0.61	0.132	274.3	0.012
25TCDC017	45.62	46.25	0.63	0.164	647	0.024
25TCDC017	46.25	46.94	0.69	0.507	2792.5	0.132
25TCDC017	46.94	47.6	0.66	1.043	4433.2	3.83
25TCDC017	47.6	48.74	1.14	0.216	1931.6	0.041
25TCDC017	48.74	49.99	1.25	0.598	1485.8	0.1
25TCDC017	49.99	50.98	0.99	0.632	1078.3	0.025

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC017	50.98	52.07	1.09	0.151	384.3	0.013
25TCDC017	52.07	53.04	0.97	0.12	829.7	0.041
25TCDC017	53.04	54.1	1.06	0.086	278.2	0.013
25TCDC017	54.1	55.21	1.11	0.052	516	0.017
25TCDC017	55.21	56.08	0.87	0.206	781	0.023
25TCDC017	56.08	57.44	1.36	0.096	413.9	0.025
25TCDC017	57.44	58.69	1.25	0.198	1000.8	0.043
25TCDC017	58.69	59.85	1.16	0.369	1032.2	0.013
25TCDC017	59.85	61	1.15	0.979	562.3	0.22
25TCDC017	61	61.8	0.8	0.13	1161.2	0.051
25TCDC017	61.8	62.4	0.6	0.205	1166.5	0.043
25TCDC017	62.4	62.8	0.4	1.554	1206.5	0.106
25TCDC017	62.8	63.1	0.3	2.985	312.7	1.17
25TCDC017	63.1	63.84	0.74	0.91	1348.8	0.18
25TCDC017	63.84	64.4	0.56	0.608	1440.6	0.161
25TCDC017	64.4	65.04	0.64	0.125	973.1	0.054
25TCDC017	65.04	65.72	0.68	2.007	261.3	1.84
25TCDC017	65.72	66.06	0.34	1.857	208.4	0.078
25TCDC017	66.06	66.38	0.32	3.701	367.3	4.68
25TCDC017	66.38	66.8	0.42	3.337	1314.7	0.63
25TCDC017	66.8	67.42	0.62	0.573	1525.8	0.056
25TCDC017	67.42	68.28	0.86	0.234	1059.8	0.057
25TCDC017	68.28	68.92	0.64	1.386	1649.1	0.018
25TCDC017	68.92	69.8	0.88	0.431	2151.4	0.03
25TCDC017	69.8	71.02	1.22	6.805	10000	0.018
25TCDC017	71.02	71.8	0.78	7.86	9247.5	0.031
25TCDC017	71.8	72.62	0.82	0.721	1640.3	0.026
25TCDC017	72.62	73.5	0.88	0.327	1674.9	0.031
25TCDC017	73.5	74.22	0.72	1.227	1629.2	0.023
25TCDC018	0	0.69	0.69	0.444		
25TCDC018	0.69	1.88	1.19	0.459		
25TCDC018	1.88	3.23	1.35	0.49		
25TCDC018	3.23	3.84	0.61	0.302		
25TCDC018	3.84	4.9	1.06	0.356		
25TCDC018	4.9	6.12	1.22	0.53		
25TCDC018	6.12	7.44	1.32	0.782		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC018	7.44	8.72	1.28	0.296		
25TCDC018	8.72	10	1.28	0.238		
25TCDC018	10	10.72	0.72	0.397		
25TCDC018	10.72	11.3	0.58	0.198		
25TCDC018	11.3	11.94	0.64	0.194		
25TCDC018	11.94	12.6	0.66	0.803		
25TCDC018	12.6	13.26	0.66	0.768		
25TCDC018	13.26	14.66	1.4	0.526		
25TCDC018	14.66	15.89	1.23	0.109		
25TCDC018	15.89	17.27	1.38	0.146		
25TCDC018	17.27	18.43	1.16	0.313		
25TCDC018	18.43	19.89	1.46	1.409		
25TCDC018	19.89	21.59	1.7	0.416		
25TCDC018	21.59	22.77	1.18	0.784		
25TCDC018	22.77	24.23	1.46	0.679		
25TCDC018	24.23	25.44	1.21	0.457		
25TCDC018	25.44	26.88	1.44	1.113		
25TCDC018	26.88	28.11	1.23	0.227		
25TCDC018	28.11	29.2	1.09	0.249		
25TCDC018	29.2	30.72	1.52	0.711		
25TCDC018	30.72	32.05	1.33	1.085		
25TCDC018	32.05	33.31	1.26	0.775		
25TCDC018	33.31	34	0.69	0.581		
25TCDC018	34	34.78	0.78	1.414		
25TCDC018	34.78	36.2	1.42	1.828		
25TCDC018	36.2	36.55	0.35	3.345		
25TCDC018	36.55	37.52	0.97	2.35		
25TCDC018	37.52	38.1	0.58	1.47		
25TCDC018	38.1	38.98	0.88	1.353		
25TCDC018	38.98	39.82	0.84	1.068		
25TCDC018	39.82	41	1.18	1.255		
25TCDC018	41	42	1	1.348		
25TCDC018	42	42.5	0.5	3.017		
25TCDC018	42.5	43.56	1.06	1.329		
25TCDC018	43.56	44.05	0.49	1.732		
25TCDC018	44.05	44.8	0.75	1.246		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC018	44.8	45.24	0.44	1.323		
25TCDC018	45.24	46.54	1.3	0.954		
25TCDC018	46.54	47.7	1.16	0.048		
25TCDC018	47.7	48.7	1	0.307		
25TCDC018	48.7	49.62	0.92	1.185		
25TCDC018	49.62	50.66	1.04	0.616		
25TCDC018	50.66	51.98	1.32	1.009		
25TCDC018	51.98	52.35	0.37	0.98		
25TCDC018	52.35	53.57	1.22	0.421		
25TCDC018	53.57	54.15	0.58	0.999		
25TCDC018	54.15	54.85	0.7	0.736		
25TCDC018	54.85	55.32	0.47	1.817		
25TCDC018	55.32	56.67	1.35	0.724		
25TCDC018	56.67	57.8	1.13	0.776		
25TCDC018	57.8	58.92	1.12	0.822		
25TCDC018	58.92	60.12	1.2	0.273		
25TCDC018	60.12	61.3	1.18	0.476		
25TCDC018	61.3	62.18	0.88	0.531		
25TCDC018	62.18	62.91	0.73	0.362		
25TCDC018	62.91	63.6	0.69	0.397		
25TCDC018	63.6	64.59	0.99	0.31		
25TCDC018	64.59	65.5	0.91	1.134		
25TCDC018	65.5	66.26	0.76	1.496		
25TCDC018	66.26	67.48	1.22	0.848		
25TCDC018	67.48	68.57	1.09	0.588		
25TCDC018	68.57	69.8	1.23	0.246		
25TCDC018	69.8	71.35	1.55	0.642		
25TCDC018	71.35	72.42	1.07	0.373		
25TCDC018	72.42	73.6	1.18	1.054		
25TCDC018	73.6	75.07	1.47	0.356		
25TCDC018	75.07	76.43	1.36	1.548		
25TCDC018	76.43	76.73	0.3	3.931		
25TCDC018	76.73	78	1.27	1.851		
25TCDC018	78	79.25	1.25	1.705		
25TCDC018	79.25	80.47	1.22	2.145		
25TCDC018	80.47	81.37	0.9	0.348		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC018	81.37	82.18	0.81	1.048		
25TCDC018	82.18	82.63	0.45	11.221		
25TCDC018	82.63	83.82	1.19	0.101		
25TCDC018	83.82	84.33	0.51	0.09		
25TCDC018	84.33	85.77	1.44	0.232		
25TCDC018	85.77	86.45	0.68	2.834		
25TCDC018	86.45	87.48	1.03	1.627		
25TCDC019	0	1.8	1.8	0.631	1036.6	0.048
25TCDC019	1.8	3.11	1.31	0.446	990.5	0.022
25TCDC019	3.11	4.32	1.21	0.278	848.1	0.036
25TCDC019	4.32	5.57	1.25	0.339	1021.6	0.037
25TCDC019	5.57	6.65	1.08	0.836	1806.4	0.039
25TCDC019	6.65	7.32	0.67	1.005	1681.5	0.098
25TCDC019	7.32	7.86	0.54	0.913	1646.5	0.112
25TCDC019	7.86	9.05	1.19	0.149	876.7	0.011
25TCDC019	9.05	10.21	1.16	0.271	918.3	0.029
25TCDC019	10.21	11.31	1.1	0.135	816.3	0.029
25TCDC019	11.31	12.4	1.09	0.375	1734.9	0.045
25TCDC019	12.4	13.48	1.08	0.349	2056.9	0.053
25TCDC019	13.48	14.21	0.73	0.055	1092.5	0.035
25TCDC019	14.21	14.65	0.44	0.199	885.9	0.016
25TCDC019	14.65	15.5	0.85	0.092	739.7	0.038
25TCDC019	15.5	16.2	0.7	0.187	1642.8	0.099
25TCDC019	16.2	16.61	0.41	2.333	610.4	6.51
25TCDC019	16.61	17.08	0.47	0.656	1822.9	0.046
25TCDC019	17.08	18.32	1.24	0.748	1636.7	0.027
25TCDC019	18.32	19.51	1.19	0.556	1723.1	0.05
25TCDC019	19.51	20.81	1.3	0.552	1714	0.046
25TCDC019	20.81	22.02	1.21	0.702	1973	0.104
25TCDC019	22.02	23.11	1.09	0.557	1839.8	0.047
25TCDC019	23.11	24.27	1.16	1.115	1694.4	0.047
25TCDC019	24.27	25.3	1.03	0.351	1410.5	0.024
25TCDC019	25.3	26.43	1.13	0.852	926.6	0.043
25TCDC019	26.43	27.5	1.07	0.123	1046.4	0.019
25TCDC019	27.5	28.32	0.82	1.237	2075.5	0.082
25TCDC019	28.32	28.75	0.43	1.26	2461.5	0.03

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC019	28.75	29.94	1.19	1.028	253.1	0.087
25TCDC019	29.94	31.2	1.26	0.912	2100.2	0.013
25TCDC019	31.2	31.95	0.75	0.732	2166	0.016
25TCDC019	31.95	32.89	0.94	1.659	3666.5	0.034
25TCDC019	32.89	34.17	1.28	1.354	1834.7	0.077
25TCDC019	34.17	35.03	0.86	1.401	1728.4	0.02
25TCDC019	35.03	35.95	0.92	0.584	1198.1	0.03
25TCDC019	35.95	36.88	0.93	0.61	1554.3	0.09
25TCDC019	36.88	37.31	0.43	0.668	2209.4	0.31
25TCDC019	37.31	38.23	0.92	0.809	1432.6	0.053
25TCDC019	38.23	39.25	1.02	1.278	1311.4	0.115
25TCDC019	39.25	39.6	0.35	2.12	971.5	0.76
25TCDC019	39.6	40.27	0.67	0.969	1509.6	0.025
25TCDC019	40.27	40.58	0.31	1.094	2726.1	0.67
25TCDC019	40.58	41.7	1.12	1.491	2156.7	0.41
25TCDC019	41.7	42.95	1.25	0.758	2699.8	0.035
25TCDC019	42.95	43.8	0.85	1.001	2275.4	0.039
25TCDC019	43.8	44.93	1.13	0.744	1665.9	0.007
25TCDC019	44.93	46.02	1.09	1.359	1962.8	0.015
25TCDC019	46.02	47.33	1.31	0.61	2096.6	0.013
25TCDC019	47.33	48.62	1.29	0.763	1735.1	0.01
25TCDC019	48.62	49.75	1.13	1.529	1860.2	0.019
25TCDC019	49.75	50.67	0.92	0.453	1728.9	0.019
25TCDC019	50.67	51.82	1.15	0.048	608.7	0.011
25TCDC019	51.82	52.41	0.59	0.148	960.5	0.018
25TCDC019	52.41	53.17	0.76	0.055	382.6	0.011
25TCDC019	53.17	54.08	0.91	0.874	721.8	0.045
25TCDC019	54.08	54.8	0.72	0.847	607.4	0.4
25TCDC019	54.8	55.39	0.59	1.123	336.5	2.51
25TCDC019	55.39	55.79	0.4	1.868	1683	30.24
25TCDC019	55.79	56.43	0.64	1.332	511	0.11
25TCDC019	56.43	57	0.57	1.974	2294.1	0.64
25TCDC019	57	57.55	0.55	0.926	1616.4	0.085
25TCDC019	57.55	58.02	0.47	2.543	1072.7	21.83
25TCDC019	58.02	59.13	1.11	0.66	1505.7	0.31
25TCDC019	59.13	59.55	0.42	2.08	2859.6	0.068

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC019	59.55	59.95	0.4	2.701	2128.8	1.25
25TCDC019	59.95	61.5	1.55	0.508	1794	0.034
25TCDC019	61.5	62.39	0.89	0.614	1210.1	0.033
25TCDC019	62.39	63.67	1.28	0.18	1175.7	0.038
25TCDC019	63.67	64.87	1.2	0.433	1493.5	0.059
25TCDC019	64.87	65.85	0.98	1.983	2369.2	0.073
25TCDC019	65.85	66.8	0.95	0.613	1712.6	0.018
25TCDC019	66.8	67.92	1.12	0.638	1394.6	0.015
25TCDC019	67.92	68.28	0.36	1.366	1847.5	0.013
25TCDC019	68.28	69.5	1.22	1.948	2385.5	0.024
25TCDC019	69.5	70.41	0.91	0.835	1785.8	0.023
25TCDC019	70.41	71.62	1.21	1.224	1487.5	0.034
25TCDC019	71.62	72.8	1.18	0.63	1734.2	0.014
25TCDC019	72.8	73.9	1.1	0.323	2031.1	0.029
25TCDC019	73.9	74.75	0.85	0.29	860.3	0.011
25TCDC019	74.75	75.9	1.15	0.13	506.4	0.012
25TCDC019	75.9	77.42	1.52	0.122	550.9	0.019
25TCDC020	0	1	1	0.331		
25TCDC020	1	2.41	1.41	0.094		
25TCDC020	2.41	3.34	0.93	0.403		
25TCDC020	3.34	3.96	0.62	0.432		
25TCDC020	3.96	5.62	1.66	0.753		
25TCDC020	5.62	7.01	1.39	0.412		
25TCDC020	7.01	8.03	1.02	0.123		
25TCDC020	8.03	8.84	0.81	0.71		
25TCDC020	8.84	9.56	0.72	0.58		
25TCDC020	9.56	11.01	1.45	0.417		
25TCDC020	11.01	12.37	1.36	0.644		
25TCDC020	12.37	13.66	1.29	0.098		
25TCDC020	13.66	14.72	1.06	0.311		
25TCDC020	14.72	15.91	1.19	0.0075		
25TCDC020	15.91	16.72	0.81	0.14		
25TCDC020	16.72	18.05	1.33	0.0075		
25TCDC020	18.05	19.07	1.02	0.179		
25TCDC020	19.07	19.5	0.43	0.036		
25TCDC020	19.5	20.16	0.66	0.449		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC020	20.16	20.97	0.81	0.638		
25TCDC020	20.97	21.94	0.97	0.893		
25TCDC020	21.94	23.44	1.5	0.063		
25TCDC020	23.44	24.69	1.25	0.152		
25TCDC020	24.69	25.88	1.19	0.676		
25TCDC020	25.88	26.42	0.54	1.405		
25TCDC020	26.42	27.78	1.36	0.864		
25TCDC020	27.78	28.35	0.57	0.954		
25TCDC020	28.35	29.24	0.89	0.56		
25TCDC020	29.24	29.69	0.45	1.262		
25TCDC020	29.69	30.68	0.99	0.535		
25TCDC020	30.68	31.1	0.42	1.448		
25TCDC020	31.1	31.58	0.48	2.513		
25TCDC020	31.58	32.11	0.53	2.1		
25TCDC020	32.11	32.49	0.38	1.602		
25TCDC020	32.49	33.07	0.58	2.019		
25TCDC020	33.07	33.73	0.66	0.947		
25TCDC020	33.73	34.24	0.51	4.658		
25TCDC020	34.24	34.6	0.36	3.455		
25TCDC020	34.6	35.16	0.56	1.196		
25TCDC020	35.16	36.35	1.19	1.683		
25TCDC020	36.35	37.04	0.69	1.811		
25TCDC020	37.04	38.42	1.38	0.655		
25TCDC020	38.42	38.78	0.36	1.895		
25TCDC020	38.78	40.51	1.73	1.637		
25TCDC020	40.51	40.84	0.33	3.076		
25TCDC020	40.84	41.83	0.99	0.81		
25TCDC020	41.83	42.23	0.4	1.837		
25TCDC020	42.23	43.69	1.46	1.096		
25TCDC020	43.69	44.94	1.25	0.7		
25TCDC020	44.94	46.56	1.62	0.999		
25TCDC020	46.56	48.06	1.5	1.127		
25TCDC020	48.06	49.68	1.62	0.962		
25TCDC020	49.68	51.33	1.65	0.891		
25TCDC020	51.33	53	1.67	0.867		
25TCDC020	53	53.67	0.67	1.27		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC020	53.67	54.44	0.77	0.314		
25TCDC020	54.44	55.38	0.94	3.423		
25TCDC020	55.38	56.51	1.13	2.415		
25TCDC020	56.51	57.17	0.66	2.424		
25TCDC020	57.17	57.61	0.44	0.76		
25TCDC020	57.61	58.53	0.92	0.62		
25TCDC020	58.53	59.77	1.24	0.709		
25TCDC020	59.77	60.16	0.39	1.326		
25TCDC020	60.16	60.96	0.8	1.733		
25TCDC020	60.96	61.4	0.44	1.038		
25TCDC020	61.4	62.87	1.47	0.953		
25TCDC020	62.87	63.72	0.85	3.109		
25TCDC020	63.72	64.44	0.72	1.911		
25TCDC020	64.44	65.19	0.75	2.394		
25TCDC020	65.19	65.72	0.53	4.309		
25TCDC020	65.72	66.86	1.14	3.697		
25TCDC020	66.86	68.65	1.79	0.167		
25TCDC020	68.65	69.73	1.08	0.491		
25TCDC020	69.73	70.54	0.81	0.215		
25TCDC020	70.54	71.26	0.72	0.283		
25TCDC020	71.26	72.63	1.37	0.046		
25TCDC020	72.63	74.22	1.59	0.103		
25TCDC020	74.22	75.2	0.98	0.14		
25TCDC020	75.2	76.17	0.97	0.107		
25TCDC024	0	0.79	0.79	0.218	436.5	0.108
25TCDC024	0.79	1.09	0.3	0.188	442.9	2.66
25TCDC024	1.09	2.07	0.98	0.084	469.2	0.027
25TCDC024	2.07	3.2	1.13	0.054	288.7	0.011
25TCDC024	3.2	4.41	1.21	0.112	447.7	0.009
25TCDC024	4.41	5.48	1.07	0.093	516.2	0.017
25TCDC024	5.48	6.56	1.08	0.068	476	0.03
25TCDC024	6.56	7.47	0.91	0.056	350.4	0.015
25TCDC024	7.47	8.8	1.33	0.068	757.9	0.008
25TCDC024	8.8	9.78	0.98	0.059	485.5	0.007
25TCDC024	9.78	10.82	1.04	0.021	276.7	0.007
25TCDC024	10.82	12.1	1.28	0.035	70.4	0.003

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC024	12.1	13.28	1.18	0.04	394	0.015
25TCDC024	13.28	14.56	1.28	0.0075	197.9	0.006
25TCDC024	14.56	15.23	0.67	0.085	904.7	0.015
25TCDC024	15.23	16.04	0.81	0.065	909.7	0.031
25TCDC024	16.04	17.29	1.25	0.043	346.3	0.019
25TCDC024	17.29	18.71	1.42	0.0075	276.9	0.023
25TCDC024	18.71	19.81	1.1	0.021	243	0.021
25TCDC024	19.81	20.8	0.99	0.0075	151.9	0.021
25TCDC024	20.8	22.16	1.36	0.104	549	0.028
25TCDC024	22.16	23.75	1.59	0.268	552.2	0.017
25TCDC024	23.75	24.9	1.15	0.127	480.4	0.017
25TCDC024	24.9	26.03	1.13	0.085	816.1	0.013
25TCDC024	26.03	27.03	1	0.099	922.4	0.023
25TCDC024	27.03	28.15	1.12	0.665	1186	0.018
25TCDC024	28.15	28.65	0.5	2.064	1433.3	0.13
25TCDC024	28.65	29.28	0.63	1.672	1839.5	0.023
25TCDC024	29.28	29.9	0.62	0.282	942.3	0.053
25TCDC024	29.9	30.5	0.6	0.253	1109.1	0.092
25TCDC024	30.5	31	0.5	0.98	951	0.63
25TCDC024	31	31.6	0.6	1.939	493	0.183
25TCDC024	31.6	31.9	0.3	1.277	553.7	42.07
25TCDC024	31.9	32.35	0.45	0.577	422.4	0.083
25TCDC024	32.35	32.86	0.51	0.38	816	0.029
25TCDC024	32.86	33.5	0.64	0.172	545.4	0.025
25TCDC024	33.5	33.93	0.43	0.99	624	0.03
25TCDC024	33.93	34.63	0.7	0.285	692.7	0.024
25TCDC024	34.63	35.23	0.6	2.421	1250.4	0.036
25TCDC024	35.23	36.24	1.01			
25TCDC024	36.24	36.82	0.58	0.171	728.6	0.015
25TCDC024	36.82	37.31	0.49	0.379	675.6	0.021
25TCDC024	37.31	38.1	0.79	0.259	616	0.029
25TCDC024	38.1	38.74	0.64	0.142	264.2	0.016
25TCDC024	38.74	39.1	0.36	0.247	915.3	0.021
25TCDC024	39.1	39.81	0.71	0.896	1463.7	0.043
25TCDC024	39.81	40.32	0.51	0.249	593.7	0.026
25TCDC024	40.32	41.52	1.2	2.009	1501.8	0.059

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC024	41.52	42.09	0.57	1.29	1512	0.139
25TCDC024	42.09	43.1	1.01	1.398	927	0.182
25TCDC024	43.1	44.05	0.95	1.973	924.4	0.147
25TCDC024	44.05	45.11	1.06	0.057	1346.7	0.098
25TCDC024	45.11	46.24	1.13	0.336	1361	0.049
25TCDC024	46.24	46.85	0.61	0.032	871.5	0.025
25TCDC024	46.85	47.82	0.97	0.02	980.2	0.026
25TCDC024	47.82	48.7	0.88	0.062	531.6	0.008
25TCDC024	48.7	49.96	1.26	0.139	452.4	0.007
25TCDC024	49.96	50.96	1	0.0075	995.2	0.02
25TCDC024	50.96	52.1	1.14	0.015	364.7	0.008
25TCDC024	52.1	53.56	1.46	0.0075	856.4	0.008
25TCDC024	53.56	54.82	1.26	0.073	742.7	0.005
25TCDC024	54.82	55.75	0.93	0.045	779.8	0.004
25TCDC024	55.75	57.06	1.31	0.079	867.2	0.005
25TCDC024	57.06	57.8	0.74	0.206	576.9	0.007
25TCDC024	57.8	59.2	1.4	0.065	1029.2	0.008
25TCDC024	59.2	60.1	0.9	0.0075	719	0.005
25TCDC024	60.1	61.37	1.27	0.0075	565.2	0.004
25TCDC024	61.37	62.35	0.98	0.039	730.2	0.007
25TCDC024	62.35	62.77	0.42	0.025	210.1	0.002
25TCDC024	62.77	64	1.23	0.344	956.8	0.008
25TCDC024	64	64.98	0.98	0.035	577.8	0.005
25TCDC024	64.98	65.65	0.67	0.067	232.8	0.002
25TCDC024	65.65	66.4	0.75	0.083	257	0.002
25TCDC024	66.4	67.69	1.29	0.046	312.6	0.004
25TCDC024	67.69	68.69	1	0.0075	321	0.004
25TCDC024	68.69	69.16	0.47	0.032	123.7	0.004
25TCDC024	69.16	70.34	1.18	0.015	169.5	0.003
25TCDC024	70.34	71.32	0.98	0.146	348.9	0.004
25TCDC024	71.32	72.3	0.98	0.035	170.7	0.024
25TCDC024	72.3	73.27	0.97	0.0075	32.8	0.003
25TCDC024	73.27	74.38	1.11	0.037	386.1	0.004
25TCDC024	74.38	75.34	0.96	0.055	436.6	0.008
25TCDC024	75.34	76.4	1.06	0.803	1313.8	0.005
25TCDC024	76.4	77.4	1	1.147	761.6	0.005

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC024	77.4	78.47	1.07	0.772	1462.6	0.007
25TCDC024	78.47	79.1	0.63	1.728	4613.5	0.012
25TCDC024	79.1	79.68	0.58	0.543	2913.6	0.007
25TCDC024	79.68	80.47	0.79	0.053	193.4	0.007
25TCDC045	0	0.75	0.75			
25TCDC045	0.75	1.73	0.98	0.261		
25TCDC045	1.73	2.74	1.01			
25TCDC045	2.74	3.51	0.77	1.877		
25TCDC045	3.51	3.9	0.39	0.2		
25TCDC045	3.9	4.7	0.8	0.083		
25TCDC045	4.7	5.43	0.73	0.13		
25TCDC045	5.43	6.52	1.09	0.052		
25TCDC045	6.52	7.98	1.46	0.088		
25TCDC045	7.98	8.26	0.28	0.088		
25TCDC045	8.26	9.2	0.94	0.124		
25TCDC045	9.2	9.8	0.6	0.113		
25TCDC045	9.8	10.27	0.47	0.171		
25TCDC045	10.27	11.23	0.96	0.068		
25TCDC045	11.23	12.14	0.91	0.088		
25TCDC045	12.14	13.23	1.09	0.0075		
25TCDC045	13.23	14.41	1.18	0.041		
25TCDC045	14.41	15.22	0.81	0.0075		
25TCDC045	15.22	16.25	1.03	0.044		
25TCDC045	16.25	17.17	0.92	0.0075		
25TCDC045	17.17	18.03	0.86	0.0075		
25TCDC045	18.03	18.35	0.32	0.034		
25TCDC045	18.35	19.68	1.33	0.028		
25TCDC045	19.68	20.38	0.7	0.046		
25TCDC045	20.38	21.47	1.09	0.039		
25TCDC045	21.47	22.25	0.78	0.043		
25TCDC045	22.25	23.43	1.18	2.771		
25TCDC045	23.43	24.45	1.02	0.666		
25TCDC045	24.45	25.42	0.97	0.763		
25TCDC045	25.42	26.52	1.1	0.641		
25TCDC045	26.52	27.34	0.82	0.055		
25TCDC045	27.34	27.81	0.47	0.0075		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC045	27.81	28.42	0.61	0.0075		
25TCDC045	28.42	29.3	0.88	0.047		
25TCDC045	29.3	30.54	1.24	0.0075		
25TCDC045	30.54	31.69	1.15	0.019		
25TCDC045	31.69	32.72	1.03	0.0075		
25TCDC045	32.72	33.63	0.91	0.0075		
25TCDC045	33.63	34.75	1.12	0.0075		
25TCDC045	34.75	36.12	1.37	0.131		
25TCDC045	36.12	37.43	1.31	0.137		
25TCDC045	37.43	38.21	0.78	0.041		
25TCDC045	38.21	39.02	0.81	0.024		
25TCDC045	39.02	39.96	0.94	0.024		
25TCDC045	39.96	40.81	0.85	0.0075		
25TCDC045	40.81	41.64	0.83	0.0075		
25TCDC045	41.64	42.29	0.65	0.0075		
25TCDC045	42.29	43.43	1.14	0.0075		
25TCDC045	43.43	44.5	1.07	0.034		
25TCDC045	44.5	45.76	1.26	0.0075		
25TCDC045	45.76	46.76	1	0.0075		
25TCDC045	46.76	47.95	1.19	0.032		
25TCDC045	47.95	49.11	1.16	0.0075		
25TCDC045	49.11	49.83	0.72	0.0075		
25TCDC045	49.83	50.88	1.05	0.018		
25TCDC045	50.88	52	1.12	0.029		
25TCDC045	52	53.07	1.07	0.0075		
25TCDC045	53.07	54.04	0.97	0.021		
25TCDC045	54.04	55.06	1.02	0.022		
25TCDC045	55.06	55.36	0.3	0.0075		
25TCDC045	55.36	56.75	1.39	0.0075		
25TCDC045	56.75	57.43	0.68	0.026		
25TCDC045	57.43	58.15	0.72	0.041		
25TCDC045	58.15	59.23	1.08	0.111		
25TCDC045	59.23	60.45	1.22	0.276		
25TCDC045	60.45	61.33	0.88	0.0075		
25TCDC045	61.33	62.06	0.73	0.173		
25TCDC045	62.06	63.15	1.09	0.023		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC045	63.15	63.97	0.82	0.0075		
25TCDC045	63.97	65.1	1.13	0.0075		
25TCDC045	65.1	66.3	1.2	0.056		
25TCDC045	66.3	67.7	1.4	0.048		
25TCDC045	67.7	68.85	1.15	0.0075		
25TCDC045	68.85	69.8	0.95	0.021		
25TCDC045	69.8	71.2	1.4	0.0075		
25TCDC045	71.2	72.2	1	0.109		
25TCDC045	72.2	73.03	0.83	0.185		
25TCDC045	73.03	73.77	0.74	0.045		
25TCDC045	73.77	75.1	1.33	0.14		
25TCDC045	75.1	76.35	1.25	0.0075		
25TCDC045	76.35	77.24	0.89	0.0075		
25TCDC045	77.24	78.49	1.25	0.0075		
25TCDC051	0	0.41	0.41			
25TCDC051	0.41	1.13	0.72	0.268		
25TCDC051	1.13	1.92	0.79	0.248		
25TCDC051	1.92	2.4	0.48			
25TCDC051	2.4	2.7	0.3	0.366		
25TCDC051	2.7	3.62	0.92	0.238		
25TCDC051	3.62	3.92	0.3	0.076		
25TCDC051	3.92	4.3	0.38	0.051		
25TCDC051	4.3	5.33	1.03	0.091		
25TCDC051	5.33	6.5	1.17	0.046		
25TCDC051	6.5	7.62	1.12	0.023		
25TCDC051	7.62	8.7	1.08	0.073		
25TCDC051	8.7	9.75	1.05	0.023		
25TCDC051	9.75	10.55	0.8	0.015		
25TCDC051	10.55	11.4	0.85	0.0075		
25TCDC051	11.4	12.6	1.2	0.025		
25TCDC051	12.6	13.02	0.42	0.0075		
25TCDC051	13.02	14.28	1.26	0.042		
25TCDC051	14.28	15.23	0.95	0.0075		
25TCDC051	15.23	16.27	1.04	0.016		
25TCDC051	16.27	17.56	1.29	0.0075		
25TCDC051	17.56	18.92	1.36	0.0075		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC051	18.92	20.02	1.1	0.0075		
25TCDC051	20.02	20.94	0.92	0.0075		
25TCDC051	20.94	22.13	1.19	0.0075		
25TCDC051	22.13	23	0.87	0.03		
25TCDC051	23	23.68	0.68	0.525		
25TCDC051	23.68	23.9	0.22			
25TCDC051	23.9	24.38	0.48	0.095		
25TCDC051	24.38	25.52	1.14	0.067		
25TCDC051	25.52	26.26	0.74	0.024		
25TCDC051	26.26	27.43	1.17	0.0075		
25TCDC051	27.43	28.43	1	0.025		
25TCDC051	28.43	29.52	1.09	0.0075		
25TCDC051	29.52	30.3	0.78	0.022		
25TCDC051	30.3	31.5	1.2	0.042		
25TCDC051	31.5	32.4	0.9	0.0075		
25TCDC051	32.4	33.53	1.13	0.0075		
25TCDC051	33.53	34.64	1.11	0.0075		
25TCDC051	34.64	35.33	0.69	0.0075		
25TCDC051	35.33	36.58	1.25	0.0075		
25TCDC051	36.58	37.2	0.62	0.0075		
25TCDC051	37.2	38.17	0.97	0.0075		
25TCDC051	38.17	39.23	1.06	0.123		
25TCDC051	39.23	40.23	1	0.0075		
25TCDC051	40.23	41	0.77	0.0075		
25TCDC051	41	41.55	0.55	0.028		
25TCDC051	41.55	42.04	0.49	0.0075		
25TCDC051	42.04	43.01	0.97	0.0075		
25TCDC051	43.01	43.71	0.7	0.0075		
25TCDC051	43.71	44.41	0.7	0.095		
25TCDC051	44.41	45.24	0.83	0.194		
25TCDC051	45.24	46.08	0.84	0.0075		
25TCDC051	46.08	46.8	0.72	0.0075		
25TCDC051	46.8	47.75	0.95	0.107		
25TCDC051	47.75	48.77	1.02	0.0075		
25TCDC051	48.77	49.25	0.48	0.114		
25TCDC051	49.25	50.1	0.85	0.039		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC051	50.1	51.12	1.02	0.025		
25TCDC051	51.12	52.17	1.05	0.0075		
25TCDC051	52.17	53.22	1.05	0.0075		
25TCDC051	53.22	54.41	1.19	0.021		
25TCDC051	54.41	55.24	0.83	0.0075		
25TCDC051	55.24	56.39	1.15	0.0075		
25TCDC051	56.39	57.39	1	0.105		
25TCDC051	57.39	58.14	0.75	1.502		
25TCDC051	58.14	58.95	0.81	0.139		
25TCDC051	58.95	59.3	0.35	0.049		
25TCDC051	59.3	60	0.7	0.025		
25TCDC051	60	60.44	0.44	0.0075		
25TCDC051	60.44	61.31	0.87	0.095		
25TCDC051	61.31	62.24	0.93	0.116		
25TCDC051	62.24	63.16	0.92	0.142		
25TCDC051	63.16	64.06	0.9	0.083		
25TCDC051	64.06	65.32	1.26	0.131		
25TCDC051	65.32	66.23	0.91	0.318		
25TCDC051	66.23	67.35	1.12	0.131		
25TCDC051	67.35	68.58	1.23	0.538		
25TCDC051	68.58	69.62	1.04	0.225		
25TCDC051	69.62	70.78	1.16	0.055		
25TCDC051	70.78	71.86	1.08	0.084		
25TCDC051	71.86	72.72	0.86	0.085		
25TCDC051	72.72	73.9	1.18	0.048		
25TCDC051	73.9	74.68	0.78	0.171		
25TCDC051	74.68	75.1	0.42	0.179		
25TCDC051	75.1	75.85	0.75	0.095		
25TCDC051	75.85	76.75	0.9	0.461		
25TCDC051	76.75	77.44	0.69	0.367		
25TCDC051	77.44	77.96	0.52	0.108		
25TCDC051	77.96	78.94	0.98	0.053		
25TCDC051	78.94	79.92	0.98	0.359		
25TCDC051	79.92	81.47	1.55			
25TCDC051	81.47	82.91	1.44	0.272		
25TCDC051	82.91	83.65	0.74	1.218		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCDC051	83.65	84.5	0.85	0.0075		
25TCDC051	84.5	84.89	0.39			
25TCDC051	84.89	86.2	1.31	0.0075		
25TCDC051	86.2	87.3	1.1	0.027		
25TCDC051	87.3	88.39	1.09	0.0075		
25TCMW002	0	1.52	1.52	0.0075		
25TCMW002	1.52	3.05	1.53	0.02		
25TCMW002	3.05	4.57	1.52	0.034		
25TCMW002	4.57	6.1	1.53	0.0075		
25TCMW002	6.1	7.62	1.52	0.0075		
25TCMW002	7.62	9.14	1.52	0.025		
25TCMW002	9.14	10.67	1.53	0.0075		
25TCMW002	10.67	12.19	1.52	0.0075		
25TCMW002	12.19	13.72	1.53	0.0075		
25TCMW002	13.72	15.24	1.52	0.033		
25TCMW002	15.24	16.76	1.52	0.021		
25TCMW002	16.76	18.29	1.53	0.0075		
25TCMW002	18.29	19.81	1.52	0.24		
25TCMW002	19.81	21.34	1.53	0.0075		
25TCMW002	21.34	22.86	1.52	0.055		
25TCMW002	22.86	24.38	1.52	0.032		
25TCMW002	24.38	25.91	1.53	0.0075		
25TCMW002	25.91	27.43	1.52	0.038		
25TCMW002	27.43	28.96	1.53	0.021		
25TCMW002	28.96	30.48	1.52	0.042		
25TCMW002	30.48	32	1.52	0.0075		
25TCMW002	32	33.53	1.53	0.0075		
25TCMW002	33.53	35.05	1.52	0.02		
25TCMW002	35.05	36.58	1.53	0.0075		
25TCMW002	36.58	38.1	1.52	0.025		
25TCMW002	38.1	39.62	1.52	0.0075		
25TCMW002	39.62	41.15	1.53	0.0075		
25TCMW002	41.15	42.67	1.52	0.038		
25TCMW002	42.67	44.2	1.53	0.0075		
25TCMW002	44.2	45.72	1.52	0.0075		
25TCMW002	45.72	47.24	1.52	0.0075		

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCMW002	47.24	48.77	1.53	0.029		
25TCMW002	48.77	50.29	1.52	0.026		
25TCMW002	50.29	51.82	1.53	0.0075		
25TCMW002	51.82	53.34	1.52	0.0075		
25TCMW002	53.34	54.86	1.52	0.022		
25TCMW002	54.86	56.39	1.53	0.04		
25TCMW002	56.39	57.91	1.52	0.031		
25TCMW002	57.91	59.44	1.53	0.047		
25TCMW002	59.44	60.96	1.52	0.188		
25TCMW002	60.96	62.48	1.52	0.024		
25TCMW002	62.48	64.01	1.53	0.026		
25TCMW002	64.01	65.53	1.52	0.016		
25TCMW002	65.53	67.06	1.53	0.057		
25TCMW002	67.06	68.58	1.52	0.044		
25TCMW002	68.58	70.1	1.52	0.363		
25TCMW002	70.1	71.63	1.53	0.317		
25TCMW002	71.63	73.15	1.52	0.272		
25TCMW002	73.15	74.68	1.53	0.171		
25TCMW002	74.68	76.2	1.52	0.276		
25TCMW002	76.2	77.72	1.52	0.129		
25TCMW002	77.72	79.25	1.53	0.653		
25TCMW003	0	1.52	1.52	0.218	254.4	0.02
25TCMW003	1.52	3.05	1.53	0.149	467.4	0.026
25TCMW003	3.05	4.57	1.52	0.133	312.1	0.026
25TCMW003	4.57	6.1	1.53	0.14	343.2	0.028
25TCMW003	6.1	7.62	1.52	0.062	281.6	0.026
25TCMW003	7.62	9.14	1.52	0.201	374.1	0.026
25TCMW003	9.14	10.67	1.53	0.132	287.1	0.021
25TCMW003	10.67	12.19	1.52	0.094	283.5	0.019
25TCMW003	12.19	13.72	1.53	0.042	233	0.022
25TCMW005	0	1.52	1.52	0.023	138.6	0.004
25TCMW005	1.52	3.05	1.53	0.028	44.3	0.002
25TCMW005	3.05	4.57	1.52	0.0075	18.6	0
25TCMW005	4.57	6.1	1.53	0.0075	18	0
25TCMW005	6.1	7.62	1.52	0.0075	13.9	0
25TCMW005	7.62	9.14	1.52	0.034	14.6	0.001

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCMW005	9.14	10.67	1.53	0.0075	36	0.001
25TCMW005	10.67	12.19	1.52	0.103	321.7	0.004
25TCRC002	0	1.52	1.52	0.095	81	0.003
25TCRC002	1.52	3.05	1.53	0.419	818.5	0.013
25TCRC002	3.05	4.57	1.52	0.705	1088.9	0.033
25TCRC002	4.57	6.1	1.53	0.851	1398.8	0.111
25TCRC002	6.1	7.62	1.52	0.631	236.2	0.05
25TCRC002	7.62	9.14	1.52	0.661	241.7	0.055
25TCRC002	9.14	10.67	1.53	1.026	290.2	0.037
25TCRC002	10.67	12.19	1.52	0.835	487	0.064
25TCRC002	12.19	13.72	1.53	0.686	174.2	0.085
25TCRC002	13.72	15.24	1.52	2.61	959	0.205
25TCRC002	15.24	16.76	1.52	0.711	1165.2	0.056
25TCRC002	16.76	18.29	1.53	0.094	714.1	0.013
25TCRC002	18.29	19.81	1.52	0.031	220.8	0.005
25TCRC002	19.81	21.34	1.53	0.137	261	0.006
25TCRC002	21.34	22.86	1.52	0.424	493.7	0.025
25TCRC002	22.86	24.38	1.52	0.043	300.6	0.011
25TCRC002	24.38	25.91	1.53	0.096	347.7	0.006
25TCRC002	25.91	27.43	1.52	0.537	615.3	0.077
25TCRC002	27.43	28.96	1.53	1.083	669.3	0.178
25TCRC002	28.96	30.48	1.52	0.221	629	0.034
25TCRC002	30.48	32	1.52	0.333	713.3	0.111
25TCRC002	32	33.53	1.53	0.232	503.8	0.059
25TCRC002	33.53	35.05	1.52	0.097	845.4	0.007
25TCRC002	35.05	36.58	1.53	0.213	527.8	0.009
25TCRC002	36.58	38.1	1.52	0.14	430.8	0.008
25TCRC002	38.1	39.62	1.52	0.106	355.9	0.004
25TCRC002	39.62	41.15	1.53	0.063	315.7	0.004
25TCRC002	41.15	42.67	1.52	0.267	278.2	0.004
25TCRC002	42.67	44.2	1.53	0.122	191.8	0.068
25TCRC002	44.2	45.72	1.52	0.186	211	0.016
25TCRC002	45.72	47.24	1.52	0.287	441.5	0.036
25TCRC002	47.24	48.77	1.53	0.395	520.6	0.032
25TCRC002	48.77	50.29	1.52	0.495	765.2	0.015
25TCRC003	0	1.52	1.52	0.148	768.5	0.014

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC003	1.52	3.05	1.53	0.482	1324.8	0.019
25TCRC003	3.05	4.57	1.52	0.595	1504.4	0.017
25TCRC003	4.57	6.1	1.53	0.453	494.5	0.012
25TCRC003	6.1	7.62	1.52	0.295	601.5	0.025
25TCRC003	7.62	9.14	1.52	0.176	251.7	0.007
25TCRC003	9.14	10.67	1.53	0.194	151.1	0.006
25TCRC003	10.67	12.19	1.52	0.254	237.1	0.038
25TCRC003	12.19	13.72	1.53	0.627	524.2	0.022
25TCRC003	13.72	15.24	1.52	0.315	841.5	0.025
25TCRC003	15.24	16.76	1.52	0.229	349.4	0.016
25TCRC003	16.76	18.29	1.53	0.294	502	0.081
25TCRC003	18.29	19.81	1.52	0.266	699.8	0.033
25TCRC003	19.81	21.34	1.53	0.3	1093.4	0.073
25TCRC003	21.34	22.86	1.52	0.244	757.3	0.041
25TCRC003	22.86	24.38	1.52	0.222	746.2	0.051
25TCRC003	24.38	25.91	1.53	0.117	221.8	0.161
25TCRC003	25.91	27.43	1.52	0.185	980.8	0.21
25TCRC003	27.43	28.96	1.53	1.982	452.9	1.11
25TCRC003	28.96	30.48	1.52	1.288	197.3	1.07
25TCRC003	30.48	32	1.52	10.9	584.6	0.81
25TCRC003	32	33.53	1.53	5.013	1032.6	1.26
25TCRC003	33.53	35.05	1.52	3.09	2348.8	0.8
25TCRC003	35.05	36.58	1.53	0.386	1446.2	0.66
25TCRC003	36.58	38.1	1.52	0.083	1565.5	0.42
25TCRC003	38.1	39.62	1.52	0.675	1417.7	0.27
25TCRC003	39.62	41.15	1.53	2.067	6560	3.6
25TCRC003	41.15	42.67	1.52	0.064	2106.6	0.22
25TCRC003	42.67	44.2	1.53	0.061	1875.8	0.137
25TCRC003	44.2	45.72	1.52	0.296	1057.4	0.052
25TCRC003	45.72	47.24	1.52	0.054	553.6	0.035
25TCRC003	47.24	48.77	1.53	0.067	460.9	0.026
25TCRC003	48.77	50.29	1.52	0.033	352.4	0.023
25TCRC004	0	1.52	1.52		1462.7	0.3
25TCRC004	1.52	3.05	1.53	1.203	2188.9	0.161
25TCRC004	3.05	4.57	1.52	1.082	3065.2	0.34
25TCRC004	4.57	6.1	1.53	1.788	687.3	0.168

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC004	6.1	7.62	1.52	2.155	610.1	0.8
25TCRC004	7.62	9.14	1.52	1.87	1931	0.175
25TCRC004	9.14	10.67	1.53	1.197	584.2	0.099
25TCRC004	10.67	12.19	1.52	0.767	627.3	0.18
25TCRC004	12.19	13.72	1.53	1.291	682.1	0.137
25TCRC004	13.72	15.24	1.52	0.791	815.9	0.066
25TCRC004	15.24	16.76	1.52	0.883	937.1	0.062
25TCRC004	16.76	18.29	1.53	0.484	763.7	0.097
25TCRC004	18.29	19.81	1.52	0.57	1014.6	0.031
25TCRC004	19.81	21.34	1.53	0.59	1668.4	0.03
25TCRC004	21.34	22.86	1.52	2.645	2058.1	0.29
25TCRC004	22.86	24.38	1.52	0.402	1052.1	0.021
25TCRC004	24.38	25.91	1.53	0.39	3369.3	0.027
25TCRC004	25.91	27.43	1.52	0.579	1200.4	0.062
25TCRC004	27.43	28.96	1.53	0.156	396.8	0.017
25TCRC004	28.96	30.48	1.52	0.037	57.1	0.014
25TCRC004	30.48	32	1.52	0.044	279.5	0.013
25TCRC004	32	33.53	1.53	0.068	283.3	0.009
25TCRC004	33.53	35.05	1.52	0.031	154	0.011
25TCRC004	35.05	36.58	1.53	0.158	169.2	0.013
25TCRC004	36.58	38.1	1.52	0.07	270	0.011
25TCRC004	38.1	39.62	1.52	0.076	332.1	0.016
25TCRC004	39.62	41.15	1.53	1.062	6083.4	0.032
25TCRC004	41.15	42.67	1.52	0.292	2833.5	0.013
25TCRC004	42.67	44.2	1.53	0.161	1918.2	0.017
25TCRC004	44.2	45.72	1.52	0.148	3300.9	0.057
25TCRC004	45.72	47.24	1.52	0.024	1201.3	0.057
25TCRC004	47.24	48.77	1.53	0.065	1702.6	0.046
25TCRC004	48.77	50.29	1.52	0.334	2104.8	0.059
25TCRC004	50.29	51.82	1.53	0.65	2002	0.076
25TCRC004	51.82	53.34	1.52	0.243	906.8	0.012
25TCRC004	53.34	54.86	1.52	0.368	734.2	0.019
25TCRC004	54.86	56.39	1.53	0.61	5599.1	0.027
25TCRC004	56.39	57.91	1.52	0.36	3400.4	0.064
25TCRC004	57.91	59.44	1.53	0.614	4382	0.044
25TCRC004	59.44	60.96	1.52	0.389	4019.9	0.081

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC008	1.52	3.05	1.53	0.123	521.4	0.037
25TCRC008	3.05	4.57	1.52	0.156	335.5	0.017
25TCRC008	4.57	6.1	1.53	0.113	683.3	0.015
25TCRC008	6.1	7.62	1.52	0.105	729.7	0.015
25TCRC008	7.62	9.14	1.52	0.069	249	0.011
25TCRC008	9.14	10.67	1.53	0.046	217.8	0.007
25TCRC008	10.67	12.19	1.52	0.058	170.7	0.008
25TCRC008	12.19	13.72	1.53	0.042	189.1	0.014
25TCRC008	13.72	15.24	1.52	0.066	224.5	0.018
25TCRC008	15.24	16.76	1.52	0.095	325.7	0.029
25TCRC008	16.76	18.29	1.53	0.078	257.3	0.018
25TCRC008	18.29	19.81	1.52	0.025	124.5	0.012
25TCRC008	19.81	21.34	1.53	0.046	372.6	0.047
25TCRC008	21.34	22.86	1.52	0.036	210.4	0.025
25TCRC008	22.86	24.38	1.52	0.046	291.2	0.054
25TCRC008	24.38	25.91	1.53	0.02	173.3	0.068
25TCRC008	25.91	27.43	1.52	0.035	228.7	0.088
25TCRC008	27.43	28.96	1.53	0.325	201.6	0.044
25TCRC008	28.96	30.48	1.52	0.681	362.8	0.102
25TCRC008	30.48	32	1.52	0.023	283.3	0.015
25TCRC008	32	33.53	1.53	0.0075	329.8	0.021
25TCRC008	33.53	35.05	1.52	0.249	437.6	0.03
25TCRC008	35.05	36.58	1.53	0.049	394.3	0.014
25TCRC008	36.58	38.1	1.52	0.143	270.2	0.046
25TCRC008	38.1	39.62	1.52	0.082	187.9	0.016
25TCRC008	39.62	41.15	1.53	0.032	276.2	0.025
25TCRC008	41.15	42.67	1.52	0.105	441.6	0.019
25TCRC008	42.67	44.2	1.53	0.129	607	0.018
25TCRC008	44.2	45.72	1.52	0.16	495.8	0.016
25TCRC008	45.72	47.24	1.52	0.078	354.4	0.018
25TCRC008	47.24	48.77	1.53	0.438	888.6	1.26
25TCRC008	48.77	50.29	1.52	0.048	2735.9	0.103
25TCRC008	50.29	51.82	1.53	0.081	748	0.019
25TCRC008	51.82	53.34	1.52	0.0075	1427.4	0.03
25TCRC008	53.34	54.86	1.52	0.858	712	1.08
25TCRC008	54.86	56.39	1.53	0.594	1103.2	0.028

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC008	56.39	57.91	1.52	0.66	693.4	0.111
25TCRC009	0	1.52	1.52		670.9	0.052
25TCRC009	1.52	3.05	1.53	0.223	612.2	0.051
25TCRC009	3.05	4.57	1.52	0.087	611	0.024
25TCRC009	4.57	6.1	1.53	0.075	289.3	0.013
25TCRC009	6.1	7.62	1.52	0.05	244.8	0.01
25TCRC009	7.62	9.14	1.52	0.048	237.5	0.029
25TCRC009	9.14	10.67	1.53	0.056	124.5	0.009
25TCRC009	10.67	12.19	1.52	0.076	238.6	0.017
25TCRC009	12.19	13.72	1.53	0.028	201.9	0.013
25TCRC009	13.72	15.24	1.52	0.107	210.7	0.016
25TCRC009	15.24	16.76	1.52	0.042	130.7	0.012
25TCRC009	16.76	18.29	1.53	0.033	193.5	0.018
25TCRC009	18.29	19.81	1.52	0.08	219.5	0.018
25TCRC009	19.81	21.34	1.53	0.022	149.2	0.01
25TCRC009	21.34	22.86	1.52	0.089	348.7	0.029
25TCRC009	22.86	24.38	1.52	0.052	251.5	0.016
25TCRC009	24.38	25.91	1.53	0.081	270.1	0.018
25TCRC009	25.91	27.43	1.52	0.167	516.5	0.019
25TCRC009	27.43	28.96	1.53	0.073	278.9	0.007
25TCRC009	28.96	30.48	1.52	0.06	396.6	0.01
25TCRC009	30.48	32	1.52	0.08	538.1	0.031
25TCRC009	32	33.53	1.53	0.088	486.8	0.015
25TCRC009	33.53	35.05	1.52	0.064	339.2	0.024
25TCRC009	35.05	36.58	1.53	0.111	490.7	0.037
25TCRC009	36.58	38.1	1.52	0.042	276.7	0.018
25TCRC009	38.1	39.62	1.52	0.083	419.6	0.033
25TCRC009	39.62	41.15	1.53	0.268	399.7	2.28
25TCRC009	41.15	42.67	1.52	1.689	646.3	9.28
25TCRC009	42.67	44.2	1.53	1.858	892.7	2.26
25TCRC009	44.2	45.72	1.52	1.276	850.1	17.68
25TCRC009	45.72	47.24	1.52	0.381	374.5	0.097
25TCRC009	47.24	48.77	1.53	0.063	276.5	0.03
25TCRC009	48.77	50.29	1.52	0.066	382.2	0.056
25TCRC009	50.29	51.82	1.53	0.107	512.8	0.028
25TCRC009	51.82	53.34	1.52	0.127	755.4	0.026

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC009	53.34	54.86	1.52	0.278	677	0.027
25TCRC009	54.86	56.39	1.53	0.282	463.3	0.021
25TCRC009	56.39	57.91	1.52	0.542	700.1	0.017
25TCRC010	0	1.52	1.52		623.7	0.04
25TCRC010	1.52	3.05	1.53	0.08	356.2	0.032
25TCRC010	3.05	4.57	1.52	0.064	457.8	0.04
25TCRC010	4.57	6.1	1.53	0.135	573.7	0.023
25TCRC010	6.1	7.62	1.52	0.728	1752.1	0.059
25TCRC010	7.62	9.14	1.52	0.053	435.8	0.023
25TCRC010	9.14	10.67	1.53	0.108	604.1	0.014
25TCRC010	10.67	12.19	1.52	0.024	173.1	0.009
25TCRC010	12.19	13.72	1.53	0.04	202.6	0.01
25TCRC010	13.72	15.24	1.52	0.805	1059	0.047
25TCRC010	15.24	16.76	1.52	1.952	1394.3	1.31
25TCRC010	16.76	18.29	1.53	1.059	1633	0.68
25TCRC010	18.29	19.81	1.52	1.172	1642.6	0.119
25TCRC010	19.81	21.34	1.53	0.53	1919.3	0.042
25TCRC010	21.34	22.86	1.52	0.631	1710.8	0.06
25TCRC010	22.86	24.38	1.52	0.73	1569.7	0.073
25TCRC010	24.38	25.91	1.53	0.27	1104	0.04
25TCRC010	25.91	27.43	1.52	0.354	964.4	0.051
25TCRC010	27.43	28.96	1.53	1.162	1902.8	0.122
25TCRC010	28.96	30.48	1.52	0.795	1470.1	0.084
25TCRC010	30.48	32	1.52	0.958	874.7	0.135
25TCRC010	32	33.53	1.53	0.953	2459.7	0.4
25TCRC010	33.53	35.05	1.52	0.097	582.3	0.021
25TCRC010	35.05	36.58	1.53	0.138	667.1	0.024
25TCRC010	36.58	38.1	1.52	0.05	389.9	0.045
25TCRC010	38.1	39.62	1.52	0.118	445.1	0.037
25TCRC010	39.62	41.15	1.53	0.062	500	0.061
25TCRC010	41.15	42.67	1.52	0.07	547.4	0.062
25TCRC010	42.67	44.2	1.53	0.228	893.6	0.021
25TCRC010	44.2	45.72	1.52	0.388	944.9	0.16
25TCRC010	45.72	47.24	1.52	0.106	939.1	0.084
25TCRC010	47.24	48.77	1.53	0.178	627.1	0.025
25TCRC010	48.77	50.29	1.52	0.126	761.7	0.143

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC010	50.29	51.82	1.53	0.856	508.9	2.71
25TCRC010	51.82	53.34	1.52	0.338	793.9	0.023
25TCRC010	53.34	54.86	1.52	0.544	1415.7	0.042
25TCRC010	54.86	56.39	1.53	0.327	1407	0.025
25TCRC010	56.39	57.91	1.52	0.387	1478	0.035
25TCRC010	57.91	59.44	1.53	0.209	1518	0.022
25TCRC010	59.44	60.96	1.52	0.575	2016.6	0.086
25TCRC010	60.96	62.48	1.52	1.016	1520.9	0.039
25TCRC010	62.48	64.01	1.53	0.104	1348.7	0.027
25TCRC010	64.01	65.53	1.52	0.419	1965.2	0.034
25TCRC010	65.53	67.06	1.53	1.776	756	0.126
25TCRC010	67.06	68.58	1.52	0.853	832.4	0.034
25TCRC010	68.58	70.1	1.52	0.39	1127.2	0.023
25TCRC010	70.1	71.63	1.53	0.352	674.9	0.017
25TCRC010	71.63	73.15	1.52	0.265	1906.1	0.04
25TCRC010	73.15	74.68	1.53	0.11	840.2	0.014
25TCRC010	74.68	76.2	1.52	0.379	877.1	0.011
25TCRC014	0	3.05	3.05	0.631	1259.4	0.023
25TCRC014	3.05	4.57	1.52	0.578	1256.1	0.031
25TCRC014	4.57	6.1	1.53	0.949	1816.6	0.086
25TCRC014	6.1	7.62	1.52	0.431	1415	0.02
25TCRC014	7.62	9.14	1.52	0.297	799.6	0.04
25TCRC014	9.14	10.67	1.53	0.172	729.9	0.011
25TCRC014	10.67	12.19	1.52	0.249	760.6	0.012
25TCRC014	12.19	13.72	1.53	0.404	816.9	0.033
25TCRC014	13.72	15.24	1.52	0.598	1504.2	0.024
25TCRC014	15.24	16.76	1.52	0.736	1568.8	0.04
25TCRC014	16.76	18.29	1.53	0.525	1290.1	0.028
25TCRC014	18.29	19.81	1.52	0.698	1355.4	0.34
25TCRC014	19.81	21.34	1.53	0.505	1297.1	0.139
25TCRC014	21.34	22.86	1.52	0.567	1240.5	0.077
25TCRC014	22.86	24.38	1.52	0.347	1230.7	0.076
25TCRC014	24.38	25.91	1.53	0.295	909.7	0.033
25TCRC014	25.91	27.43	1.52	0.323	994	0.014
25TCRC014	27.43	28.96	1.53	0.487	1023.3	0.03
25TCRC014	28.96	30.48	1.52	0.316	1070.4	0.019

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC014	30.48	32	1.52	0.485	1283.5	0.035
25TCRC014	32	33.53	1.53	0.734	1770.5	0.4
25TCRC014	33.53	35.05	1.52	0.801	1367.5	0.013
25TCRC014	35.05	36.58	1.53	0.588	1251.2	0.011
25TCRC014	36.58	38.1	1.52	0.271	900	0.022
25TCRC014	38.1	39.62	1.52	1.398	1335.8	0.017
25TCRC014	39.62	41.15	1.53	1.681	1624.3	0.153
25TCRC014	41.15	42.67	1.52	0.802	1136.6	0.28
25TCRC014	42.67	44.2	1.53	1.514	1623.9	0.087
25TCRC014	44.2	45.72	1.52	0.426	823.7	0.11
25TCRC014	45.72	47.24	1.52	1.307	2052.1	0.116
25TCRC014	47.24	48.77	1.53	0.966	2334.8	0.052
25TCRC014	48.77	50.29	1.52	1.524	2993.1	0.152
25TCRC014	50.29	51.82	1.53	0.7	1632.2	0.046
25TCRC014	51.82	53.34	1.52	0.552	1260.9	0.078
25TCRC015	0	1.52	1.52	0.624		
25TCRC015	1.52	3.05	1.53	0.162	1311.3	0.017
25TCRC015	3.05	4.57	1.52	0.288	1088.8	0.016
25TCRC015	4.57	6.1	1.53	1.153	1717.3	0.029
25TCRC015	6.1	7.62	1.52	0.308	479.1	0.016
25TCRC015	7.62	9.14	1.52	0.823	973.4	0.014
25TCRC015	9.14	10.67	1.53	0.584	1147.8	0.014
25TCRC015	10.67	12.19	1.52	0.219	1349.3	0.027
25TCRC015	12.19	13.72	1.53	0.44	937.5	0.046
25TCRC015	13.72	15.24	1.52	0.225	690.6	0.034
25TCRC015	15.24	16.76	1.52	0.488	2023.4	0.051
25TCRC015	16.76	18.29	1.53	0.433	1689.9	0.032
25TCRC015	18.29	19.81	1.52	0.644	1475.4	0.084
25TCRC015	19.81	21.34	1.53	0.447	2015.6	0.106
25TCRC015	21.34	22.86	1.52	0.357	1158	0.02
25TCRC015	22.86	24.38	1.52	0.61	1772.8	0.025
25TCRC015	24.38	25.91	1.53	0.823	1828.7	0.089
25TCRC015	25.91	27.43	1.52	0.434	1498.1	0.051
25TCRC015	27.43	28.96	1.53	0.576	1235.6	0.06
25TCRC015	28.96	30.48	1.52	0.908	778.1	0.053
25TCRC015	30.48	32	1.52	0.288	1651	0.022

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC015	32	33.53	1.53	0.46	1180.2	0.014
25TCRC015	33.53	35.05	1.52	0.426	971.1	0.035
25TCRC015	35.05	36.58	1.53	0.436	1398.8	0.07
25TCRC015	36.58	38.1	1.52	0.749	1549.9	0.069
25TCRC015	38.1	39.62	1.52	0.366	982	0.035
25TCRC015	39.62	41.15	1.53	0.372	1908.5	0.115
25TCRC015	41.15	42.67	1.52	0.618	2092.7	0.31
25TCRC015	42.67	44.2	1.53	1.448	840.9	1.95
25TCRC015	44.2	45.72	1.52	1.499	2647.3	0.32
25TCRC015	45.72	47.24	1.52	1.98	1899.7	0.138
25TCRC015	47.24	48.77	1.53	0.886	1091.6	0.087
25TCRC015	48.77	50.29	1.52	0.782	1785.1	0.11
25TCRC019	0	1.52	1.52	0.115	360.6	0.36
25TCRC019	1.52	3.05	1.53	0.095	315.9	0.03
25TCRC019	3.05	4.57	1.52	0.102	449.4	0.017
25TCRC019	4.57	6.1	1.53	0.093	574	0.013
25TCRC019	6.1	7.62	1.52	0.028	428.6	0.036
25TCRC019	7.62	9.14	1.52	0.242	768.7	0.008
25TCRC019	9.14	10.67	1.53	0.105	274.3	0.126
25TCRC019	10.67	12.19	1.52	0.347	856	0.171
25TCRC019	12.19	13.72	1.53	0.427	1230.5	0.117
25TCRC019	13.72	15.24	1.52	0.151	1289.7	0.018
25TCRC019	15.24	16.76	1.52	1.708	2177.4	0.85
25TCRC019	16.76	18.29	1.53	0.142	1228.4	0.64
25TCRC019	18.29	19.81	1.52	0.036	362.9	0.046
25TCRC019	19.81	21.34	1.53	0.043	384.8	0.033
25TCRC019	21.34	22.86	1.52	0.0075	617.4	0.071
25TCRC019	22.86	24.38	1.52	0.015	736.3	0.088
25TCRC019	24.38	25.91	1.53	0.049	349.8	0.02
25TCRC019	25.91	27.43	1.52	0.0075	372.4	0.015
25TCRC019	27.43	28.96	1.53	0.0075	485.8	0.029
25TCRC019	28.96	30.48	1.52	0.029	366.8	0.018
25TCRC019	30.48	32	1.52	0.066	211.1	0.005
25TCRC019	32	33.53	1.53	0.098	435.3	0.008
25TCRC019	33.53	35.05	1.52	0.016	189.4	0.011
25TCRC019	35.05	36.58	1.53	0.0075	237.1	0.01

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC019	36.58	38.1	1.52	0.0075	211.6	0.008
25TCRC019	38.1	39.62	1.52	0.022	213.4	0.008
25TCRC019	39.62	41.15	1.53	0.065	271	0.013
25TCRC019	41.15	42.67	1.52	0.0075	223	0.026
25TCRC019	42.67	44.2	1.53	0.0075	149.5	0.03
25TCRC019	44.2	45.72	1.52	0.051	268.3	0.023
25TCRC019	45.72	47.24	1.52	0.021	203.1	0.012
25TCRC019	47.24	48.77	1.53	0.102	370.8	0.017
25TCRC019	48.77	50.29	1.52	0.045	218.6	0.008
25TCRC021	0	1.52	1.52			
25TCRC021	1.52	3.05	1.53	0.668	1035.7	0.089
25TCRC021	3.05	4.57	1.52	0.341	1124.4	0.111
25TCRC021	4.57	6.1	1.53	0.678	1365.4	0.18
25TCRC021	6.1	7.62	1.52	0.209	598.2	0.028
25TCRC021	7.62	9.14	1.52	0.468	669.5	0.25
25TCRC021	9.14	10.67	1.53	0.362	259.6	0.012
25TCRC021	10.67	12.19	1.52	0.461	330	0.017
25TCRC021	12.19	13.72	1.53	0.27	428.3	0.054
25TCRC021	13.72	15.24	1.52	0.351	325.4	0.125
25TCRC021	15.24	16.76	1.52	0.185	289.9	0.084
25TCRC021	16.76	18.29	1.53	0.198	273.5	0.021
25TCRC021	18.29	19.81	1.52	0.518	438.5	0.02
25TCRC021	19.81	21.34	1.53	0.177	213.8	0.079
25TCRC021	21.34	22.86	1.52	0.49	914.5	0.044
25TCRC021	22.86	24.38	1.52	0.474	900.6	0.082
25TCRC021	24.38	25.91	1.53	0.993	1229.3	0.099
25TCRC021	25.91	27.43	1.52	0.132	1114.9	0.118
25TCRC021	27.43	28.96	1.53	0.443	1622.9	0.143
25TCRC021	28.96	30.48	1.52	0.169	436.5	0.017
25TCRC021	30.48	32	1.52	0.664	1366.9	0.023
25TCRC021	32	33.53	1.53	0.148	803.3	0.03
25TCRC021	33.53	35.05	1.52	0.606	1429.3	0.45
25TCRC021	35.05	36.58	1.53	0.211	254.1	0.132
25TCRC021	36.58	38.1	1.52	0.581	862.5	0.08
25TCRC021	38.1	39.62	1.52	0.231	1124	0.132
25TCRC021	39.62	41.15	1.53	0.443	869.5	0.143

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC021	41.15	42.67	1.52	0.862	1594.6	0.052
25TCRC021	42.67	44.2	1.53	0.934	1118.7	0.14
25TCRC021	44.2	45.72	1.52	0.618	906.9	0.039
25TCRC021	45.72	47.24	1.52	0.045	471.2	0.016
25TCRC021	47.24	48.77	1.53	0.189	544.6	0.01
25TCRC021	48.77	50.29	1.52	0.217	318.8	0.008
25TCRC021	50.29	51.82	1.53	0.429	1609.6	0.012
25TCRC021	51.82	53.34	1.52	0.736	1509.3	0.014
25TCRC021	53.34	54.86	1.52	0.712	1930.5	0.012
25TCRC021	54.86	56.39	1.53	1.355	1112.8	0.014
25TCRC021	56.39	57.91	1.52	0.476	791.3	0.016
25TCRC021	57.91	59.44	1.53	1.32	1582.2	0.019
25TCRC021	59.44	60.96	1.52	0.027	239.2	0.01
25TCRC022	0	1.52	1.52	0.21	653.6	0.039
25TCRC022	1.52	3.05	1.53	0.017	218.2	0.017
25TCRC022	3.05	4.57	1.52	0.075	295.4	0.022
25TCRC022	4.57	6.1	1.53	0.073	766.3	0.073
25TCRC022	6.1	7.62	1.52	0.075	501.8	0.028
25TCRC022	7.62	9.14	1.52	0.036	176.5	0.012
25TCRC022	9.14	10.67	1.53	0.026	264.2	0.015
25TCRC022	10.67	12.19	1.52	0.048	218.5	0.011
25TCRC022	12.19	13.72	1.53	0.092	351.1	0.007
25TCRC022	13.72	15.24	1.52	0.028	181.7	0.006
25TCRC022	15.24	16.76	1.52	0.096	418.9	0.009
25TCRC022	16.76	18.29	1.53	0.055	474.1	0.01
25TCRC022	18.29	19.81	1.52	0.048	234.4	0.006
25TCRC022	19.81	21.34	1.53	0.064	345.4	0.007
25TCRC022	21.34	22.86	1.52	0.066	373.6	0.009
25TCRC022	22.86	24.38	1.52	0.051	300.8	0.009
25TCRC022	24.38	25.91	1.53	0.053	344.5	0.008
25TCRC022	25.91	27.43	1.52	0.0075	187.1	0.006
25TCRC022	27.43	28.96	1.53	0.084	317.6	0.005
25TCRC022	28.96	30.48	1.52	0.0075	304.8	0.01
25TCRC022	30.48	32	1.52	0.0075	196.2	0.006
25TCRC022	32	33.53	1.53	0.027	231.1	0.007
25TCRC022	33.53	35.05	1.52	0.0075	231.6	0.009

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC022	35.05	36.58	1.53	0.019	236.3	0.012
25TCRC022	36.58	38.1	1.52	0.042	259.1	0.03
25TCRC022	38.1	39.62	1.52	0.046	333.5	0.051
25TCRC022	39.62	41.15	1.53	0.102	446.2	0.019
25TCRC022	41.15	42.67	1.52	0.098	224.8	0.01
25TCRC022	42.67	44.2	1.53	0.039	481.8	0.022
25TCRC022	44.2	45.72	1.52	0.04	403.8	0.019
25TCRC022	45.72	47.24	1.52	0.0075	596.1	0.048
25TCRC022	47.24	48.77	1.53	0.197	644.5	0.036
25TCRC022	48.77	50.29	1.52	0.179	585.3	0.027
25TCRC022	50.29	51.82	1.53	0.08	463	0.039
25TCRC022	51.82	53.34	1.52	0.043	360.4	0.037
25TCRC022	53.34	54.86	1.52	0.576	635.3	0.052
25TCRC022	54.86	56.39	1.53	0.134	394.8	0.035
25TCRC022	56.39	57.91	1.52	0.274	524.9	0.096
25TCRC022	57.91	59.44	1.53	0.088	548.6	0.06
25TCRC022	59.44	60.96	1.52	0.101	380.6	0.03
25TCRC023	0	1.52	1.52			
25TCRC023	1.52	3.05	1.53	0.166	459.4	0.057
25TCRC023	3.05	4.57	1.52	0.039	291	0.02
25TCRC023	4.57	6.1	1.53	0.042	465.3	0.028
25TCRC023	6.1	7.62	1.52	0.037	246.9	0.016
25TCRC023	7.62	9.14	1.52	0.024	228.1	0.014
25TCRC023	9.14	10.67	1.53	0.022	146.4	0.012
25TCRC023	10.67	12.19	1.52	0.027	333.6	0.026
25TCRC023	12.19	13.72	1.53	0.041	154.4	0.011
25TCRC023	13.72	15.24	1.52	0.0075	170.1	0.01
25TCRC023	15.24	16.76	1.52	0.016	152.6	0.008
25TCRC023	16.76	18.29	1.53	0.027	134.2	0.008
25TCRC023	18.29	19.81	1.52	0.0075	114.8	0.007
25TCRC023	19.81	21.34	1.53	0.021	226.6	0.011
25TCRC023	21.34	22.86	1.52	0.023	178.5	0.008
25TCRC023	22.86	24.38	1.52	0.0075	170.3	0.008
25TCRC023	24.38	25.91	1.53	0.052	229.6	0.014
25TCRC023	25.91	27.43	1.52	0.017	227.6	0.009
25TCRC023	27.43	28.96	1.53	0.067	230	0.007

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC023	28.96	30.48	1.52	0.038	118.3	0.005
25TCRC023	30.48	32	1.52	0.027	147.8	0.004
25TCRC023	32	33.53	1.53	0.02	157.2	0.006
25TCRC023	33.53	35.05	1.52	0.024	127.9	0.007
25TCRC023	35.05	36.58	1.53	0.029	350.5	0.022
25TCRC023	36.58	38.1	1.52	0.042	156.4	0.01
25TCRC023	38.1	39.62	1.52	0.106	353.1	0.017
25TCRC023	39.62	41.15	1.53	0.079	284.1	0.008
25TCRC023	41.15	42.67	1.52	0.019	132.5	0.006
25TCRC023	42.67	44.2	1.53	0.053	208.7	0.008
25TCRC023	44.2	45.72	1.52	0.026	178.7	0.01
25TCRC023	45.72	47.24	1.52	0.167	350	0.015
25TCRC023	47.24	48.77	1.53	0.168	474	0.032
25TCRC023	48.77	50.29	1.52	0.079	274.8	0.012
25TCRC024	0	1.52	1.52	0.189	428.7	0.057
25TCRC024	1.52	3.05	1.53	0.054	376.1	0.023
25TCRC024	3.05	4.57	1.52	0.0075	389.3	0.025
25TCRC024	4.57	6.1	1.53	0.047	327.7	0.021
25TCRC024	6.1	7.62	1.52	0.106	800.6	0.058
25TCRC024	7.62	9.14	1.52	0.096	355.9	0.018
25TCRC024	9.14	10.67	1.53	0.031	995.2	0.047
25TCRC024	10.67	12.19	1.52	0.0075	363.1	0.021
25TCRC024	12.19	13.72	1.53	0.018	307.4	0.018
25TCRC024	13.72	15.24	1.52	0.027	292.3	0.015
25TCRC024	15.24	16.76	1.52	0.056	292.2	0.016
25TCRC024	16.76	18.29	1.53	0.0075	313.4	0.016
25TCRC024	18.29	19.81	1.52	0.068	270.2	0.016
25TCRC024	19.81	21.34	1.53	0.063	296	0.01
25TCRC024	21.34	22.86	1.52	0.098	350.7	0.01
25TCRC024	22.86	24.38	1.52	0.042	221.6	0.007
25TCRC024	24.38	25.91	1.53	0.028	224.3	0.006
25TCRC024	25.91	27.43	1.52	0.016	215.3	0.007
25TCRC024	27.43	28.96	1.53	0.03	198.1	0.008
25TCRC024	28.96	30.48	1.52	0.069	243.3	0.01
25TCRC024	30.48	32	1.52	0.03	135.9	0.007
25TCRC024	32	33.53	1.53	0.035	177.2	0.006

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC024	33.53	35.05	1.52	0.038	131.5	0.005
25TCRC024	35.05	36.58	1.53	0.092	237.9	0.056
25TCRC024	36.58	38.1	1.52	0.04	224.8	0.015
25TCRC024	38.1	39.62	1.52	0.056	270.1	0.017
25TCRC024	39.62	41.15	1.53	0.053	225.4	0.013
25TCRC024	41.15	42.67	1.52	0.134	331.9	0.02
25TCRC024	42.67	44.2	1.53	0.126	445.6	0.014
25TCRC024	44.2	45.72	1.52	0.118	314.2	0.013
25TCRC024	45.72	47.24	1.52	0.239	527.8	0.023
25TCRC024	47.24	48.77	1.53	0.163	361.6	0.032
25TCRC024	48.77	50.29	1.52	0.053	104.3	0.015
25TCRC025	1.52	3.05	1.53	0.198	427.7	0.091
25TCRC025	3.05	4.57	1.52	0.159	419.8	0.037
25TCRC025	4.57	6.1	1.53	0.286	735.6	0.043
25TCRC025	6.1	7.62	1.52	0.246	414.9	0.024
25TCRC025	7.62	9.14	1.52	0.13	295.2	0.013
25TCRC025	9.14	10.67	1.53	0.146	553	0.026
25TCRC025	10.67	12.19	1.52	0.045	212.3	0.007
25TCRC025	12.19	13.72	1.53	0.108	333.1	0.01
25TCRC025	13.72	15.24	1.52	0.02	295.5	0.021
25TCRC025	15.24	16.76	1.52	0.035	283	0.057
25TCRC025	16.76	18.29	1.53	0.0075	453.3	0.101
25TCRC025	18.29	19.81	1.52	0.055	332.2	0.084
25TCRC025	19.81	21.34	1.53	0.12	545.8	0.43
25TCRC025	21.34	22.86	1.52	0.263	594.4	0.73
25TCRC025	22.86	24.38	1.52	0.043	540.8	0.035
25TCRC025	24.38	25.91	1.53	0.021	367.2	0.022
25TCRC025	25.91	27.43	1.52	0.096	555.6	0.039
25TCRC025	27.43	28.96	1.53	0.049	346	0.025
25TCRC025	28.96	30.48	1.52	0.049	324.4	0.027
25TCRC025	30.48	32	1.52	0.221	888.8	0.038
25TCRC025	32	33.53	1.53	0.252	281.2	5.89
25TCRC025	33.53	35.05	1.52	0.286	212.5	0.13
25TCRC025	35.05	36.58	1.53	0.136	469.4	0.03
25TCRC025	36.58	38.1	1.52	0.063	176.2	0.022
25TCRC025	38.1	39.62	1.52	0.039	114.5	0.018

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC025	39.62	41.15	1.53	0.05	55.6	0.011
25TCRC025	41.15	42.67	1.52	0.016	113.7	0.016
25TCRC025	42.67	44.2	1.53	0.113	457.1	0.021
25TCRC025	44.2	45.72	1.52	0.095	284.8	0.013
25TCRC025	45.72	47.24	1.52	0.027	98	0.019
25TCRC025	47.24	48.77	1.53	0.029	108.9	0.015
25TCRC025	48.77	50.29	1.52	0.064	260.6	0.012
25TCRC025	50.29	51.82	1.53	0.096	600.8	0.023
25TCRC025	51.82	53.34	1.52	0.21	495.2	0.029
25TCRC025	53.34	54.86	1.52	0.037	142	0.023
25TCRC026	0	1.52	1.52	0.29	602.5	0.052
25TCRC026	1.52	3.05	1.53	0.217	521.7	0.143
25TCRC026	3.05	4.57	1.52	0.259	589.7	0.08
25TCRC026	4.57	6.1	1.53	0.186	447.5	0.074
25TCRC026	6.1	7.62	1.52	0.112	297.6	0.033
25TCRC026	7.62	9.14	1.52	0.062	385.3	0.015
25TCRC026	9.14	10.67	1.53	0.155	844.5	0.015
25TCRC026	10.67	12.19	1.52	0.104	619.8	0.014
25TCRC026	12.19	13.72	1.53	0.065	279.6	0.014
25TCRC026	13.72	15.24	1.52	0.032	410.3	0.036
25TCRC026	15.24	16.76	1.52	0.173	727.1	5.23
25TCRC026	16.76	18.29	1.53	0.195	1006.9	1.87
25TCRC026	18.29	19.81	1.52	0.083	408.6	0.047
25TCRC026	19.81	21.34	1.53	0.305	921.8	0.11
25TCRC026	21.34	22.86	1.52	0.092	820	0.068
25TCRC026	22.86	24.38	1.52	0.397	2058.5	1
25TCRC026	24.38	25.91	1.53	0.243	1041.2	0.053
25TCRC026	25.91	27.43	1.52	0.083	307.4	0.029
25TCRC026	27.43	28.96	1.53	0.17	877.1	0.037
25TCRC026	28.96	30.48	1.52	0.097	768	0.018
25TCRC026	30.48	32	1.52	0.172	631.3	0.013
25TCRC026	32	33.53	1.53	0.127	722	0.012
25TCRC026	33.53	35.05	1.52	0.15	291.7	0.023
25TCRC026	35.05	36.58	1.53	0.0075	245.2	0.016
25TCRC026	36.58	38.1	1.52	0.016	561.6	0.023
25TCRC026	38.1	39.62	1.52	0.074	381	0.011

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC026	39.62	41.15	1.53	0.016	663.9	0.02
25TCRC026	41.15	42.67	1.52	0.237	1049.9	0.064
25TCRC026	42.67	44.2	1.53	0.312	494.3	0.019
25TCRC026	44.2	45.72	1.52	0.55	458.4	0.022
25TCRC026	45.72	47.24	1.52	0.997	708.3	0.025
25TCRC026	47.24	48.77	1.53	0.937	545.4	0.027
25TCRC026	48.77	50.29	1.52	1.113	619.5	0.028
25TCRC026	50.29	51.82	1.53	1.143	1145.7	0.04
25TCRC028	0	1.52	1.52	0.105	426	0.05
25TCRC028	1.52	3.05	1.53	0.08	518.5	0.045
25TCRC028	3.05	4.57	1.52	0.091	501.2	0.044
25TCRC028	4.57	6.1	1.53	0.129	408.6	0.035
25TCRC028	6.1	7.62	1.52	0.05	208.6	0.018
25TCRC028	7.62	9.14	1.52	0.063	287.2	0.018
25TCRC028	9.14	10.67	1.53	0.136	402.5	0.025
25TCRC028	10.67	12.19	1.52	0.076	310.2	0.018
25TCRC028	12.19	13.72	1.53	0.117	626.9	0.05
25TCRC028	13.72	15.24	1.52	0.063	340.2	0.015
25TCRC028	15.24	16.76	1.52	0.283	522.5	1.04
25TCRC028	16.76	18.29	1.53	0.443	549.2	11.3
25TCRC028	18.29	19.81	1.52	0.211	751	0.052
25TCRC028	19.81	21.34	1.53	0.087	798.6	0.044
25TCRC028	21.34	22.86	1.52	0.245	1390.5	0.26
25TCRC028	22.86	24.38	1.52	0.138	1294.7	0.08
25TCRC028	24.38	25.91	1.53	0.025	857.7	0.059
25TCRC028	25.91	27.43	1.52	0.064	863.6	0.053
25TCRC028	27.43	28.96	1.53	0.096	1545.1	0.147
25TCRC028	28.96	30.48	1.52	0.048	568.6	0.051
25TCRC028	30.48	32	1.52	0.103	1249.9	0.056
25TCRC028	32	33.53	1.53	0.201	1125.2	0.03
25TCRC028	33.53	35.05	1.52	0.0075	703.5	0.018
25TCRC028	35.05	36.58	1.53	0.377	536.4	0.021
25TCRC028	36.58	38.1	1.52	0.163	253.4	0.011
25TCRC028	38.1	39.62	1.52	0.117	450.9	0.013
25TCRC028	39.62	41.15	1.53	0.437	147.7	0.061
25TCRC028	41.15	42.67	1.52	0.446	338.4	0.093

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC028	42.67	44.2	1.53	0.121	705.4	0.019
25TCRC028	44.2	45.72	1.52	0.067	414.7	0.012
25TCRC028	45.72	47.24	1.52	0.168	431.9	0.006
25TCRC028	47.24	48.77	1.53	0.036	318.2	0.006
25TCRC028	48.77	50.29	1.52	0.039	547.3	0.017
25TCRC029	1.52	3.05	1.53		481.8	0.086
25TCRC029	3.05	4.57	1.52	0.094	202.1	0.017
25TCRC029	4.57	6.1	1.53	0.0075	58.4	0.01
25TCRC029	6.1	7.62	1.52	0.04	194.7	0.019
25TCRC029	7.62	9.14	1.52	0.0075	147.5	0.018
25TCRC029	9.14	10.67	1.53	0.017	118.4	0.017
25TCRC029	10.67	12.19	1.52	0.025	160	0.02
25TCRC029	12.19	13.72	1.53	0.0075	213.3	0.023
25TCRC029	13.72	15.24	1.52	0.043	253.1	0.023
25TCRC029	15.24	16.76	1.52	0.043	164.3	0.012
25TCRC029	16.76	18.29	1.53	0.0075	118.2	0.013
25TCRC029	18.29	19.81	1.52	0.23	517.7	0.031
25TCRC029	19.81	21.34	1.53	0.13	706.3	0.024
25TCRC029	21.34	22.86	1.52	0.077	627.5	0.014
25TCRC029	22.86	24.38	1.52	0.078	357.6	0.012
25TCRC029	24.38	25.91	1.53	0.105	419.2	0.018
25TCRC029	25.91	27.43	1.52	0.098	388.4	0.02
25TCRC029	27.43	28.96	1.53	0.086	557.5	0.022
25TCRC029	28.96	30.48	1.52	0.028	283	0.027
25TCRC029	30.48	32	1.52	0.068	405.4	0.051
25TCRC029	32	33.53	1.53	0.101	471.3	0.081
25TCRC029	33.53	35.05	1.52	0.0075	214.7	0.037
25TCRC029	35.05	36.58	1.53	0.206	562.6	0.118
25TCRC029	36.58	38.1	1.52	0.404	370.7	10.92
25TCRC029	38.1	39.62	1.52	0.722	1061.5	1.69
25TCRC029	39.62	41.15	1.53	0.055	277.5	0.082
25TCRC029	41.15	42.67	1.52	0.1	294	0.043
25TCRC029	42.67	44.2	1.53	0.015	402.2	0.043
25TCRC029	44.2	45.72	1.52	0.0075	359.2	0.035
25TCRC029	45.72	47.24	1.52	0.163	495.5	0.67
25TCRC029	47.24	48.77	1.53	0.328	648.8	0.173

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC029	48.77	50.29	1.52	0.028	372.6	0.042
25TCRC029	50.29	51.82	1.53	0.058	226.3	0.014
25TCRC029	51.82	53.34	1.52	0.043	116.1	0.011
25TCRC029	53.34	54.86	1.52	0.047	314.7	0.018
25TCRC029	54.86	56.39	1.53	0.034	312.4	0.02
25TCRC029	56.39	57.91	1.52	0.167	570	0.013
25TCRC029	57.91	59.44	1.53	0.069	911.1	0.027
25TCRC029	59.44	60.96	1.52	0.074	1143.9	0.043
25TCRC030	0	1.52	1.52		674.8	0.31
25TCRC030	1.52	3.05	1.53		745.8	0.034
25TCRC030	3.05	4.57	1.52	0.022	160.8	0.012
25TCRC030	4.57	6.1	1.53	0.024	126	0.01
25TCRC030	6.1	7.62	1.52	0.019	169.9	0.018
25TCRC030	7.62	9.14	1.52	0.0075	105	0.007
25TCRC030	9.14	10.67	1.53	0.0075	164.4	0.014
25TCRC030	10.67	12.19	1.52	0.034	288.5	0.037
25TCRC030	12.19	13.72	1.53	0.015	103	0.014
25TCRC030	13.72	15.24	1.52	0.0075	87	0.01
25TCRC030	15.24	16.76	1.52	0.024	100.9	0.012
25TCRC030	16.76	18.29	1.53	0.038	206.1	0.026
25TCRC030	18.29	19.81	1.52	0.054	127.3	0.013
25TCRC030	19.81	21.34	1.53	0.053	234.4	0.016
25TCRC030	21.34	22.86	1.52	0.034	241.2	0.018
25TCRC030	22.86	24.38	1.52	0.073	288.5	0.018
25TCRC030	24.38	25.91	1.53	0.031	226.4	0.022
25TCRC030	25.91	27.43	1.52	0.139	650.5	0.049
25TCRC030	27.43	28.96	1.53	0.153	662.9	0.082
25TCRC030	28.96	30.48	1.52	0.09	521.1	0.026
25TCRC030	30.48	32	1.52	0.036	269.1	0.02
25TCRC030	32	33.53	1.53	0.277	508.8	1.48
25TCRC030	33.53	35.05	1.52	0.34	701	0.64
25TCRC030	35.05	36.58	1.53	0.056	493.6	0.24
25TCRC030	36.58	38.1	1.52	0.069	378.2	0.06
25TCRC030	38.1	39.62	1.52	0.049	233.6	0.041
25TCRC030	39.62	41.15	1.53	0.188	546.9	0.41
25TCRC030	41.15	42.67	1.52	0.209	653.4	1.09

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC030	42.67	44.2	1.53	0.15	726.6	0.05
25TCRC030	44.2	45.72	1.52	0.036	469.5	0.036
25TCRC030	45.72	47.24	1.52	0.099	753.5	0.057
25TCRC030	47.24	48.77	1.53	0.083	777.8	0.04
25TCRC030	48.77	50.29	1.52	0.115	823.2	0.041
25TCRC030	50.29	51.82	1.53	0.035	448.9	0.011
25TCRC030	51.82	53.34	1.52	0.102	847.7	0.026
25TCRC030	53.34	54.86	1.52	0.111	571	0.018
25TCRC030	54.86	56.39	1.53	0.693	508.6	0.056
25TCRC030	56.39	57.91	1.52	1.041	239.4	0.082
25TCRC030	57.91	59.44	1.53	0.449	101.9	0.052
25TCRC030	59.44	60.96	1.52	0.742	145.1	0.043
25TCRC030	60.96	62.48	1.52	0.425	157.2	0.051
25TCRC030	62.48	64.01	1.53	0.247	600.8	0.036
25TCRC031	0	1.52	1.52			
25TCRC031	1.52	3.05	1.53	0.113	497	0.02
25TCRC031	3.05	4.57	1.52	0.1	583.7	0.01
25TCRC031	4.57	6.1	1.53	0.223	784.4	0.009
25TCRC031	6.1	7.62	1.52	0.366	1383.8	0.097
25TCRC031	7.62	9.14	1.52	0.259	785.1	0.041
25TCRC031	9.14	10.67	1.53	0.139	651.6	0.018
25TCRC031	10.67	12.19	1.52	0.069	731	0.031
25TCRC031	12.19	13.72	1.53	0.06	432.9	0.027
25TCRC031	13.72	15.24	1.52	0.087	531.5	0.043
25TCRC031	15.24	16.76	1.52	0.051	554.3	0.049
25TCRC031	16.76	18.29	1.53	-0.015	248.5	0.013
25TCRC031	18.29	19.81	1.52	0.061	307	0.019
25TCRC031	19.81	21.34	1.53	0.03	243.4	0.017
25TCRC031	21.34	22.86	1.52	0.045	257.2	0.014
25TCRC031	22.86	24.38	1.52	0.071	381.2	0.014
25TCRC031	24.38	25.91	1.53	0.128	662.5	0.025
25TCRC031	25.91	27.43	1.52	-0.015	410.5	0.016
25TCRC031	27.43	28.96	1.53	0.083	552.1	0.014
25TCRC031	28.96	30.48	1.52	0.119	803.2	0.016
25TCRC031	30.48	32	1.52	0.146	896.5	0.025
25TCRC031	32	33.53	1.53	0.207	838	0.04

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC031	33.53	35.05	1.52	0.458	1102.5	0.094
25TCRC031	35.05	36.58	1.53	0.719	1956.5	0.061
25TCRC031	36.58	38.1	1.52	0.311	594.7	0.027
25TCRC031	38.1	39.62	1.52	0.726	788.3	0.066
25TCRC031	39.62	41.15	1.53	0.377	796.7	0.025
25TCRC031	41.15	42.67	1.52	0.643	546.6	0.044
25TCRC031	42.67	44.2	1.53	0.909	377.6	0.99
25TCRC031	44.2	45.72	1.52	0.683	2252.1	0.33
25TCRC031	45.72	47.24	1.52	0.9	1373.7	1.65
25TCRC031	47.24	48.77	1.53	0.622	1541.1	0.85
25TCRC031	48.77	50.29	1.52	0.265	1225	0.027
25TCRC031	50.29	51.82	1.53	0.357	1313.9	0.021
25TCRC031	51.82	53.34	1.52	0.334	1023.8	0.023
25TCRC031	53.34	54.86	1.52	0.45	1357.2	0.046
25TCRC031	54.86	56.39	1.53	1.054	1344.3	0.035
25TCRC031	56.39	57.91	1.52	0.761	943.4	0.022
25TCRC031	57.91	59.44	1.53	1.079	494.3	0.034
25TCRC031	59.44	60.96	1.52	0.746	535.1	0.014
25TCRC031	60.96	62.48	1.52	0.656	517.2	0.025
25TCRC031	62.48	64.01	1.53	0.159	1207.8	0.046
25TCRC031	64.01	65.53	1.52	0.138	1122.9	0.025
25TCRC033	0	1.52	1.52		973.3	0.172
25TCRC033	1.52	3.05	1.53	0.48	997.5	0.063
25TCRC033	3.05	4.57	1.52	0.721	1034.8	0.063
25TCRC033	4.57	6.1	1.53	0.053	565.3	0.028
25TCRC033	6.1	7.62	1.52	0.885	988	0.04
25TCRC033	7.62	9.14	1.52	0.483	1273.6	0.027
25TCRC033	9.14	10.67	1.53	0.74	800	0.067
25TCRC033	10.67	12.19	1.52	0.318	431.6	0.058
25TCRC033	12.19	13.72	1.53	0.176	486.4	0.021
25TCRC033	13.72	15.24	1.52	0.163	601.5	0.02
25TCRC033	15.24	16.76	1.52	0.12	245.3	0.012
25TCRC033	16.76	18.29	1.53	0.107	573	0.027
25TCRC033	18.29	19.81	1.52	0.072	593.2	0.082
25TCRC033	19.81	21.34	1.53	0.28	1253.4	0.097
25TCRC033	21.34	22.86	1.52	0.342	1622.2	0.085

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC033	22.86	24.38	1.52	0.325	1119.3	0.022
25TCRC033	24.38	25.91	1.53	0.241	1322.9	0.32
25TCRC033	25.91	27.43	1.52	0.512	2119.5	0.142
25TCRC033	27.43	28.96	1.53	0.489	244	0.72
25TCRC033	28.96	30.48	1.52	0.146	277.9	0.126
25TCRC033	30.48	32	1.52	0.25	494.5	0.131
25TCRC033	32	33.53	1.53	0.563	533.2	0.07
25TCRC033	33.53	35.05	1.52	0.792	1205.4	0.206
25TCRC033	35.05	36.58	1.53	1.272	1328.8	0.103
25TCRC033	36.58	38.1	1.52	1.107	1530.4	0.107
25TCRC033	38.1	39.62	1.52	0.816	1683.5	0.045
25TCRC033	39.62	41.15	1.53	1.002	2850.7	0.105
25TCRC033	41.15	42.67	1.52	1.05	2750	0.119
25TCRC033	42.67	44.2	1.53	0.688	1141.5	0.034
25TCRC033	44.2	45.72	1.52	1.628	1338.1	0.134
25TCRC033	45.72	47.24	1.52	1.163	2128.4	0.182
25TCRC033	47.24	48.77	1.53	1.459	3107.6	0.207
25TCRC033	48.77	50.29	1.52	0.485	1189.3	0.012
25TCRC033	50.29	51.82	1.53	0.577	1275.8	0.018
25TCRC033	51.82	53.34	1.52	0.536	1326.9	0.014
25TCRC033	53.34	54.86	1.52	0.674	1341.6	0.015
25TCRC033	54.86	56.39	1.53	0.439	2405.7	0.04
25TCRC033	56.39	57.91	1.52	0.688	1258.9	0.058
25TCRC033	57.91	59.44	1.53	1.044	1245.2	0.11
25TCRC033	59.44	60.96	1.52	1.909	267.7	4.85
25TCRC033	60.96	62.48	1.52	3.517	1375.6	1.03
25TCRC033	62.48	64.01	1.53	1.135	1565.3	2.59
25TCRC033	64.01	65.53	1.52	0.289	1234.1	0.046
25TCRC033	65.53	67.06	1.53	0.134	578.8	0.015
25TCRC033	67.06	68.58	1.52	0.179	1087	0.049
25TCRC033	68.58	70.1	1.52	0.172	663.5	0.015
25TCRC048	0	1.52	1.52		1465.7	0.084
25TCRC048	1.52	3.05	1.53	0.162	478.7	0.041
25TCRC048	3.05	4.57	1.52	0.113	357.2	0.021
25TCRC048	4.57	6.1	1.53	0.109	1066.1	0.062
25TCRC048	6.1	7.62	1.52	0.136	631.6	0.043

HoleID	SampleID	From M	To M	Au g/t Photonassay	Sb %	As ppm
25TCRC048	7.62	9.14	1.52	0.081	1323.2	0.08
25TCRC048	9.14	10.67	1.53	0.162	2061.4	0.089
25TCRC048	10.67	12.19	1.52	0.252	1910.9	0.071
25TCRC048	12.19	13.72	1.53	0.665	1280.7	0.052
25TCRC048	13.72	15.24	1.52	0.89	916	0.078
25TCRC048	15.24	16.76	1.52	1.972	1811.5	0.1
25TCRC048	16.76	18.29	1.53	0.67	1608.2	0.094
25TCRC048	18.29	19.81	1.52	0.253	1631.7	0.079
25TCRC048	19.81	21.34	1.53	0.741	782.4	0.185
25TCRC048	21.34	22.86	1.52	0.594	1044.3	0.062
25TCRC048	22.86	24.38	1.52	0.592	885.8	0.043
25TCRC048	24.38	25.91	1.53	0.365	1458	0.064
25TCRC048	25.91	27.43	1.52	0.127	990.9	0.05
25TCRC048	27.43	28.96	1.53	0.118	697	0.027
25TCRC048	28.96	30.48	1.52	0.136	520	0.027
25TCRC048	30.48	32	1.52	0.086	964.8	0.027
25TCRC048	32	33.53	1.53	0.073	1084.3	0.024
25TCRC048	33.53	35.05	1.52	0.125	915.3	0.03
25TCRC048	35.05	36.58	1.53	0.587	1173	0.049
25TCRC048	36.58	38.1	1.52	1.185	665.4	0.044
25TCRC048	38.1	39.62	1.52	0.228	385.7	0.07
25TCRC048	39.62	41.15	1.53	0.113	553.5	0.096
25TCRC048	41.15	42.67	1.52	0.086	320.8	0.034
25TCRC048	42.67	44.2	1.53	0.132	341.4	0.043
25TCRC048	44.2	45.72	1.52	0.152	994.8	0.05
25TCRC048	45.72	47.24	1.52	0.048	813	0.039
25TCRC048	47.24	48.77	1.53	0.114	424.3	0.018
25TCRC048	48.77	50.29	1.52	0.054	332.4	0.024